PAPER • OPEN ACCESS

Supramolecular structure of polymer binders and composites: targeted control based on the hierarchy

To cite this article: Larisa Matveeva and Yuri Belentsov 2017 IOP Conf. Ser.: Earth Environ. Sci. 90 012104

View the article online for updates and enhancements.

You may also like

- Widely accessible 3D printing technologies in chemistry, biochemistry and pharmaceutics: applications, materials and prospects Evgeniy G. Gordeev and Valentine P.

Ananikov

- Interpenetrated Gel Polymer Binder for High Performance Silicon Anodes in Lithium-Ion Batteries Jiangxuan Song, Zhaoxin Yu, Qingquan Huang et al.
- An Efficient Two-Polymer Binder for High-Performance Silicon Nanoparticle-Based Lithium-Ion Batteries: A Systematic Case Study with Commercial Polyacrylic Acid and Polyvinyl Butyral Polymers Anna Urbanski, Ahmad Omar, Jing Guo et al.





DISCOVER how sustainability intersects with electrochemistry & solid state science research



This content was downloaded from IP address 3.134.118.95 on 07/05/2024 at 12:19

Supramolecular structure of polymer binders and composites: targeted control based on the hierarchy

Larisa Matveeva¹ and Yuri Belentsov²

¹Saint Petersburg State University of Architecture and Civil Engineering, Vtoraya Krasnoarmeiskaya str. 4. St. Petersburg, 190005, Russia ²Emperor Alexander I St. Petersburg State Transport University, Moskovskyave., 9, Saint Petersburg, 190031, Russia

E-mail: lar.ma2011@yandex.ru

Abstract. The article discusses the problem of targeted control over properties by modifying the supramolecular structure of polymer binders and composites based on their hierarchy. Control over the structure formation of polymers and introduction of modifying additives should be tailored to the specific hierarchical structural levels. Characteristics of polymer materials are associated with structural defects, which also display a hierarchical pattern. Classification of structural defects in polymers is presented. The primary structural level (nano level) of supramolecular formations is of great importance to the reinforcement and regulation of strength characteristics.

1. Introduction

Despite the rapid development of polymer science, the problem of targeted control over the supramolecular structure in manufacturing tailored polymer and composite materials still remains unsolved. We need to determine, which methods and techniques of impact on the structure of the material and composite are preferable and efficient under various technological conditions and during operation. These pending problems, as well as the others, reduce the performance capabilities of engineering polymeric materials and composites, reduce their efficiency and ultimately hinder the widespread introduction of novel advanced materials into the building practice.

Progress in the development of building polymer composite materials is feasible under condition of understanding the mechanisms of structure formation and the role of supramolecular structures in the resulting set of material properties, as well as upon identifying the effective tools for regulation and control over the supramolecular structure. This knowledge is indispensable in designing building materials with desired set of properties, in development of modern production technologies for polymerbased composite materials [1, 2]. Determination of the basic patterns in the design chain for engineering polymer composites: "composition – structure/modification – manufacturing technology for materials or products – properties – application" defines the objective and content of the present work.

2. Literaturere View

Structural and defect hierarchy as a prerequisite for the level-based structure modification of polymers and composites

The structure of polymeric materials is commonly interpreted as the spatial positioning of structural elements - macromolecules, units, and clusters that form a macroscopic polymeric substance. According

Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

to modern concepts, the organization of polymer matter should be considered as a set of progressively complexified structures. Thus, the polymer substance has a certain hierarchy of supramolecular structures represented by successively increasing multi-molecular formations and complexified structural elements of these formations. The levels of supramolecular structures and their structural elements can be classified according to the following criteria: 1) geometric; 2) thermodynamic (stability in a given specific system); 3) kinetic (time of transition from one structural state to another and the lifetime of a structural element).

Changing the structure of one subsystem is associated with changes in properties and behavior of other structural formations; that is why the discrete behavior pattern of complex hierarchically-structured polymeric material went unnoticed for so long and does not always clearly demonstrate itself [3]. In the process of operation, a polymeric substance is modified under the influence of external factors and its supramolecular structure is rearranged. Separate hierarchical levels of the structure are rearranged rather independently. When the capability of one structural level is completely exhausted, the subsequent levels are reorganized. Discreteness of structural rearrangement is confirmed by data on the deformation fractures values observed and described by G. M. Bartenev [4].

Studies of the fracture micromechanics in polymeric materials by small-angle X-ray scattering method have demonstrated that sub-microcracks of up to 10 nanometers length develop rapidly in weak spots of the structure under load. This coincides with the dimensions of primary molecular structures. However, even numerous sub-microcracks are not as destructive and hazardous as large microcracks, which expand, spread and merge together, resulting in the final destruction of the material.

According to Peterlin [5], the microcrack nuclei are associated with the boundaries of primary structures and defects located at the joints of the subsequent structural levels. These are the weakest sites of supramolecular structures. The discrete spectrum of sub-microcracks and microcracks dimensions (length) was identified and described by G. M. Bartenev and other researchers [6, 7].

The relatively ordered structure of amorphous thermosetting polymers is evidenced by measurements of mechanical, electrical and other properties. Measuring the characteristics of macroscopic properties of non-crystalline polymers suggests that both the elements with dimensions in the tens of angstroms, and substantially larger structural formations and elements are retained in their structure [8].

3. Results and Discussion

We have consistently observed a discrete pattern of modifying characteristics of polymer materials and composites in the study of mechanical properties as a function of the rate of loading material. Under a slow and gradual increase of the loading rate, a discrete (stepwise) pattern of modifying characteristics was established in samples in ultimate tension and compression strength test series. We attribute this feature to the manifestation of discrete deformation of the structural elements at various macromolecule packing levels and the associated certain structural defects.

The macromolecular substance can not be perfect in structure, due to the bulkiness of the macromolecules as such, and their packing failures caused by a number of reasons. The supramolecular polymer structure has many defects and these are different at different structural levels.

Thus, taking into account the hierarchical organization of the polymer matter and the relative independence, i.e., discreteness of the structural elements levels, it becomes obvious that structural defects of the system also follow the law of hierarchy. In other words, there is a hierarchy of structural defects in polymers [3].

When the operating polymeric materials are exposed to external factors, we have to deal with the destruction of weak or defective structural elements with the hierarchical pattern and dependence. It can be argued with high probability that different external impacts keep with the weaknesses of different structural levels, i.e., hierarchy-specific structural defects.

If we turn to classifying structural defects, their hierarchy can be represented as follows:

1. Defects of the short-range order (nano scale) associated with failed conformations in the arrangement of separate fragments of the polymer chain and its primary packing, the asymmetry and gaps in spatial mesh nodes formation; these defects range in dimensions from one to tens nanometers and are comparable with the structural elements of the initial (primary) structural-level of macromolecule packing.

2. Defects of the globular order emerge under the packing failures of globules (folded into conglomerates or coils of long sections of polymer chains) and their mutual arrangement. These defects tend to concentrate at the boundaries of globular elements, are formed mainly by the chain ends, free (unpacked) parts of macromolecules belonging to the transit chains and low molecular weight macromolecules. Dimensions of these defects are comparable with those of the globules and can range from tens to hundreds nanometers.

3. Defects related to the asymmetry and failures of cluster associates, packs, domain and other 3-D structures of the higher level, resulting from inherent stresses, as well as defects at the boundaries between the polymer binder and the filler. Defectiveness (i.e., deviation from the crystallographic order) in the pack or the domain is very high. Dimensions of these defects can be estimated in tenths of microns. 4. Structural macro defects of the composite or the entire product are macropores, foreign inclusions, macro cracks, etc. Dimensions of these defects are even greater and can reach tens and hundreds of

microns. Structural defects can derive from various causes; they can be formed by different conditions, in the same way as the structural elements:

1) geometry, for example, steric constraints, spatial disorder; in these cases, geometrical defects can have different dimensions depending on the structural hierarchy level;

2) thermodynamics, due to thermodynamic instability of formations (groups and clusters) and fluctuations at different structural levels. The higher hierarchical level of the structure (of a more long-range order) is the more defective, due to the accumulation and summation of defects;

3) kinetics – in the case when the rate of relaxation processes is less than the rate of structural elements formation.

The basic concept or idea in designing durable polymeric materials and composites with enhanced operational properties should consider the hierarchy of structural levels in polymers, as well as the hierarchy of structural defects.

Actions aimed at reducing the structural defectiveness, or any effects on the structural packing of the polymer macromolecules should be undertaken purposefully, with consideration to its hierarchy and depending on the defective structure level to be controlled or "cured". When designing tailored composite materials, it needs to be coordinated with a specific destructive impact factor using the structure modifiers effective at a given hierarchical level (see *Table*).

With view of these findings, the primary structural level (nano level) of supramolecular formations gains particular importance, since it (i.e., its defectiveness) determines the further macromolecule packing and the defectiveness of the subsequent structural elements. This level has long been neglected in the studies concerned with structure modification of polymeric materials. The situation has changed with the development of nanotechnology and its methods, because the nano scale supramolecular organization can be addressed only by nanotechnology methods, i.e., by nano dimensional particles. Here, the related problem of their dispersion and distribution in the mass of polymeric material comes to the foreground.

Formerly conventional modifiers of the polymer structure – rubbers and elastomers, ordinary powdered solids are inappropriate for nano structural modifications, due to the large size of their particles. Oligomeric systems (rubbers and elastomers) are extremely hard (almost impossible) to be dispersed properly and to be distributed uniformly in the cubic content of the polymer matrix, in order to ensure their action at the nano scale level.

Their action is manifested at the micro level at best, which is quite sufficient for certain (small) improvements of physical and mechanical characteristics. But this would not affect significantly the physical, chemical and mechanical properties. Hence, numerous attempts to achieve a greater effect by nano modification of polymeric materials were unsuccessful

doi:10.1088/	/1755-13	15/90/1	/012104
--------------	----------	---------	---------

Structural level	Modifiers	Characteristics of structural levels	Associated characteristics
Y	<u> </u>		
1.	Monomolecular	Chains and chain fragments of	Chemical and radiation
Submicroscopic	substances or	polymers. Structure is determined	resistance, aging,
level (molecular	nanoparticles	by packing and stacking of	resistance to thermal-
or nanolevel)	dispersed by	individual chains and fragments	oxidative degradation
	nanotechnology	with dimensions up to tens of	
	methods	nanometers (nanostructure).	
		Dimensions of defects – nanometers	
II.	Alloying micro	Globular formations, interglobular	Hardness, microre
Mesoscopic level	additives and	boundaries, contact zones between	sistance, diffusion
(topological or	oligomers injected	chain-packed structures of the	properties, heat
cluster)	by liquid-phase	polymer, mesopores, sub-	resistance, bio stability
,	methods	microcracks. Dimensions of defects	ý j
		up to 0.1 microns	
III.	Micro-sized	Polymeric substance with	Modulus of elasticity.
Supramolecular	particles and	inclusions between domains and	modulus of shear.
level (formation	additives. fillers.	packs of microparticles (cement.	brittleness, creep, water
of associates.	polymers.	mineral dust. "aerosil".	absorption. low
domains and	elastomers.	microsphere, etc.). Dimensions of	temperature resistance
packs)	rubbers, etc.	defects can reach tens of microns	·····F · · · · · · · · · · · · · · · ·
IV.	Powdered fillers	Polymer composite with inclusions	Mechanical properties:
Macroscopic level	and additives	of filler grains, micro- and	strength, wear resistance.
(composite or	introduced by a	macropores and microcracks with	resistance to static and
finished building	common method	dimensions of $0.01-1.0$ mm the	dynamic loads shocks
product)	The structure is	Characteristic dimension of	abrasion etc
product)	largely determined	structural defects is comparable	ubrusion, etc.
	by the product	with that of grain size macro- and	
	technology and	micropores	
	introduction of	meropores	
	additives		
	auditives		

 Table 1. Hierarchy of structure, defect levels of polymer matrices and composites, and associated properties

From the standpoint of the above described representations, the mechanism of reinforcing rigid polymer matrices by rubber modifiers becomes obvious and clear, since it improves mechanical characteristics of elasticized (rubber-modified) plastics and resins.

Rubbers form an independent phase in the thermo set (e.g., epoxy) matrix and thus prevent merging and spreading "large" microcracks responsible for mechanical destruction of the polymer. According to G. M. Bartenev [4], dimensions significant for the mechanical destruction of micro-cracks, are at least ~ $30 \cdot 10^{-4}$ mm, which corresponds to the third structural level of the hierarchy structure presented in our table. Dimensions of defects and cracks (matching with the data of G. M. Bartenev) are large enough and can be "cured" by macromolecules of rubbers and oligomers. Cracks (microcracks) of the second level are ~ $1-3 \cdot 10^{-4}$ mm. The first, i.e., the initial level (sub-microcracks) has dimensions of ~ 0.3– $0.2 \cdot 10^{-4}$ mm, which corresponds to the primary structural level, and, accordingly, modifiers with the same particle size, i.e., nanoparticles are required. The discrete spectrum of cracks in polymeric systems was recorded by a number of researchers [6-9, 11].

At the same time, there have been very successful attempts to improve significantly the properties of polymeric materials by nanomo difying with carbon nano particles, fulleranes, and similar nano modifiers. [12-14].

Thus, it became obvious that strengthening and protection of the molecular structure at the nan oscale level needs nanostructural modifiers, i.e., chemical compounds and substances that can be spread within

doi:10.1088/1755-1315/90/1/012104

the polymer nanostructure. This is a great challenge. For example, these requirements are met by nanoparticles of liquid molecular organosilanes and siloxanes (subjected to ultra dispersion, for example, using the ultrasound) [15-17].

Our experience has shown that small quantities of organosilanes and organosiloxanes have good compatibility with most polymers in melts or solutions. Saturated silanes and siloxanes are chemically inert and generally do not react with molecules of the polymer binder. During formation of the supra molecular structure, they are expelled to the disorder zones and get localized in structural defects. In the case when the modifier particle size is within the nanometer dimension, these substances can settle at the primary nano structural level of polymer matter. This level is the least defective; it is responsible for chemical and physical-chemical processes of polymer destruction, i.e., ageing, thermal oxidative degradation, photo destruction, resistance to aggressive gaseous media, chemical factors, etc.). The number of structural defects at the initial hierarchical level is estimated by the fraction of a percent and does not exceed 0.5-1.5%. Stabilizing additives, antioxidants, ageing retarders, UV adsorbers, etc. are introduced into polymers in the same proportions (with a small margin allowing for the uneven distribution). The action of stabilizers is performed at the level of polymer macromolecules, i.e., within the primary structural level. Structural modifiers for "curing" the nano scale defects should be introduced approximately in the same quantities as stabilizing additives, i.e., from 0.5 up to 1,5% or slightly more.

The problem of detailed structure of polymers, which are traditionally viewed as amorphous, is still under discussion but the possible existence of ordered structural formations at different hierarchical levels in amorphous polymers is conclusively established.

Until recently, irregular and unstructured mass of heavily entangled coils (globules) with the excess free volume served as the conventional model of amorphous polymers. The physical properties of such systems are described by a single-phase statistical coil model. This model played an important role in the development of the theory of high elasticity, because the entanglement of molecules explains satisfactorily the expansion of the area of high elasticity against the increasing molecular weight, while the excess free volume – high values of coefficients of gas diffusion in amorphous vs. crystalline state. However, this model can not explain the irreversible plastic flow and the overestimated density values in amorphous polymers, as compared with those derived from the same model. The disadvantage of this model is that it does not provide for the presence of the experimentally observed regions of regularity, namely, structural aggregates of 50-100 Å in size [2, 3].

We have studied the effect of liquid organosilicon modifiers on the supra molecular structure of the epoxy binder. Alternating ordered formations of globular-type particles were detected with a scanning electron microscope in ED-20 dianeoligomer epoxy matrix consolidated with PEPA (polyethylene polyamine) amine hardener at room temperature (Fig.). The photomicrographs presented below demonstrate the epoxy matrix modification by organo siloxane, which leads to the formation of a more ordered structure containing significantly less pores and voids.

Distribution of organosiloxane particles and low molecular weight heat-resistant siloxane synthetic rubber across the matrix is clearly visible in the photomicrographs (see figure 1). Large particles are localized in the epoxy matrix as an independent phase; fine particles are distributed between the globules of epoxy macromolecules and in some cases form chained clusters, which corresponds with the above mentioned notions on the hierarchy in the supra molecular polymer structure.

In our view, structural organization of polymers (including those cross-linked orthermo setting) can be subdivided into at least three hierarchical levels and, consequently, include at least three types of ordered supra molecular structures. Accordingly, the polymer substance includes at least three hierarchical levels of structural defects.



Figure 1. Electron photomicrographs of supramolecular structures in ED-20 polyethylene polyamine epoxy matrix: a) initial (unmodified), X 20,000; b) organosiloxane-modified (1 % wt.), X 25,000; c) heat-resistant siloxane rubber-modified, X 20,000.

Certain physic -chemical and physic -mechanical (including strength) characteristics of the polymer substance, performance properties of the finished product are associated with defects in supra molecular, micro- and macrostructure and are determined by them. We have identified the following hierarchical structural levels:

1) Primary level (micro level or nano level) features a short-range order in the arrangement of chains fragments and macromolecules. Within the small spatial regions, groups of atoms and chain fragments are more or less ordered. The degree of disorder (defectiveness) at this level probably ranges from 0.5 to 2.5 % depending on technological parameters.

2) Meso level (or cluster) – pseudo crystals, packs and clusters, which are more often formed at above plasticization temperature, can emerge and disappear, due to fluctuations. These structural formations reveal a permanent dimensional distribution pattern. The degree of defectiveness at this level probably ranges from 10 to 20-30 %, i.e., is approximately greater by an order of magnitude; it depends mainly on the kinetic conditions of formation and the defectiveness of the preceding level.

3) Supramolecular level – associates of clusters and packs. The degree of defectiveness is even higher and is comparable with the degree of order but can as well exceed it (40-60 %). The structural defectiveness at this level depends on the defectiveness of the preceding levels and is associated with the external environmental factors.

4) The composite structure of the finished product is mainly determined by its manufacturing technology. The result of structure formation is a macrostructure of the finished composite or product, which depends on the entire set of technological factors, external impacts, as well as the internal conditions preceding its formation.

4. Conclusions

The above discussed features of the polymorphic and hierarchical structure of polymeric substances and structural defects yield several important implications.

First, the structural and physical heterogeneity creates a non-uniform distribution of reagents in the polymer matrix. Thus, low-molecular substances (oxygen, oxidation products, monomolecular stabilizing additives, etc.) are concentrated mainly in the sites where the initial order is absent, i.e., amorphous or defective zones of the polymer structure. The most reactive elements of macromolecules (oxidized groups, unsaturated bonds, etc.) are also located there. Local concentrations of chemical reagents in these zones may significantly differ from the average values.

Second, structural micro heterogeneity leads to widespread regions of various molecular motions within the polymer resulting in a broad set of kinetic constants and activation energies of elementary chemical reactions and physicochemical interactions occurring in different regions.

IOP Publishing

Third, structural-kinetic heterogeneity of polymers and the respective localization of reagents lead to the spatial localization of chemical reactions, i.e., to the formation of unique "microreactors", where the intensive processes of the polymer oxidation and destruction develop.

Modification of the structure of polymeric materials and composites, "curing" its defects should be tailored to specific hierarchical levels.

The above discussed theoretical principles concerning the discreteness and hierarchy of supramolecular structures, the hierarchy of structural defects, as well as special importance of primary structural formations (nano levels) to improve the operational properties of composite materials, methods of their modification and "curing" defects have been confirmed for various classes of materials, thermoplastic and thermosetting (epoxy and polyester polymer composites), and many others [3,18–20].

References

- Paturoev V V 1987 Polymer concretes (Moscow: Stroyizdat) 286p [1]
- [2] Solomatov V I, Bobryshev A N and HimmlerK.G 1988 Polymeric composite materials in construction Solomatov VIEd (Moscow: Stroyizdat) 312 p
- Ogrel L I 2006 PhD Thesis (Belgorod: BSTU) 414 p [3]
- [4] Bartenev G M 1984 Polymer strength and destruction mechanism (Moscow: Chemistry) 280p
- Peterlin A 1983 Ultra high modulus polymers Chemistry pp 205–240 [5]
- [6] Bartenev G M, Karimov S N, Narzullaev B M, Tsoy B and Shermatov D 1982 High-molecular compounds 24 A 9 pp 1981–1985
- [7] Bartenev G M, Karimov S N and Šermatov D 1983 Gesetzmäßigkeiten und Natur des Bruchs von Polyethylenterephthalat folien Acta Polymerika. V 34 Issue 1 pp 44-47
- [8] Vasileva OG, Nikulina LP, Gotlib EM, Artemenko SE and Ovchinnikova GP 2001 Concerning the structurization in modifiede poxy polymers Plastics. 3 p 28
- [9] Tamuzh V P and Kuksenko V S 1978 Polymer material destruction mechanics (Riga: Znanie) 294pp
- [10] Iartsev V P 2001 Operability prediction of polymer materials in parts and structures of buildings and structures (Tambov: TambovStateTechnicalUniversityPubl) 149pp
- Allen R C and Mandelkern L 1982 J. PolymerScience: Polym. Phys. 20 pp 1465–1484 [11]
- [12] Burunkova I E, Semiyna S A, Kaporskiy L N and Levichev V V 2008 Optic. journal 75 (10) pp 54 - 58
- [13] Amirov R R, Amirova L M, Bezzametnov O N and Gorbachuk V V 2012 Proceedings of the Kazan University Science Ser. Vol. 154 4 pp 71-79
- Amirov R R, Amirova L M, Bezzametnov O N and Gorbachuk V V 2012 Proceedings of the [14] Kazan University ScienceSer. Vol. 154 4 pp 71–79
- [15] Minko N I and Nartsev V M 2005 Obtainment method sand properties of nanoobjects (Belgorod: ShukhovBSTUPubl.) 105pp
- [16] Komarov S M 2000 Chemistry and life 5 pp 10–17
- Strokova V V, Ogrel L I, Iakho Li and Baode Zang 2009 Construction materials 9 pp 75–76 [17]
- [18] Akatenkov R V, Aleksashin V N and Anoshkin I V 2000 Coll. of abstracts Rusnanotech 9 pp 302-303
- [19] Pomogaylo A D, Rozenberg A S and Uflyand I E Metal nano particles in polymers (Moscow: Chemistry) 672 pp
- [20] Bobryshev A N, Zharin A A and Bobryshev A A 2005 Effect of epoxy modifier on polyurethane polymers Construction materials 6 pp 67–69