PAPER • OPEN ACCESS

Time-frequency analysis of acoustic emission signals generated by the Glass Fibre Reinforced Polymer Composites during the tensile test

To cite this article: G Świt et al 2017 IOP Conf. Ser.: Mater. Sci. Eng. 251 012002

View the article online for updates and enhancements.

You may also like

- <u>Comparative Analysis of the Reliability of</u> <u>Steel Structure with Pinned and Rigid</u> <u>Nodes Subjected to Fire</u> Katarzyna Kubicka, Urszula Rado, Waldemar Szanice et al.
- <u>Domestic hot water supply with air-source</u> <u>CO_heat pump</u>
 T Orzechowski, M Orzechowski, M Osowska et al.
- <u>Utilization of the UV laser with picosecond</u> <u>pulses for the formation of surface</u> <u>microstructures on elastomeric plastics</u> B Antoszewski, S Tofil, M Scendo et al.





DISCOVER how sustainability intersects with electrochemistry & solid state science research



This content was downloaded from IP address 3.145.206.169 on 28/04/2024 at 19:11

Time-frequency analysis of acoustic emission signals generated by the Glass Fibre Reinforced Polymer Composites during the tensile test

G Świt¹, A Adamczak¹, A Krampikowska¹

¹Kielce University of Technology, Faculty of Civil Engineering and Architecture, Aleja Tysiąclecia Państwa Polskiego 7, 25-314 Kielce, Poland

E-mail: aadamczak@tu.kielce.pl

Abstract. Fibre reinforced polymer composites are currently dominating in the composite materials market. The lack of detailed knowledge about their properties and behaviour in various conditions of exposure under load significantly limits the broad possibilities of application of these materials. Occurring and accumulation of defects in material during the exploitation of the construction lead to the changes of its technical condition. The necessity to control the condition of the composite is therefore justified. For this purpose, non-destructive method of acoustic emission can be applied. This article presents an example of application of acoustic emission method based on time analysis and time-frequency analysis for the evaluation of the progress of the destructive processes and the level of degradation of glass fibre reinforced composite tapes that were subject to tensile testing.

1. Introduction

A composite is a material consisting of two or more different materials: they are purposefully combined and they can be separated with the use of mechanical methods, distributed in a controlled manner in order to provide them with optimal properties, having properties that are unique and better than individual components. A continuous component of a composite is called a base or a matrix. Fibres or grains (particles) are embedded in the matrix, and they are called in accordance with their application: filler, reinforcement or reinforcing bar (rebar) [1].

Dynamically developing technology and constantly increasing needs and requirements of the industry force the development of new materials that would cut the production costs and that would be simultaneously characterised by better physical and/or chemical properties than traditional materials. Thanks to the increasing level of knowledge about the relationships that occur between the production technology, chemical composition of the components used for the production, and the structure and properties of the finished products, numerous new alloys, plastics and ceramic materials have been developed over the last two decades [2], [3].

Searching for new materials, thanks to the desired properties achieved during their production, intended for specific industrial applications, has led to rapid development of research on the widely understood issue of materials engineering, namely composite materials. Moreover, the progress in the methods of non-destructive tests related to composites, both at the stage of prefabrication and the diagnostics of load-bearing structures, conduces dissemination of this material in applications in construction [4], [5].

Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

IOP Publishing

Unique properties of polymer composites are appreciated by more and more recipients. The improvement of safety and economics of usage is the main motive of their increasing application in the industry. Many branches of industry are currently using the constantly widening family of composite materials, among these industries there are: construction industry, automotive, trail, aviation or arms industries [6], [7], [8].

Mechanical degradation of polymer composites, which is caused by prolonged permanent loads, is connected with the changes of the material structure that are local or that include the whole volume of the element's body. These changes are in the form of various types of discontinuity, including: debonding, matrix and fibres cracks and delamination [9], [10], [11].

For composites testing, a method of acoustic emission is useful. This method consists in recording elastic waves resulting from changes on micro- or macro-structural level of the material as a result of imposing external stimulus (load, the activity of external environment, etc.) in real time. AE method is a developing and widely applied diagnostic, non-destructive testing method (NDT) [12], [13], [14], [15], [16], [17], [18], [19], [20], [21], [22].

2. Materials and methods

2.1. Materials

Glass fibre reinforced composite tapes with cross-sections of 12x3 mm were the subject of the test. Test was carried out with the use of Zwick-Roell testing machine located at Kielce University of Technology. Tensile speed was 0.2 mm/min. The test included determining the tensile strength, indicating percentage elongation at rupture and determining modulus of elasticity.

The samples of the tapes for testing were prepared through double-sided sticking of bevelled sections of aluminium flat with the use of epoxy glue (Figure 1).

For the acquisition of acoustic emission signals, Vallen AMSY-5 measuring apparatus was used. Two broadband sensors were used, and they were mounted with a clamp on the central part of the sample. A layer of resin was applied on the surface of the contact. The accuracy of the working of apparatus was checked before carrying out the proper measurement. In the vicinity of each sensor, signals for testing the efficiency of the sensors and the correctness of their mounting were initiated. The source of those signals was graphite that was being broken, its diameter was 0.5 mm and it was made by Pentel company. It was stated that each sensor recorded AE signals with the amplitude of about 98 dB.



Figure 1. The sample of glass fibre tape for testing.

2.2. Time-frequency methods of vibration signals analysis

Programs analysing measurement data used by Vallen company are based mainly on waves analysis, using fast Fourier transform and wavelet (time-frequency) analysis. The basic technique of frequency analysis is Fourier transform. However, the disadvantage of this method is the lack of the possibility to determine the time of occurrence of effects caused by local non-stationarities of the signal. This inconvenience has been partially removed in Gabor transform, which is the modification of Fourier transform. On the other hand, the generalisation of Gabor transform is Short Time Fourier Transform (STFT), which is the following [23]:

$$S(b,f) = \int_{-\infty}^{+\infty} x(t) \cdot e^{-j2\pi ft} \cdot w(t-b)dt \tag{1}$$

In this transform, a localisation window w(t-b), was implemented, in which b parameter replaces the window in time domain. The function of the window can be any function which meets specific conditions. This window, because of its permanent width, turned out to be not much effective in the analysis of signals that simultaneously consist of components of low and high frequencies.

After implementing an additional scale parameter a to localisation window in Gabor transform, a continuous wavelet transform has been developed. An analysis function, $\Psi(\frac{t-b}{a})$, called a main wavelet, has a scale factor a, which causes the change of duration of a wavelet and the moving factor b, which changes the position of the wavelet on time axis. The equation therefore represents a band-pass filtration of the signal with the use of filters of different passbands. Wavelet transform is the following dual function:

 $WT(a,b) = \frac{1}{\sqrt{a}} \int_{-\infty}^{+\infty} x(t) \cdot \Psi\left(\frac{t-b}{a}\right) dt, \ a,b \in R, a \neq 0 \quad (2)$

The basic advantage of wavelet transform is an optimal compromise in selecting resolution in the domain of frequency and time. The modulus of wavelet transform of the signal presents the changes of vibration energy in the time and frequency function.

Wavelet theory has been in the focus of attention of both mathematicians and engineers for several years, apart from time-frequency analysis, it has a wide application in the fields of, among others, speech analysis, images recognition and it improves the quality of recordings, etc [24], [25], [26], [27].

3. Results and discussions

Table 1 and Figure 2 present the results of the tensile testing of glass fibre reinforced composite tapes. During the test, three stages of the deformation process were noticed:

- rupture of matrix
- delamination and dividing the fibres from the matrix
- rupture of fibres, causing the tape destruction

	Average coefficient		Average elongation
	of elasticity of tapes	Average tensile strength	at rupture
	[GPa]	[MPa]	[%]
The result of the test	59	600	<1,5

Table 1. The results of the tensile testing of tapes with glass fibre.



Figure 2. Dependency graph of force and displacement in time for the representative sample.

The evaluation of AE signals of the tested tapes was carried out in time-frequency domain, by determining two-dimensional spectrograms of spectral density. For the purpose of comparing the results, the spectrograms for one of the samples for two significantly different levels of count and absolute energy of the signals are presented. In this figure, the "a" symbol shows the results of the analysis of AE signals generated by the tape at the moment of time of 100 s, where the count is about 100 and the absolute energy of the signal is at the level of $2x10^5$ eu. The "b" symbol shows the results of the analysis of AE signals generated by the tape at the moment of time of 910 s, where the count is 10703 and the absolute energy of the signal is at the level of $5,1x10^9$ eu (Figure 3,4).



Figure 3. Dependency graph of count in time for representative sample.



Figure 4. Dependency graph of absolute energy of the signals in time for representative sample.

On the two-dimensional spectrograms of spectral density, time-frequency structures occurring in the range of frequency: (5 - 250) kHz for both cases that were considered are visible. The range of frequency of the structure at the moment of time of 100 s decreases along with coming to the end of the considered time window, and the structures at the moment of time of 910 s reach the frequencies on the level of 150 kHz in the whole analysed run (Figure 5a, 5b).



Figure 5. Two-dimensional spectrograms of spectral density of AE signals generated during the tensile test of a representative tape with glass fibre a) at the moment of time of 100 s b) at the moment of time of 910 s.

Frequency components between 75 kHz and 110 kHz for the moment of time of 100 s and 60 kHz to 125 kHz for the moment of time of 910 s have the highest values of amplitudes, whereby in the second case, two areas of occurrence of maximum values of the amplitudes can be distinguished. The analysis of the measurement results also proved that the signals corresponding to the activity of the elongated tape at the moment of time of 910 s have time-frequency structures of the highest amplitudes (Figure 5b). On the basis of the analysis of spectrograms determined for AE signals generated by the glass fibre tape at the moment of time of 910 s (Figure 5b), it was stated that explicit differences in their time-frequency structure occur. It was noticed that there was a substantial delamination of the acoustic structure of the analysis of the presented results, the signals generated by the tape at the moment of time of 910 s and different distribution of particular frequency structures in time. Based on the analysis of the presented results, the signals generated at the moment of time of 910 s are attributed to the rupture of matrix, while the signals generated at the moment of time of 910 s are attributed to the rupture of the fibers. Analyzing the time-frequency structures, the power of AE

density spectra was significantly higher at the moment of time of 910 s. In further investigations, a precise analysis of the frequency of damage of a given type and attributed them to specific damages is planned.

4. Conclusions

During the conducted tests, the lack of plastic reaction of glass fibre reinforced composite tapes on the loads and sudden destruction of the material after passing boundary deformations were observed. Composite materials are characterized by the lack of plastic range of their reaction to loads – the condition before the break is not signaled, the break occurs unexpectedly, after the violation of boundary deformations. The process of destruction itself can only be seen in laboratory tests under scanning microscope, and this hinders or even makes it impossible to diagnose reinforced constructions that are active in real conditions. It is substantiated by the necessity to control the state of the composite material on account of determining the conditions of safe exploitation of the construction. For this purpose, non-destructive testing (NDT) methods can be used, and they allow to determine the condition of the material periodically or in a continuous manner in real time. On the basis of the results presented in the article it can be stated that with the application of modern methods of digital image processing in the domain of time and in the time-frequency domain, there is a possibility to use the acoustic emission method to evaluate the condition of glass fibre composite tapes.

References

- Hollaway L C 2010 A review of the present and future utilisation of FRP composites in the civil infrastructure with reference to their important in-service properties *Construction and Building Materials* 24(12) pp 2419-45
- [2] 2007 fib. FRP reinforcement in RC structures *Féderation International du Béton, fib Task Group* 9.3 **40** p 147
- [3] Debaiky A S Nkurunziza G Benmokrane B and Cousin P 2006 Re-sidual Tensile Properties of GFRP Reinforcing Bars after Loading in Severe Environments *Journal of Composites* for Construction 10(5) pp 370-80
- [4] Cromwell J R Harries K A Shahrooz B M 2011 Environmental durability of externally bonded FRP materials intended for repair of concrete structures *Construction and Building Materials* 25(5) pp 2528-39
- [5] Kawada H Kobiki A Koyanagi J and Hosoi A 2005 Long-Term Durability of Polymer Matrix Composites Under Hostile Environments *Materials Science and Engineering* 412(1-2) pp 159–64
- [6] Ray B C 2006 Effects of Changing Environment and Loading Speed on Mechanical Behavior of FRP Composites *Reinforced Plastics and Composites* **25(12)** pp 1227-40
- [7] Yeonho P Young Hoon K Swoo-Heon L 2014 Long-Term Flexural Behaviors of GFRP Reinforced Concrete Polymers 14(6) pp 1773-93
- [8] Myers T J Kytömaa H K Smit T R 2007 Environmental stress-corrosion cracking of fiberglass: lessons learned from failures in the chemical industry *Journal of Hazardous Materials* 142(3) pp 695-704
- [9] Świt G 2000 Durability of stressed E glass fibre in alkaline medium *Recent Development* in Durability Analysis of Composite Systems Proceedings pp 473-76
- [10] Swit G 2004 Evaluation of compliance change in concrete beams reinforced by GRP using AE *Journal of Materials in Civil Engineering* **16(5)** pp 414-19
- [11] Aggelis D G Soulioti D V Sapouridis N Barkoula N M Paipetis A S Matikas T E 2011 Acoustic emission characterization of the fracture process in fibre reinforced concrete *Construction* and Building Materials 25(11) pp 4126-31
- [12] Bacharz M Trampczyński W 2016 Identification of Active Destructive Processes in Unloaded Early-Age Concrete with the Use of the Acoustic Emission Method Proceedings of 2016 Prognostics and System Health Management Conference (PHM-Chengdu) pp 1-6

- [13] 2002 Encyclopedia of Smart Materials vol 1. (red.Schwartz M.) pp 291-318
- [14] Kurzydłowski E J Boczkowska A et al. 2005 Monitoring of failures in the composites by nondestructive methods *Polymers* 50(4) pp 255 – 61
- [15] Gholizadeh S 2016 A review of non-destructive testing methods of composite materials *Procedia* Structural Integrity 1 pp 50-7
- [16] Goszczyńska B Świt G Trąmpczyński W 2015 Analysis of the microcracking process with the Acoustic Emission method with respect to the service life of reinforced concrete structures with the example of the RC beams BULLETIN OF THE POLISH ACADEMY OF SCIENCES-TECHNICAL SCIENCES 63(1) pp 55-63
- [17] Goszczyńska B Świt G Trąmpczyński W 2014 Application of the Acoustic Emission Method of identification and location of destructive processes to the monitoring concrete bridges 7th International Conference on Bridge Maintenance, Safety and Management (IABMAS) pp 688-94
- [18] Świt G Krampikowska A Chinh L M 2016 A Prototype System for Acoustic Emission-Based Structural Health Monitoring of My Thuan Bridge Prognostics and System Health Management Conference (PHM-Chengdu) pp 19-21
- [19] Świt G Krampikowska A 2016 Influence of the Number of Acoustic Emission Descriptors on the Accuracy of Destructive Process Identification in Concrete Structures *Prognostics and System Health Management Conference (PHM-Chengdu)*
- [20] Olaszek P Swit G Casas JR 2010 Proof load testing supported by acoustic emission 5th International Conference on Bridge Maintenance, Safety and Management (IABMAS) pp 484-94
- [21] Goszczyńska B Świt G Trąmpczyński W 2016 Application of the IADP acoustic emission method to automatic control of traffic on reinforced concrete bridges to ensure their safe operation ARCHIVES OF CIVIL AND MECHANICAL ENGINEER 16(4) pp 867-75
- [22] Goszczyńska B Świt G Trąmpczyński W Krampikowska A Tworzewska J Tworzewski P 2012 Experimental validation of concrete crack identification and location with acoustic emission method ARCHIVES OF CIVIL AND MECHANICAL ENGINEER 12(1) pp 23-8
- [23] Clotaire M Gueguen P 2009 Time-Frequency Analysis of Small Frequency Variations in Civil Engineering Structures Under Weak and Strong Motions Using a Reassignment Method Structural Health Monitoring 9(2) pp 159-71
- [24] Auger F Flandrin P Concalves P and Lenoine O 1996 TFTB for Matlab CNRS
- [25] Adamowski J Sun K 2010 Development of a coupled wavelet transform and neural network method for flow forecasting of non-perennial rivers in semi-arid watersheds *Journal* of Hydrology 390(1-2) pp 85-91
- [26] Starck J-L Bobin J 2009 Astronomical Data Analysis and Sparsity: from Wavelets to Compressed Sensing ASTRONOMICAL DATA ANALYSIS pp 1-7
- [27] Kimura R Terashima W et al. 1997 Diagnostic method for 2-stroke diesel engine by measurement of vibration on cylinder- jacket observation of change in normal vibration pattern *Journal* of MESJ 33(10)