#### PAPER • OPEN ACCESS

# Oil as Corrosion Inhibitor for Aluminium Alloy in Aggressive Environment

To cite this article: O. Sanni et al 2018 IOP Conf. Ser.: Mater. Sci. Eng. 391 012004

View the article online for updates and enhancements.

#### You may also like

- (Invited) Selective Response of Magnesium Corrosion Inhibitors Incorporated in PEO Coatings Bahram Vaghefinazari, Sviatlana V Lamaka, Endzhe Matykina et al.
- Multi-Scale Insight into Inhibition Mechanism of Benzo Derivatives in Chemical Mechanical Polishing of Copper Film Based on Experiments and Theoretical Calculations Jianghao Liu, Xinhuan Niu, Ni Zhan et al.
- (Digital Presentation) Investigation of Microstructure Dependent Inhibitor Adsorption Mechanism on Carbon Steel By in Situ Atomic Force Microscopy Huiru Wang, Bruce N Brown, Alain Pailleret et al.





DISCOVER how sustainability intersects with electrochemistry & solid state science research



This content was downloaded from IP address 3.129.19.251 on 04/05/2024 at 16:28

### Oil as Corrosion Inhibitor for Aluminium Alloy in Aggressive Environment

**O.SANNI, API POPOOLA, OSI FAYOMI** 

Department of Chemical, Metallurgical and Materials Engineering, Tshwane University of Technology, Pretoria, South Africa Corresponding author: tayo.sanni@yahoo.com

**ABSTRACT.** Corrosion processes are responsible for huge losses in industry. This deterioration of components results in loss of plant efficiency, total shutdown and aggressive damage in a number of industries. Though organic, inorganic and mixed material inhibitors were used for a long time to combat corrosion, the environmental toxicity of inorganic corrosion inhibitors has prompted the search for organic corrosion inhibitors. In search for this, the use of organic inhibitors is one of the best options of protecting metals and alloys against corrosion as it is environmentally acceptable, inexpensive and readily available. In this regards, silicon oil was used as inhibitor in this study. Weight loss, corrosion rate, inhibition efficiency and potentiodynamic polarization techniques were used in this study. The aluminium alloy samples exposed to the inhibitor showed a lower corrosion rate values and excellent polarization resistance as compared with the corrosion rate samples without inhibitor. The corrosion inhibition rate increases with increasing the concentration of the silicone oil. The adsorption isotherm was confirmed by Langmuir adsorption isotherm.

Keywords: Corrosion; Silicone oil; Inhibition; and Corrosion rate

#### 1. **INTRODUCTION**

Aluminum comprises eight percent of the earth's crust. The annual market of aluminium is 25 million tons which makes it one of the principal nonferrous metals in the metallurgy industry [1]. The applications of aluminium and its alloys varied from household to electrical engineering, packaging, transport and building [2-6]. Also, it demonstrates a good fatigue resistance as well as high strength to weight ratio. Aluminium resistance to corrosion in aqueous media can be attributed to a rapidly formed surface oxide film. Because the aluminium oxide layer is very thin, it is easily degraded by physical or chemical methods. On the contrary, this alloy is highly susceptible to corrosion because of the presence of inter metallic particles at the surface resulting in need for the development of several methods in order to enhance its resistance against corrosion [7, 8]. Efforts have been made to protect the corrosion of aluminium surface in different corrosive environments. Recently, the addition of inhibitors has been considered to be one of the most common approaches to hinder the corrosion of aluminium [9-13]. Aliphatic, aromatic amines and nitrogen heterocyclic molecules compounds have been widely reported as corrosion inhibitors of aluminum in aggressive media [14-16]. However, some of these compounds are costly and not environmentally friendly. In search for an alternative, environmentally friendly, protection for alluminium alloy, the present study aims to investigate the inhibition action of silicone oil and their protective

Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

performance for aluminium alloy in 3.5% NaCl solution using a variety of electrochemical tests; weight loss, corrosion rate, inhibition efficiency and potentiodynamic polarization techniques. Adsorption mechanism was also investigated.

#### 2. MATERIALS AND METHODS

#### 2.1. Materials and Sample Preparation

The aluminum alloy sheet with chemical composition shown in Table 1 below was mechanically press-cut into specimens of dimension 30 mm by 30mm by 0.3mm. All test plates of aluminium alloy samples were ultrasonically degreased in acetone for 15 min. After that, the aluminum alloy specimens were washed thoroughly with distilled water and dried. The specimens with an exposed area of  $1 \text{ cm}^2$  were used for potentiodynamic polarization tests. Analytical reagent grade of sodium chloride and double distilled water were used to prepare the corrosive medium. Molecular structures of silicone oil are shown in Figure 1.



Figure 1. Molecular structure of silicone oil

#### 2.2. Weight Loss Test

The aluminum alloy specimens in triplicate were immersed in a 3.5 % NaCl solution with and without different concentration (0.1-0.5 g/L) of silicone oil for 168 hours. The temperature was controlled by a thermostat aqueous bath at 304K. For all weight loss tests, the volume of prepared solution was 250 mL. After the immersion, all specimens were brought out from the solution, scrubbed with bristle brush under running water, then washed thoroughly with distilled water, dried in acetone, and weighed accurately. Minimum of three samples were tested and the average value was obtained. The corrosion rates and inhibition efficiency were determined from equations previously reported by [13].

Element	Compositions		
Si	0.157		
Fe	0.282		
Cu	0.0025		

-					
Table	1: Chemica	l composition	of aluminium	alloy (	(%wt)

The 1st International Conference on Engineering for Sustainable World (ICESW)

IOP Conf. Series: Materials Science and Engineering **391** (2018) 012004 doi:10.1088/1757-899X/391/1/012004

Mn	0.024
Mg	0.51
Cr	0.023
Ti	0.006
Ca	0.0011
Zr	0.002
V	0.0035
Al	Balance

#### 2.3. Electrochemical Measurements

The potentiodynamic polarization tests were carried out in a three-electrode cell system with a non-aqueous Ag/Ag electrode used as reference electrode, and a platinum wire used as counter electrode. The working electrode was mounted aluminium alloy sample. For each sample, measurements were performed in at least triplicate. The following electrochemical parameters were determined: corrosion current density (icorr), corrosion potential (Ecorr), and corrosion rate (CR). The corrosion inhibition effectiveness, IE, was calculated accordingly using equation reported elsewhere. All specimens were embedded in Teflon using epoxy resin and were prepared as rotating disc electrodes. Before the electrochemical measurements, all samples were mechanically polished with 1,200 grit emery paper, washed with double distilled water and put into the cell containing the studied solutions. There was an immersion in the solution for 1 h for the open circuit potential to reach a steady state. The polarization curves were obtained by changing potential from -250 mV to +250 mV with a scan rate of 0.5mV/s. The electrochemical experiments were performed using a Potentiostat/Galvanostat with NOVA software, Version 1.8. Each experiment was repeated at least three times to ensure the reproducibility.

#### 2.4 Adsorption Isotherm

To understand the adsorption mechanism of the corrosion resistance of aluminium alloy surface, the data obtained from the corrosion study were tested with several adsorption isotherms models including Langmuir, Frumkin, and Temkin. The surface coverage,  $\theta$ , was calculated using equation 1 below where  $\eta$  is the inhibition efficiency:

#### 3. **RESULTS AND DISCUSSION**

With the silicone oil concentration varying from 0.1 to 0.5 g/L in saline solution, the weight loss by the aluminium alloy in various concentration of silicone oil took the order of Control < 0.1 < 0.2 < 0.3 < 0.4 < 0.5.

The 1st International Conference on Engineering for Sustainable World (ICESW)IOP PublishingIOP Conf. Series: Materials Science and Engineering **391** (2018) 012004doi:10.1088/1757-899X/391/1/012004

#### **3.1. Adsorption Characteristics**

Inhibition efficiency of silicone oil falls within the first 96 hour but becomes linear after 120 hours. For the period of 96 hours the inhibition efficiency of silicone oil was averagely maintained at 70% and 83% respectively at 0.4 and 0.5g/L of silicone oil as indicated in Figures 2, 3 and 4. Corrosion rate of aluminum in various concentrations of silicone oil in the studied medium are in the order control > 0.1 > 0.2 > 0.3 > 0.4 > 0.5 as shown in Figure 4. As corrosion of aluminum alloy increases with time that of inhibitor decreases with inhibitor concentration. It was observed that out of the five concentrations of silicone oil that were tested for weight loss, 0.5g/L gave the highest efficiency. This implies that 0.5g/L concentration of silicone oil inhibited the aluminum alloy most and followed by 0.4g/L. The silicone oil contents are expected to have affinity to bind with the aluminum alloy coupon and adhered to its surface by chemical reactions thereby preventing direct attack by the medium.



Figure 2: Weight loss of aluminium alloy with time of immersion in 3.5% NaCl at 304K at different inhibitor concentration

Figure 4 indicated the higher inhibition efficiency potential of silicone oil to be higher with increase in its concentration. In Figure 3, corrosion rate of the samples with inhibitor decreased above the control at all the concentrations studied. The adsorption of this oil on the aluminium alloy surface reduces the rate of corrosion. It shows aluminium alloy has affinity for elements that made up its ore rather than organic constituents of silicone oil. The addition of the oil hindered the affinity of the aluminium alloy for the elemental components of the oil thereby reduced the adsorption of the components on the metal. Different oil has been reported to inhibit corrosion of metals [18-23]. Due to interaction between the metal and the oil there could be formation of a soluble compound which may stimulate corrosion rather than favor inhibition. Also the properties responsible for effective inhibition such as the number of adsorption may have been restructured. The ability of the silicone oil to reduce aluminium corrosion is shown in Figures 2, 3 and 4

This confirms that pure metals are ready to return to their ore or oxide state in the presence of required substances and in the absence of organic substance from oil with significant sodium content will retard adsorption of inhibitors on the metal surface.



Figure 3: Corrosion rates of aluminium in 3.5% NaCl at 304K at different inhibitor concentration



Figure 4: Percentage inhibition efficiency of aluminium in 3.5% NaCl at 304K at different inhibitor concentration

## Table 2. Data obtained from Tafel plot curves of aluminium alloy in 3.5%NaCl solution at different concentrations of silicone oil

**IOP** Publishing

	• •			
IOP Conf. Series: Materials Science an	d Engineerin	g <b>391</b> (2018) 012004	doi:10.1088/1757-	899X/391/1/012004

S/N	C (g/L)	Icorr	βc	βa	LPR Rp	-Ecorr	CR
		(A/cm2)	(V/dec)	(V/dec)	(Ωcm2)	(V)	(mm/yr)
1	Control	0.000802	0.60085	1.3086	175.96	-0.92732	3.7570
2	0.1	0.000235	0.27822	0.64902	359.87	-0.92732	2.7309
3	0.2	0.000164	0.02582	0.1081	86.79	-0.92732	1.9011
4	0.3	0.000156	0.20144	0.094419	178.57	-0.92732	1.8168
5	0.4	5.75E-05	0.24695	0.352	196.4	-0.92732	0.6679
6	0.5	4.28E-05	0.16668	0.15949	55.324	-0.92732	0.4974

Current density-potential curves were recorded to obtain information on the effectiveness of the silicone oil on the corrosion processes and its effect on the anodic and cathodic reactions. Figure 5 represent the anodic and cathodic polarization curves for the aluminium alloy immersed in 3.5% NaCl in the absence and presence of different concentrations of silicone oil at 304K. From these polarization curves the corrosion kinetic parameters such as corrosion current density (icorr), corrosion potential (Ecorr), anodic and cathodic Tafel slopes (ba, bc) were deduced by extrapolating Tafel's lines.



Figure 5. Tafel polarization curves of aluminium alloy in 3.5% NaCl solution in the absence and presence of different concentrations of silicone oil

The changes observed in the polarization curves in the presence of the inhibitor are usually used as criteria to classify inhibitors as anodic, cathodic or mixed. Figure 4 shows the shifting of The 1st International Conference on Engineering for Sustainable World (ICESW)IOP PublishingIOP Conf. Series: Materials Science and Engineering **391** (2018) 012004doi:10.1088/1757-899X/391/1/012004

corrosion potential (Ecorr) as dependent on inhibitor concentrations, while the general shape of anodic and cathodic curves in the absence and presence of the inhibitor is comparable. The curves are shifted towards lower current density values compared to that of the control solution, indicating the inhibition of the aluminium alloy. The decrease in corrosion rate associated with a shift of both cathodic and anodic plots of the polarization curves toward lower current densities, and a positive shift in corrosion potential, indicates that this oil acts as a mixed-type inhibitor. When the concentration of oil increases, the anodic branches make a sudden shift to more positive potential direction. The data in Table 2 show that the bc values are almost constant at different concentrations of inhibitor. This observation indicates that the mechanism of proton discharge reaction is not affected in the presence of silicone oil. Likewise, the constancy of the cathodic slope may have indicated that the hydrogen evolution reaction is activation controlled and that the inhibitor is absorbed by simply blocking the active sites of the aluminium surface [17]. In the anodic area, as the inhibitor concentration increases, there is a shift towards positive values of corrosion potential. However, the slight variation of ba near the shift of Ecorr toward anodic potentials may be attributed to the modification of the anodic process due to the formation of a protective film on the electrode surface rather than a simple adsorption on the active sites. The analysis of these results shows that the increase of silicone oil concentration decreases icorr, and consequently there is an increase of inhibition efficiency. The increase in efficiency may be due to the blocking effect on the surface by both adsorption and film formation mechanism, which decreases the effective area of attack.

#### **Adsorption Isotherm**

Adsorption characteristics are helpful in understanding the nature of corrosion inhibition and it can be deduced in the term of adsorption isotherm. By fitting the various adsorption isotherms into Freundlich, Temkin, Langmuir and Frumkin isotherms, the data were tested graphically. The process of adsorption occur when liquid or gas accumulates on the surface of a solid or liquid, forming a molecular or atomic film. In general, adsorption isotherm can be divided into two categories. First category occurs when the molecules adsorb but their chemical originality remains unchanged. In this state, the adsorption bond between inhibitor molecule and surface is fairly weak. The best fitted isotherm that describes the adsorption behavior of silicone oil on aluminium surface was Langmuir adsorption isotherm and it can be expressed by using the equation as described by [23].

It was found that the Langmuir adsorption model was the best fit with correlation coefficients above 0.858 for the temperature studied (Figure 6) while the others correlated are less than 0.602.

IOP Conf. Series: Materials Science and Engineering **391** (2018) 012004 doi:10.1088/1757-899X/391/1/012004





#### 4. CONCLUSION

Our study indicates that silicone oil acts as an effective corrosion inhibitor for aluminium alloy in 3.5% NaCl solution. The inhibition efficiency of the inhibitor concentration is in the order 0.5 > 0.4 > 0.3 > 0.2 > 0.1 > Control. Polarization tests indicated that this oil behaves as a mixed-inhibitor type with a predominant anodic effectiveness at higher concentration. The results obtained from weight loss measurements and electrochemical techniques were in reasonable agreement.

#### REFERENCES

- [1] Schutze, M, Wieser D. and Bender, R. Corrosion Resistance of Aluminium and Aluminium Alloys, Wiley –VCH (2010).
- [2] Gudic, S, Vrsalovic, L, Kliskic, M, Jerkovic, I, Radonic, A, and Zekic, M. 2016. Corrosion inhibition of AA5052 aluminium alloy in 0.5 M NaCl solution by different types of honey. Int. J. Electrochem. Sci., 11, 998–1011.
- [3] Rosliza, R, Nik, W.B.W, Izman, S and Prawoto, Y. 2010. Anti-corrosive properties of natural honey on Al–Mg–Si alloy in seawater. Curr. Appl. Phys. 10, 923–929.
- [4] Hill, J.A, Markley, T, Forsyth, M, Howlett, P.C and Hinton, B.R.W. 2011. Corrosion inhibition of 7000 series aluminium alloys with cerium diphenyl phosphate. J. Alloy. Compd., 509, 1683–1690.
- [5] Rosliza, R, Nik, W.B.W and Senin, H.B. 2008. The effect of inhibitor on the corrosion of aluminum alloys in acidic solutions. Mater. Chem. Phys., 107, 281–288.
- [6] Dabala, M, Ramous, E and Magrini, M. 2004. Corrosion resistance of cerium-based chemical conversion coatings on AA5083 aluminium alloy. Mater. Corros. 55, 381–386.
- [7] Oubaha, M, Varma, P.C.R., Duffy, B, Gasem, Z.M, and Hinder, S.J. 2014. Development of a novel hybrid aluminum-based sol-gel materials: application to the protection of

IOP Conf. Series: Materials Science and Engineering **391** (2018) 012004 doi:10.1088/1757-899X/391/1/012004

AA2024 T3 alloys in alkaline environment, Advances in Materials Physics and Chemistry 4, 75–84.

- [8] Davis, J.R. 1999. Corrosion of aluminium and aluminium alloys, ASM International, Materials Park, OH.
- [9] Oguzie, E.E, Onuoha, G.N and Ejike, E.N. 2007. Effect of gongronema latifolium extract on aluminium corrosion in acidic and alkaline media. Pigment Resin Technol., 36, 44– 49.
- [10] Al-Turkustani, A.M, Arab, S.T and Al-Dahiri, R.H. 2010. Aloe plant extract as environmentally friendly inhibitor on the corrosion of aluminum in hydrochloric acid in absence and presence of iodide ions. Mod. Appl. Sci., 4, 105–124.
- [11] Li, J, Hurley, B and Buchheit, R. 2015. Microelectrochemical characterization of the effect of rare earth inhibitors on the localized corrosion of AA2024-T3. J. Electrochem. Soc., 162, C563–C571.
- [12] Ilevbare, G.O and Scully, J.R. 2001. Mass-transport-limited oxygen reduction reaction on AA2024-T3 and selected intermetallic compounds in chromate-containing solutions. Corrosion, 57, 134–152.
- [13] Qian Z, Tiantian T, Peilin D, Zhiyi Z and Fang W. 2017. The Corrosion Inhibition Effect of Triazinedithiol Inhibitors for Aluminum Alloy in a 1M HCl Solution, Metals, 7, 44, 1-11.
- [14] Hachelef, H, Benmoussat, A, Khelifa, A, Athmani, D and Bouchareb, D. 2016. Study of corrosion inhibition by Electrochemical Impedance Spectroscopy method of 5083 aluminum alloy in 1 M HCl solution containing propolis extract. J. Mater. Environ. Sci. 7, 1751–1758.
- [15] Khaled, K.F. 2010. Electrochemical investigation and modeling of corrosion inhibition of aluminum in molar nitric acid using some sulphur-containing amines. Corros. Sci., 52, 2905–2916.
- [16] Zhang, Q.B and Hua, Y.X. 2010. Corrosion inhibition of aluminum in hydrochloric acid solution by alkylimidazolium ionic liquids. Mater. Chem. Phys., 119, 57–64.
- [17] El-Naggar, M. M. 2007. Corrosion inhibition of mild steel in acidic medium by some sulfa drugs compounds, Corros. Sci., 49, 2226–2236.
- [18] Afia, L, Benali, O, Salghi, R, Ebenso, E.E, Jodeh, S, Zougagh, M and Hammouti, B. 2014. Steel Corrosion Inhibition by Acid Garlic Essential Oil as a Green Corrosion Inhibitor and Sorption Behavior, Int. J. Electrochem. Sci., 9, 8392 8406.
- [19] Benabdellah, M., Hammouti, B., Bendahhou, M. and Aouniti, A. 2006, Inhibition of steel corrosion in 2M H3PO4 by artemisia oil, Applied Surface Science, 252, 6212-7.
- [20] Booth, G., Delatte, D.E. and Thames, S.F. 2007, Incorporation of drying oils into emulsion polymers for use in low-VOC architectural coatings, Industrial Crops and Products, 25, 257-65.
- [21] Bouyanzer, A. and Hammouti, B. 2004a, A study of anticorrosive effects of artemisia oil on steel, Pigment & Resin Technology, 33, 287-92.
- [22] Bouyanzer, A. and Hammouti, B. 2004b, Naturally occuring ginger as corrosion inhibitor for steel in molar hydrocloric acid at 353 K, Bulletin of Electrochemistry, 20, 63-5.
- [23] Bouyanzer, B., Hammouti, B. and Majadi, L. 2006, Pennyroyal oil from Mentha pulegium as corrosion inhibitor for steel in 1 M HCl, Materials Letters, 60, pp. 2840-3.