

### PERSPECTIVE

# Converging biofabrication and organoid technologies: the next frontier in hepatic and intestinal tissue engineering?

To cite this article: Kerstin Schneeberger et al 2017 Biofabrication 9 013001

View the article online for updates and enhancements.

### You may also like

al

- In vitro reconstitution of the hormoneresponsive testicular organoids from murine primary testicular cells Yan Yang, Rufei Huang, Zhen Cao et al.
- <u>Development of a high-throughput</u> <u>micropatterned agarose scaffold for</u> <u>consistent and reproducible hPSC-derived</u> <u>liver organoids</u> Shanqing Jiang, Fang Xu, Menglong Jin et
- <u>Gastrointestinal organs and organoids-on-</u> <u>a-chip: advances and translation into the</u> clinics

<u>clinics</u> Mariana R Carvalho, Le-Ping Yan, Bo Li et al.

### **Biofabrication**

PERSPECTIVE

## Converging biofabrication and organoid technologies: the next frontier in hepatic and intestinal tissue engineering?

PUBLISHED 6 March 2017

CrossMark

#### Kerstin Schneeberger<sup>1,6</sup>, Bart Spee<sup>1,6</sup>, Pedro Costa<sup>2,3</sup>, Norman Sachs<sup>4</sup>, Hans Clevers<sup>4</sup> and Jos Malda<sup>2,3,5</sup>

- <sup>1</sup> Department of Clinical Sciences of Companion Animals, Utrecht University, Utrecht, The Netherlands
- <sup>2</sup> Department of Orthopaedics, University Medical Center Utrecht, Utrecht, The Netherlands
- <sup>3</sup> Utrecht Biofabrication Facility, Utrecht University, Utrecht, The Netherlands
- <sup>4</sup> Hubrecht Institute for Developmental Biology and Stem Cell Research, Royal Dutch Academy of Sciences and University Medical Center Utrecht, Utrecht, The Netherlands
- <sup>5</sup> Department of Equine Sciences, Faculty of Veterinary Medicine, Utrecht University, Utrecht, The Netherlands
- <sup>6</sup> Authors contributed equally.

Keywords: bioprinting, regenerative medicine, vascularization, organoids, tissue engineering

#### Abstract

Adult tissue stem cells can form self-organizing 3D organoids *in vitro*. Organoids resemble small units of their organ of origin and have great potential for tissue engineering, as well as models of disease. However, current culture technology limits the size, architecture and complexity of organoids. Here, we review the establishment of intestinal and hepatic organoids and discuss how the convergence of organoids and biofabrication technologies can help overcome current limitations, and thereby further advance the translational application of organoids in tissue engineering and regenerative medicine.

### Introduction

The establishment of three-dimensional (3D) organoid cultures from multiple organs has been a major breakthrough and has gained increasing attention over the last ten years. A historical perspective of the evolvement of 3D tissue cultures, and the different definitions of the term organoids has recently been reviewed [1]. In general, organoids are self-organizing 3D structures that grow in vitro, embedded in an extracellular matrix (ECM) and resemble their organ of origin [2]. They can be established from different cell sources, such as primary tissue explants, cell lines, multipotent adult stem cells, pluripotent embryonic stem cells (ES cells) or induced pluripotent stem cells (iPS cells), and from a variety of tissues [1, 3]. In this perspective, we focus on intestinal and hepatic organoids from adult stem cells or iPS cells, and how the integration with advanced biofabrication technologies may enhance the utility of organoids in research and therapeutic applications.

The generation of 3D organoids stems from our increasing understanding of stem cell signaling pathways [4]. Key components of stable hepatic and intestinal organoid cultures include agonists of WNT and epidermal growth factor, antagonists of bone morphogenetic protein (BMP), and embedding the cells in an ECM. Under those culture conditions, adult stem cells [5, 6] can produce all progeny of their tissue lineage and self-organize into small 3D structures closely mimicking the homeostasis and function of their native organ [7]. Organoids can also be derived from pluripotent iPS or ES cells, which can be specified into definitive endoderm, and subsequently into a hindgut [8, 9] or hepatic fate [10, 11]. Hindgut spheroids form intestinal organoids when cultured in the same conditions as adult intestinal stem cells, containing all intestinal epithelial cell types with mesenchymal cells surrounding the organoids [8, 9]. When cultured in expansion medium with active WNT signaling, intestinal and hepatic organoids appear as hollow cyst structures and are highly proliferative. In differentiation conditions, where WNT signaling is blocked, organoids become smaller and cell-dense and upregulate the expression of differentiation markers [4-6, 12] (figure 1). Since the stem cells retain their self-renewing capacity in culture, organoids represent an unlimited source of primary epithelium, which has been shown to remain genetically stable [13], especially for organoids derived from adult stem cells [5, 6, 14]. Hence, organoids are already widely applied in in vitro studies [2, 7], for example as disease models, and hold



great potential for transplantation and tissue regeneration purposes [15–18].

Despite their great potential, current organoid culture conditions feature several limitations that prevent accurate recapitulation of tissue architecture and in vivo behavior. Matrigel, which is often used, is an undefined ECM of murine origin, which hampers translation to humans due to immunogenicity. Local signaling gradients, in vivo, tightly control cell fate and tissue architecture; in contrast, organoid cultures offer no spatiotemporal control over the provided growth factors. Moreover, organoids are restricted in size due to limitations of nutrient diffusion, and lack complex interactions with non-parenchymal cell types. Consequently, the architectural organization, maturation status and functionality of organoids does not yet reach in vivo levels despite the fact that they contain all differentiated epithelial cell types found in vivo [6, 19]. We anticipate that combining organoids and biofabrication technologies may overcome those limitations, and produce larger, functional tissues under highly controllable culture conditions.

Biofabrication aims to recapitulate tissues and organs by combining cells and biomaterials into very specific structures with dictated organization. Recently, biofabrication was defined as

...the automated generation of biologically functional products with structural organization from living cells, bioactive molecules, biomaterials, cell aggregates such as micro-tissues, or hybrid cell-material constructs, through *bioprinting or bioassembly and subsequent tissue maturation processes* [20].

Biofabrication effectively employs and combines an array of technologies, methods and material compositions. It includes direct cell-laden printing methods using inkjet printing [21] or robotic dispensing [22] as well as indirect or multi-stage methods, such as melt electrospinning writing [23], which allow us to simply shape, direct and promote the development of cell-material constructs.

### Mimicking the ECM

The ECM regulates cell behavior and is an essential component of the stem cell niche. In vivo, hepatocytes are in close proximity to the ECM in the space of Disse, and intestinal epithelial cells face an underlying basement membrane. In the liver, receptors of the  $\beta 1$ integrin family interact with collagen type I, fibronectin and laminin that are present in the ECM [24, 25]. In the intestine, the basement membrane is rich in collagen type IV and laminins, which provide adhesion sites for receptors of the integrin superfamily that are expressed on the basolateral membrane of intestinal epithelial cells [26–28]. The ECM not only anchors the epithelial cells, but also influences proliferation, differentiation and migration of the interacting cells [27, 29, 30]. Differentiation of liver progenitor cells towards the hepatocyte or cholangiocyte lineage [31] and proliferation and differentiation of intestinal stem

cells [32] are not only regulated through biochemical signals (the matrix composition), but also through the mechanical properties (stiffness) of the ECM. Mimicking the biochemistry and biomechanics of the native ECM of a certain tissue *in vitro* is thus crucial for controlling proliferation and differentiation of the cells that constitute an organoid.

Hepatic and intestinal organoids are currently mostly cultured in Matrigel [4–6, 12, 33], a gelatinous protein mixture with high biological activity that is secreted by mouse sarcoma cells [34]. The protein complexity of Matrigel is advantageous as it closely mimics the composition of the basement membrane, and enables proliferation, differentiation and selforganization of embedded cells into 3D structures [35]. However, the murine origin, complex extraction process and undefined composition of Matrigel all lead to a relatively high batch-to-batch variation in composition and stiffness, and hamper in vivo applications in humans due to immunogenicity. Cellmatrix type I-A has also been used to culture intestinal organoids in one study [36]. The collagen-based gel is more defined than Matrigel, however the porcine origin still hampers clinical translation. Thus, in order to advance the maturation and translational potential of organoids to the clinics, there is a need for a defined hydrogel that can substitute and overcome the disadvantages posed by animal-derived gels.

The use of synthetic or biological hydrogels may bypass the need for Matrigel. Synthetic polymers are chemically defined and allow for a tight control over the mechanical properties, however, they lack biofunctionality, and thus require the incorporation of biomolecules to recapitulate the biological functions of the ECM [37]. Biological polymers, such as gelatin, are biofunctional, but the mechanical properties are more difficult to control. In recent years, biomaterial approaches have focused on the physicochemical tailoring of biological hydrogels to control their mechanical properties. This is of particular importance when applied to the culture of organoids since these are sensitively regulated through mechanotransduction [38]. The mechanical properties of hydrogels can be finetuned by varying the mixing ratio of their components [39], or by the reinforcement of very soft gels with more mechanically and dimensionally stable structures [40].

Gelatin-methacryloyl (GelMA) hydrogels, for example, are fabricated by the addition of methylacryloyl side groups to gelatin. This process makes gelatin crosslinkable, and thus yields a hydrogel that is biofunctional and mechanically tunable [41, 42]. It is highly versatile and suitable for processing, since it can be easily crosslinked by either enzymes or light, which makes it suitable for direct 3D printing [41]. Likewise, we recently showed that enzymatically crosslinkable poly-ethylene glycol (PEG) hydrogels can be functionalized with a covalently linked Arg–Gly–Asp peptide (which represents binding to fibronectin) to support the expansion of intestinal stem cells [32]. Subsequently, by varying the mechanical properties and decreasing the stiffness of the functionalized PEG hydrogel in a modular manner, differentiation and polarization of intestinal epithelial organoids could be induced [32]. Thus, by mimicking the biological and mechanical ECM properties of a particular tissue with a tailormade and defined hydrogel, proliferation and maturation of organoids can be controlled and improved. These defined and modular hydrogels offer new possibilities to study the influence of biological and mechanic properties of ECM on cell behavior in the self-organizing organoid system. In addition, synthetic hydrogels can be altered for a particular application. For example, organoids can be cultured in a functionalized hydrogel with a relatively high stiffness that promotes proliferation, when large amounts of organoids are needed. In contrast, the use of modular hydrogels for the culture of organoids may increase their maturation status and functionality. Additionally, the defined nature of synthetic hydrogels may provide exciting opportunities for the translation of organoid technology to clinical settings.

### Complex scaffolds to mimic tissue architecture

The small intestine is highly structured. The epithelium is organized into proliferative crypt compartments which are embedded in the intestinal submucosa, and extruding villi harbor the differentiated cells of the small intestinal epithelium [43]. The proximal duodenum contains a high number of very long villi, whereas the abundance and lengths of the villi decreases towards the distal part of the small intestine [44]. This defined topography affects the mechanics and fluid dynamics of the small intestine *in vivo* [45]. The importance of topography on cell fate decisions can be demonstrated by intestinal Caco-2 cells, which differentiate along the crypt-villus axis *in vitro* when seeded on a collagen scaffold that reflects the shape and size of villi [46].

In current organoid culture conditions, both murine and human small intestinal organoids do not contain villus architecture. Murine small intestinal organoids self-organize into crypts and flat villus-like domains, however do not build real extruding villi [4]. Human small intestinal organoids are cultured as round cysts under expansion conditions, and undergo a change in morphology into a highly folded structure upon exposure to differentiation medium [5, 14], with an even more pronounced lack of clear villus architecture.

Biofabrication techniques, such as laser ablation or stereolithography, using bioinert photopolymer resins, allow easy and fast production of a scaffold with villus topography [47]. Such a scaffold can be either directly seeded with cells, or used as a mold for the subsequent production of a hydrogel-based (porous) scaffold [48]. Indeed, murine and human intestinal organoids were recently grown on such a scaffold *in vitro* and after omental implantation into immunedeficient mice *in vivo*, where they supported the growth of epithelial cells and blood vessels [49]. As such, the combination of hydrogel-based scaffolds and organoids may be the next step in the development of a tissue-engineered small intestine for the treatment of patients with short-bowel syndrome and other intestinal diseases.

### Flow perfusion culture for homogeneous distribution of nutrients and oxygen

In order to create larger tissues composed of multiple organoids, flow perfusion bioreactors may bypass the limitations of size, oxygen supply and nutrient/waste transport. These bioreactors enable perfusion of a biofabricated tissue or tissue construct; support shear stress by microfluidics, which can maintain or even increase function of parenchymal cells [50]; provide a uniform medium distribution, and maintain the desired concentration of gases and nutrients in the medium [51]. Flow perfusion bioreactors have shown great potential over previous bioreactor systems, such as spinner flasks and rotating wall vessels [52]. All flow perfusion bioreactors consist of a similar setup with a pump, tubing, media container and a perfusion chamber. The design of the perfusion chamber is customized to the tissue of interest and intended application.

These flow perfusion bioreactors provide a highly controlled system for bioengineered tissues. For instance low shear stress can polarize hepatocytes in a bioreactor, thereby increasing the function of drugmetabolizing cytochromes [53-56]. For intestinal tissue models using organoids, flow perfusion bioreactors have been developed which allow long-term perfusion and polarized transport from the apical side of the epithelial cells towards their basolateral side [57] and increase functions, such as multidrug resistance protein 1 (MDR1) transporter activity [58]. In addition, a more homogeneous maturation status of cells within organoids may be achieved if growth factors could reach the cells more easily by using porous tissue constructs. Porous tissue constructs in flow perfusion bioreactors would also increase the distribution of oxygen and nutrient/waste transport and provide a better and more constant exposure. Taken together, flow perfusion bioreactors will prove vital in maintaining tissue-specific functionality and providing proper distribution of gases and nutrients in the media.

### Spatio-temporal control over growth factors

Current organoid culture systems do not regulate the spatial and temporal signaling cascades (WNT, Notch, transforming growth factor beta, BMP and hedgehog) necessary for homeostasis and regeneration in the intestine [43, 59] and liver [60]. A range of growth factors are added to the culture medium to mimic the *in vivo* signaling pathways, however all cells are exposed to a uniform concentration of growth factors, whereas concentration gradients *in vivo* are crucial for localized cell fate decisions. As such, human intestinal and liver organoids mainly consist of stem and progenitor cells under expansion conditions, and require the withdrawal of several growth factors in order to induce differentiation [5, 6].

Biofabrication will allow us to expose organoid cells to their required growth factors in a modular, highly controllable and reproducible manner [61]. Spatio-temporal control over growth factors and small molecules can be achieved by using specific biomaterials, which are able to either define the length of the release period [62] or promote release of bioactive molecules in multiple discrete stages [63, 64]. Other more complex strategies can use materials that release drugs, on demand, as a response to specific external stimuli such as local pH [65], temperature or combinations thereof [66].

### Patterning of organoids and nonparenchymal cells

In both the intestine and liver, non-parenchymal cells heavily influence tissue homeostasis and regeneration. Intestinal [4, 5, 14] and hepatic [6, 12, 33] epithelial organoids from adult tissue stem cells are a simplified model of the complex *in vivo* environment and lack non-parenchymal cells that intersperse and interact with the epithelial cells *in vivo*. The simplistic nature of organoids is an advantage when using a reductionist approach to studying stem cells and their progenies, without the confounding influences of their (cellular) environment. However, the lack of a native microenvironment hampers studies involving immune responses and interaction of epithelial cells with their supporting cells, and might limit the maturation of epithelial cells due to missing instructive cues.

In the intestine, the epithelium is in close spatial proximity to several non-parenchymal cells, including the underlying mesenchyme and immune cells. Mesenchymal cells have been shown to drive villus formation [67], and secrete growth factors to the epithelium. For example, intestinal epithelial stem cells receive niche signals from neighboring Paneth cells [68], but upon ablation of Paneth cells in a mouse model, the stem cells remain functional [69] due to redundant WNT ligands secreted by surrounding mesenchymal cells [70]. *In vitro* culture of Paneth celldeficient *Atoh1<sup>-/-</sup>* KO organoids on an intestinal mesenchymal layer rescued their survival [70], and culture of small intestinal wildtype organoids on a layer of stromal cells [71, 72] or subepithelial myofibroblasts [73, 74] promoted organoid formation and survival without addition of exogenous WNT agonists. In addition, innate immune cells have been shown to support stem cell survival and organoid growth by the secretion of IL-22 [75].

The liver consists of the parenchymal hepatocytes and several non-parenchymal cell types such as liver mesenchymal stromal cells, sinusoidal endothelial cells, stellate cells and Kupffer cells. When cultured on a fibroblast feeder layer, adult hepatocytes show an increased *in vitro* proliferation capacity [76]. Kupffer cells, the tissue resident macrophages of the liver, play a pivotal role in tissue homeostasis, and seem to facilitate liver injury by the secretion of inflammatory cytokines and reactive oxygen species [77]. Furthermore, the sinusoidal endothelium promotes liver regeneration by the secretion of hepatocyte growth factor and angiocrine signals [78, 79].

We expect that biofabrication will help create the complex cellular microenvironments found in vivo by enabling the patterning of several cell types with high spatial accuracy. Specialized software allows precise and easy design of heterogeneous constructs, which can define various patterns, gradients and densities of cells [80] and material compositions [81]. In addition, the required biochemical and mechanical hydrogel properties may vary between cell types within one tissue, and greatly influence the behavior of developing tissues. To account for those different local requirements, multiple types of cell-laden gels can be combined through robotic dispensing technologies [82] or by melt electrospinning writing [83] for gels with more solid structures. A good example of the importance of cellular patterning can be found in liver applications, where bioprinting of hepatocyte progenitor cells (HPCs) and non-parenchymal cells in a 3D model with hexagonal architecture was found to improve morphological organization and liver-specific functions of the HPCs [84]. This kind of patterned combination of cell-laden materials can result in the generation of constructs composed of multiple inner biomechanical microenvironments, which may be specifically suitable for organoids and different nonparenchymal cells.

### Vascularization of organoids and tissues

One of the major challenges for the biofabrication of larger multi-organoid structures (or even organs) is vascularization [85]. Diffusion for delivery of nutrients, oxygen, growth factors, and removal of metabolic waste is often already insufficient when tissue thickness exceeds 100–200  $\mu$ m [86], and organoids easily

reach sizes above 300  $\mu$ m. Diffusion in a bioengineered tissue can be achieved with well-distributed and interconnected vascular networks. Several approaches that can create neovascularization appropriate for diffusion include the incorporation of endothelial cells with scaffolds; in layered cell sheets by 3D printing; in co-culture with spheroids or aggregates of parenchymal cells; or with the addition of angiogenesis-inducing growth factors [87, 88]. One promising approach using 3D bioprinting creates channels with a sacrificial material, e.g. agarose or Pluronic F127, enclosed inside a cell-laden hydrogel matrix. After removal of the sacrificial material, these microchannels can be filled with endothelial cells [89-91]. Patent lumens are thus created with endothelial linings, allowing better representation of native tissue such as liver [92].

Endothelial cells are essential for vascularization and angiogenesis, and they communicate with smooth muscle cells to promote and stabilize vascular development and function [93]. Human umbilical vein endothelial cells are often used in these types of co-cultures as a source for endothelial cells. However, the type of endothelial cells required depends on the application and tissue of interest [85]. For example, capillaries in the intestine have a continuous endothelial lining whereas capillaries in the liver are leaky and have large intercellular gaps [94]. The addition of endothelial cells in bioengineered liver tissue using organoids allows vascularization and transplantation [16, 95], but ex vivo bioengineered liver tissue based on organoids might also benefit from the addition of endothelial cells by increasing hepatic function [96, 97]. Addition of cells that promote or stabilize vascularization can also be achieved by adding (vascular) smooth muscle cells [93]. As organoids easily reach sizes above 300  $\mu$ m, vascularization is a necessity for the use of organoids for tissue engineering approaches. Although vascularization is still considered one of the greatest challenges in tissue engineering, methods such as the use of sacrificial material combined with endothelial cells in organoid-laden hydrogels will lead to bioengineered tissues that better represent in vivo physiology.

#### Conclusions

Organoids represent an exciting new organ model, since they can be established from a variety of species, resemble their organ of origin, and can be infinitely expanded in culture while retaining their genetic integrity. Current limitations of organoids are caused by the lack of fully controllable culture conditions, and therefore, the inability to reproduce the microenvironments necessary for the proper behavior and organization of cells; to induce vascularization; and to control cell–cell and cell– matrix interactions. Biofabrication offers a wide



variety of techniques that can introduce these additional dimensions of control to organoid cultures (figure 2).

We envision an additive effect of biofabrication on the versatility of organoid technology. For example, the use of a defined synthetic hydrogel with control over biological cues will increase spatial control over proliferation and maturation of organoids in a tissuespecific manner, while also potentially enabling translation of organoids towards the clinic. Biofabrication of scaffolds on which organoids can be seeded will allow the growth of a tissue with *in vivo*-like architecture, which may increase maturation and functionality of organoid cells and could potentially be used for transplantations in the future. Advances in biomimetic hydrogels and 3D bioprinting will allow us to combine organoids and supporting cells with highly defined spatial control. The culture of organoids or organoid-derived porous tissue constructs in a flowperfusion bioreactor will increase the control over growth factor concentrations, oxygen and the pH in the medium, thereby facilitating a homogenous organoid culture with increased functionality. Finally, biofabrication will enable the incorporation of structural microchannels into organoid cultures, which can be seeded with endothelial cells in order to receive vascularized multiple-organoid constructs that will allow the formation of larger tissues without a necrotic core. In summary, we predict that the combination of biofabrication technologies and organoids will increase the organization, complexity and maturation of organoids, and thereby enhance their application potential, especially for tissue engineering and regenerative medicine.

6

In order for the convergence of biofabrication and organoid technologies to become a reality, it is necessary to define, fine-tune and standardize this modified approach. It will be challenging to faithfully support organoid biology with technically feasible methods, as the mechanical properties of tissue-engineered constructs are often a compromise between printability and biological performance [40]. In addition, building a multi-layer, multi cell type, complex 3D structure that mimics *in vivo* architecture and interactions (both internal and external) leaves each individual system open to a range of variables, and optimal conditions for each case will need to be established.

Nevertheless, both organoids and biofabrication have already proven themselves as great tools for regenerative medicine, and the combination will offer unmatched possibilities for creating complex and functional tissues that more closely resemble the *in vivo* situation.

### Acknowledgements

All authors declare no conflict of interest. JM was supported by the Dutch Arthritis Foundation (LLP-12), the European Community's Seventh Framework Programme (FP7/2007-2013) under grant agreement n°309962 (HydroZONES) and the European Research Council under grant agreement n°647426 (3D-JOINT). BS was supported by the Dutch Research Counsel NWO ZON/MW (92003538 and 16004121).

#### References

- Simian M and Bissell M J 2017 Organoids: a historical perspective of thinking in three dimensions *J. Cell Biol.* 216 31–40
- [2] Fatehullah A, Tan S H and Barker N 2016 Organoids as an in vitro model of human development and disease Nat. Cell Biol. 18 246–54
- [3] Clevers H 2016 Modeling development and disease with organoids *Cell* 165 1586–97
- [4] Sato T et al 2009 Single Lgr5 stem cells build crypt-villus structures in vitro without a mesenchymal niche Nature 459 262–5
- [5] Sato T et al 2011 Long-term expansion of epithelial organoids from human colon, adenoma, adenocarcinoma, and Barrett's epithelium Gastroenterology 141 1762–72
- [6] Huch M et al 2015 Long-term culture of genome-stable bipotent stem cells from adult human liver Cell 160 299–312
- [7] Lancaster M A and Knoblich J A 2014 Organogenesis in a dish: modeling development and disease using organoid technologies *Science* 345 1247125
- [8] Spence J R et al 2011 Directed differentiation of human pluripotent stem cells into intestinal tissue in vitro Nature 470 105–9
- [9] McCracken K W, Howell J C, Wells J M and Spence J R 2011 Generating human intestinal tissue from pluripotent stem cells in vitro Nat. Protocols 6 1920–8
- [10] Touboul T et al 2010 Generation of functional hepatocytes from human embryonic stem cells under chemically defined conditions that recapitulate liver development *Hepatology* 51 1754–65

- [11] Rashid S T et al 2010 Modeling inherited metabolic disorders of the liver using human induced pluripotent stem cells J. Clin. Invest. 120 3127–36
- [12] Huch M et al 2013 In vitro expansion of single Lgr5+ liver stem cells induced by Wnt-driven regeneration Nature 494 247–50
- [13] Cheng L et al 2012 Low incidence of DNA sequence variation in human induced pluripotent stem cells generated by nonintegrating plasmid expression Cell Stem Cell 10 337–44
- [14] Jung P *et al* 2011 Isolation and *in vitro* expansion of human colonic stem cells *Nat. Med.* **17** 1225–7
- [15] Li V S and Clevers H 2012 In vitro expansion and transplantation of intestinal crypt stem cells Gastroenterology 143 30–4
- [16] Takebe T et al 2013 Vascularized and functional human liver from an iPSC-derived organ bud transplant Nature 499 481–4
- [17] Watson C L et al 2014 An in vivo model of human small intestine using pluripotent stem cells Nat. Med. 20 1310–4
- [18] Yui S et al 2012 Functional engraftment of colon epithelium expanded in vitro from a single adult Lgr5 stem cell Nat. Med. 18 618–23
- [19] Middendorp S et al 2014 Adult stem cells in the small intestine are intrinsically programmed with their location-specific function Stem Cells 32 1083–91
- [20] Groll J et al 2016 Biofabrication: reappraising the definition of an evolving field Biofabrication 8 013001
- [21] Calvert P 2007 Materials science: printing cells *Science* **318** 208–9
- [22] Schacht K, Jungst T, Schweinlin M, Ewald A, Groll J and Scheibel T 2015 Biofabrication of cell-loaded 3D spider silk constructs Angew. Chem. Int. Ed. in Engl. 54 2816–20
- [23] Farrugia B L, Brown T D, Upton Z, Hutmacher D W, Dalton P D and Dargaville T R 2013 Dermal fibroblast infiltration of poly(epsilon-caprolactone) scaffolds fabricated by melt electrospinning in a direct writing mode *Biofabrication* 5 025001
- [24] Tanimizu N, Kikkawa Y, Mitaka T and Miyajima A 2012 alpha1-and alpha5-containing laminins regulate the development of bile ducts via beta1 integrin signals J. Biol. Chem. 287 28586–97
- [25] Martinez-Hernandez A and Amenta P S 1993 The hepatic extracellular matrix: I. Components and distribution in normal liver Virchows Archiv A 423 1–11
- [26] Beaulieu J F 1999 Integrins and human intestinal cell functions Frontiers Biosci. 4 D310–21
- [27] Teller I C and Beaulieu J F 2001 Interactions between laminin and epithelial cells in intestinal health and disease *Expert Rev. Mol. Med.* 3 1–18
- [28] Moore R, Madara J L and MacLeod R J 1994 Enterocytes adhere preferentially to collagen IV in a differentially regulated divalent cation-dependent manner Am. J. Physiol. 266 G1099–107
- [29] Zhu C, Coombe D R, Zheng M H, Yeoh G C and Li L 2013 Liver progenitor cell interactions with the extracellular matrix J. Tissue Eng. Regen. Med. 7 757–66
- [30] Klaas M et al 2016 The alterations in the extracellular matrix composition guide the repair of damaged liver tissue Sci. Rep. 6 27398
- [31] Kourouklis A P, Kaylan K B and Underhill G H 2016 Substrate stiffness and matrix composition coordinately control the differentiation of liver progenitor cells *Biomaterials* 99 82–94
- [32] Gjorevski N et al 2016 Designer matrices for intestinal stem cell and organoid culture Nature 539 560–4
- [33] Nantasanti S et al 2015 Disease modeling and gene therapy of copper storage disease in canine hepatic organoids Stem Cell Rep. 5 895–907
- [34] Kleinman H K and Martin G R 2005 Matrigel: basement membrane matrix with biological activity Semin. Cancer Biol. 15 378–86
- [35] Hughes C S, Postovit L M and Lajoie G A 2010 Matrigel: a complex protein mixture required for optimal growth of cell culture *Proteomics* **10** 1886–90

- [36] Jabaji Z et al 2014 Type I collagen as an extracellular matrix for the *in vitro* growth of human small intestinal epithelium Plos One 9 e107814
- [37] Lutolf M P and Hubbell J A 2005 Synthetic biomaterials as instructive extracellular microenvironments for morphogenesis in tissue engineering *Nat. Biotechnol.* 23 47–55
- [38] Buske P et al 2012 On the biomechanics of stem cell niche formation in the gut–modelling growing organoids FEBS J. 279 3475–87
- [39] Melchels F P W, Dhert W J A, Hutmacher D W and Malda J 2014 Development and characterisation of a new bioink for additive tissue manufacturing J. Mater. Chem. B 2 2282–9
- [40] Malda J et al 2013 25th anniversary article: engineering hydrogels for biofabrication Adv. Mater. 25 5011–28
- [41] Klotz B J, Gawlitta D, Rosenberg A J, Malda J and Melchels F P 2016 Gelatin-methacryloyl hydrogels: towards biofabricationbased tissue repair *Trends Biotechnol.* 34 394–407
- [42] Loessner D et al 2016 Functionalization, preparation and use of cell-laden gelatin methacryloyl-based hydrogels as modular tissue culture platforms Nat. Protocols 11 727–46
- [43] van der Flier L G and Clevers H 2009 Stem cells, self-renewal, and differentiation in the intestinal epithelium Annu. Rev. Physiol. 71 241–60
- [44] Altmann G G and Leblond C P 1970 Factors influencing villus size in the small intestine of adult rats as revealed by transposition of intestinal segments *Am. J. Anat.* **127** 15–36
- [45] Chen X, Zhao J and Gregersen H 2008 The villi contribute to the mechanics in the guinea pig small intestine J. Biomech. 41 806–12
- [46] Yu J, Peng S, Luo D and March J C 2012 In vitro 3D human small intestinal villous model for drug permeability determination Biotechnol. Bioeng. 109 2173–8
- [47] Sung J H, Yu J, Luo D, Shuler M L and March J C 2011 -Microscale 3D hydrogel scaffold for biomimetic gastrointestinal (GI) tract model Lab Chip 11 389–92
- [48] Costello C M et al 2014 Synthetic small intestinal scaffolds for improved studies of intestinal differentiation *Biotechnol. Bioeng.* 111 1222–32
- [49] Shaffiey S A *et al* 2016 Intestinal stem cell growth and differentiation on a tubular scaffold with evaluation in small and large animals *Regen. Med.* 11 45–61
- [50] Goral V N and Yuen P K 2012 Microfluidic platforms for hepatocyte cell culture: new technologies and applications Ann. Biomed. Eng. 40 1244–54
- [51] Plunkett N and O'Brien F J 2011 Bioreactors in tissue engineering *Technol. Health Care* **19** 55–69
- [52] Gaspar D A, Gomide V and Monteiro F J 2012 The role of perfusion bioreactors in bone tissue engineering *Biomatter* 2 167–75
- [53] Tilles A W, Baskaran H, Roy P, Yarmush M L and Toner M 2001 Effects of oxygenation and flow on the viability and function of rat hepatocytes cocultured in a microchannel flatplate bioreactor *Biotechnol. Bioeng.* 73 379–89
- [54] Powers M J, Janigian D M, Wack K E, Baker C S, Beer Stolz D and Griffith L G 2002 Functional behavior of primary rat liver cells in a three-dimensional perfused microarray bioreactor *Tissue Eng.* 8 499–513
- [55] Gelinsky M, Bernhardt A and Milan F 2015 Bioreactors in tissue engineering: advances in stem cell culture and threedimensional tissue constructs *Eng. Life Sci.* 15 670–7
- [56] Yuki T, Masayuki Y, Teruo O, Takehiko K and Kiichi S 2006 Evaluation of effects of shear stress on hepatocytes by a microchip-based system *Meas. Sci. Technol.* 17 3167
- [57] Kimura H, Yamamoto T, Sakai H, Sakai Y and Fujii T 2008 An integrated microfluidic system for long-term perfusion culture and on-line monitoring of intestinal tissue models *Lab Chip* 8 741–6
- [58] Schweinlin M et al 2016 Development of an advanced primary human in vitro model of the small intestine Tissue Eng. C 22 873–83
- [59] Leushacke M and Barker N 2014 Ex vivo culture of the intestinal epithelium: strategies and applications Gut 63 1345–54

- [60] Kitade M, Kaji K and Yoshiji H 2016 Relationship between hepatic progenitor cell-mediated liver regeneration and nonparenchymal cells *Hepatol. Res.* 46 1187–93
- [61] Liu Y-Y, Yu H-C, Liu Y, Liang G, Zhang T and Hu Q-X 2016 Dual drug spatiotemporal release from functional gradient scaffolds prepared using 3D bioprinting and electrospinning *Polym. Eng. Sci.* 56 170–7
- [62] Costa P F, Puga A M, Diaz-Gomez L, Concheiro A, Busch D H and Alvarez-Lorenzo C 2015 Additive manufacturing of scaffolds with dexamethasone controlled release for enhanced bone regeneration *Int. J. Pharmaceutics* 496 541–50
- [63] Facca S et al 2010 Active multilayered capsules for in vivo bone formation Proc. Natl Acad. Sci. USA 107 3406–11
- [64] Keeney M et al 2013 Mutant MCP-1 protein delivery from layer-by-layer coatings on orthopedic implants to modulate inflammatory response Biomaterials 34 10287–95
- [65] Vazhayal L, Talasila S, Abdul Azeez P M and Solaiappan A 2014 Mesochanneled hierarchically porous aluminosiloxane aerogel microspheres as a stable support for pH-responsive controlled drug release ACS Appl. Mater. Interfaces 6 15564–74
- [66] Peng J et al 2013 Controlled release of cisplatin from pHthermal dual responsive nanogels Biomaterials 34 8726–40
- [67] Walton K D et al 2016 Villification in the mouse: BMP signals control intestinal villus patterning Development 143 427–36
- [68] Sato T et al 2011 Paneth cells constitute the niche for Lgr5 stem cells in intestinal crypts Nature 469 415–8
- [69] Durand A et al 2012 Functional intestinal stem cells after paneth cell ablation induced by the loss of transcription factor MATH1 (Atoh1) Proc. Natl Acad. Sci. USA 109 8965–70
- [70] Farin H F, Van Es J H and Clevers H 2012 Redundant sources of Wnt regulate intestinal stem cells and promote formation of Paneth cells *Gastroenterology* 143 1518–29
- [71] Pastula A et al 2016 Three-dimensional gastrointestinal organoid culture in combination with nerves or fibroblasts: a method to characterize the gastrointestinal stem cell niche Stem Cells Int. 2016 3710836
- [72] Ootani A *et al* 2009 Sustained *in vitro* intestinal epithelial culture within a Wnt-dependent stem cell niche *Nat. Med.* 15 701–6
- [73] Lahar N *et al* 2011 Intestinal subepithelial myofibroblasts support *in vitro* and *in vivo* growth of human small intestinal epithelium *PloS One* 6 e26898
- [74] Lei N Y et al 2014 Intestinal subepithelial myofibroblasts support the growth of intestinal epithelial stem cells PloS One 9 e84651
- [75] Lindemans C A *et al* 2015 Interleukin-22 promotes intestinalstem-cell-mediated epithelial regeneration *Nature* 528 560–4
- [76] Cho C H, Berthiaume F, Tilles A W and Yarmush M L 2008 A new technique for primary hepatocyte expansion *in vitro Biotechnol. Bioeng.* 101 345–56
- [77] Roberts R A, Ganey P E, Ju C, Kamendulis L M, Rusyn I and Klaunig J E 2007 Role of the Kupffer cell in mediating hepatic toxicity and carcinogenesis *Toxicol. Sci.* 96 2–15
- [78] Ding B S et al 2010 Inductive angiocrine signals from sinusoidal endothelium are required for liver regeneration *Nature* 468 310–5
- [79] Wang L, Wang X, Xie G, Wang L, Hill C K and DeLeve L D 2012 Liver sinusoidal endothelial cell progenitor cells promote liver regeneration in rats J. Clin. Invest. 122 1567–73
- [80] Faulkner-Jones A, Greenhough S, King J A, Gardner J, Courtney A and Shu W 2013 Development of a valve-based cell printer for the formation of human embryonic stem cell spheroid aggregates *Biofabrication* 5 015013
- [81] Anderson D G, Levenberg S and Langer R 2004 Nanoliter-scale synthesis of arrayed biomaterials and application to human embryonic stem cells *Nat. Biotechnol.* 22 863–6
- [82] Melchels F P et al 2016 Hydrogel-based reinforcement of 3D bioprinted constructs *Biofabrication* 8 035004
- [83] Visser J et al 2015 Reinforcement of hydrogels using threedimensionally printed microfibres Nat. Commun. 6 6933

- [84] Ma X et al 2016 Deterministically patterned biomimetic human iPSC-derived hepatic model via rapid 3D bioprinting Proc. Natl Acad. Sci. USA 113 2206–11
- [85] Bae H et al 2012 Building vascular networks Sci. Trans. Med. 4 160ps23
- [86] Du Y, Ghodousi M, Qi H, Haas N, Xiao W and Khademhosseini A 2011 Sequential assembly of cell-laden hydrogel constructs to engineer vascular-like microchannels *Biotechnol. Bioeng.* 108 1693–703
- [87] Fennema E, Rivron N, Rouwkema J, van Blitterswijk C and de Boer J 2013 Spheroid culture as a tool for creating 3D complex tissues *Trends Biotechnol.* 31 108–15
- [88] Sarker M, Chen X B and Schreyer D J 2015 Experimental approaches to vascularisation within tissue engineering constructs J. Biomater. Sci. Polym. Ed. 26 683–734
- [89] Bertassoni L E et al 2014 Hydrogel bioprinted microchannel networks for vascularization of tissue engineering constructs Lab Chip 14 2202–11
- [90] Lee J H et al 2013 Generation of osteogenic construct using periosteal-derived osteoblasts and polydioxanone/pluronic F127 scaffold with periosteal-derived CD146 positive endothelial-like cells J. Biomed. Mater. Res. A 101 942–53

- [91] Therriault D, White S R and Lewis J A 2003 Chaotic mixing in three-dimensional microvascular networks fabricated by direct-write assembly *Nat. Mater.* 2 265–71
- [92] Miller J S et al 2012 Rapid casting of patterned vascular networks for perfusable engineered three-dimensional tissues Nat. Mater. 11 768–74
- [93] Hegen A et al 2011 Efficient in vivo vascularization of tissueengineering scaffolds J. Tissue Eng. Regen. Med. 5 e52–62
- [94] Sarin H 2010 Physiologic upper limits of pore size of different blood capillary types and another perspective on the dual pore theory of microvascular permeability *J. Angiogenesis Res.* **2** 14
- [95] Mavila N et al 2017 Functional human and murine tissueengineered liver is generated from adult stem/progenitor cells Stem Cells Transl. Med. 6 238–48
- [96] Ohno M, Motojima K, Okano T and Taniguchi A 2009 Maturation of the extracellular matrix and cell adhesion molecules in layered co-cultures of HepG2 and endothelial cells J. Biochem. 145 591–7
- [97] Nahmias Y, Casali M, Barbe L, Berthiaume F and Yarmush M L 2006 Liver endothelial cells promote LDL-R expression and the uptake of HCV-like particles in primary rat and human hepatocytes *Hepatology* 43 257–65