

## LETTER • OPEN ACCESS

## Enhancement of carrier mobility in metal-oxide semiconductor field-effect transistors using negative thermal expansion gate electrodes

To cite this article: Hisashi Kino et al 2022 Appl. Phys. Express 15 111004

View the article online for updates and enhancements.

## You may also like

- A novel mechanical metamaterial with tailorable Poisson's ratio and thermal expansion based on a chiral torsion unit Jiahao Li, Qingsheng Yang, Ning Huang et al.
- <u>Properties of negative thermal expansion -</u> <u>eucryptite ceramics prepared by spark</u> <u>plasma sintering</u> Li-Min Zhao, , Yong-Guang Cheng et al.
- <u>Negative thermal expansion and</u> associated anomalous physical properties: review of the lattice dynamics theoretical foundation

Martin T Dove and Hong Fang

Applied Physics Express 15, 111004 (2022)

https://doi.org/10.35848/1882-0786/ac9d24

## Enhancement of carrier mobility in metal-oxide semiconductor field-effect transistors using negative thermal expansion gate electrodes

Hisashi Kino<sup>1\*</sup><sup>(0)</sup>, Takafumi Fukushima<sup>1,2</sup>, and Tetsu Tanaka<sup>1,2</sup>

<sup>1</sup>Graduate School of Biomedical Engineering, Tohoku University, Sendai, Miyagi 980-8579, Japan <sup>2</sup>Graduate School of Engineering, Tohoku University, Sendai, Miyagi 980-8579, Japan

\*E-mail: kino@lbc.mech.tohoku.ac.jp

Received June 15, 2022; revised October 20, 2022; accepted October 23, 2022; published online November 4, 2022

Strained-Si technology is crucial to improving the performance of metal-oxide-semiconductor field-effect transistors (MOSFETs). To introduce large strain into the channel, we proposed a structure for the negative thermal expansion gate electrode. In this study, we used manganese nitride as the gate material, which is a negative thermal expansion material. The fabricated MOSFETs with the manganese nitride gate showed a 10% increase in electron mobility compared to the MOSFET with the Al gate. The results show that the negative thermal expansion gate technology is promising as a technology booster for MOSFET scaling. © 2022 The Author(s). Published on behalf of The Japan Society of Applied Physics by IOP Publishing Ltd

o enhance the carrier mobility in metal-oxide-semiconductor field-effect transistors (MOSFETs), various strain introduction technologies have been studied.<sup>1–3)</sup> Well-known examples are the application of SiN stress liner and SiGe-source/drain structure as strain technologies.<sup>4–7)</sup> As a result of these advancements, MOSFETs' scaling has been improved. Recently, other strain technologies have been strongly required for further scaling down of MOSFETs. This study proposes the use of negative thermal expansion materials as gate electrodes to introduce larger strain into the channel of MOSFETs. The conclusion section summarizes the important results and impact of the research.

Generally, the volume of the materials expands when the temperature of the materials increases. However, a limited number of compounds indicate negative thermal expansion.<sup>8–16)</sup> Here, negative thermal expansion indicates that the volume of the materials shrinks when the temperature of the materials increases. Advanced ICs have various stress/ strain issues that could be resolved by the negative thermal expansion materials.<sup>17–21)</sup> The unique characteristics of negative thermal expansion materials have been considered for application in semiconductor packaging, microelectrome-chanical systems, and superconductivity.<sup>22–24)</sup>

The coefficient of thermal expansion (CTE) mismatch between different materials is a principal factor that induces film stress. In advanced MOSFETs, the strain is introduced into the channel material because of the film stress induced by the CTE mismatch. Therefore, a large CTE mismatch can introduce a large strain into channel materials.<sup>25,26)</sup> The CTE mismatch between the gate electrode and substrate also introduces strain into the channel material. TiN, which is usually used as the gate electrode, has a higher positive CTE than that of Si. Thus, a thicker TiN layer increases the strain of a Si channel along the compressive direction.<sup>27)</sup> Therefore, negative thermal expansion materials have significant prospects by the introduction of tensile strain into MOSFET channels.

Figure 1 shows the conceptual drawing of the MOSFET with a negative thermal expansion gate electrode for carrier mobility enhancement. Generally, the deposition process of gate electrode material, such as sputtering and chemical vapor deposition, is performed at a high temperature. In addition, the post-annealing process is often required after deposition to improve crystallinity. These facts indicate that temperature lowering always occurs for gate formation. If the gate electrode material has a negative CTE, the temperature lowering expands the volume of the gate electrode. Thus, negative thermal expansion can introduce tensile strain into the channel material of the MOSFETs. The tensile strain induced by the negative thermal expansion gate electrode can enhance electron mobility. The use of negative thermal expansion materials as gate electrodes to introduce strain is a unique and unprecedented approach.

In this study, we fabricated and evaluated nMOSFETs with negative thermal expansion gate electrodes. Subsequently, we first demonstrated the ability of the negative thermal expansion gate electrode to enhance electron mobility in nMOSFETs.

To introduce a large strain in the channel of the MOSFETs, we focused on an antiperovskite manganese nitride compound that exhibits negative thermal expansion. Manganese nitride compounds with an antiperovskite crystal structure are unique materials with several characteristics, such as a near-zero temperature-coefficient of resistivity and magnetocaloric effects.<sup>28–31)</sup> The absolute value of the CTE of manganese nitride compounds is extremely high compared with that of other materials with negative CTEs.<sup>12–16)</sup> Meanwhile, the Young's modulus of manganese nitride compounds exceeds 200 GPa,<sup>32)</sup> which is sufficient to introduce a large strain. In addition, the resistivity of the manganese nitride compounds is approximately 300  $\mu\Omega$ cm, which is almost the same as the resistivity of the doped poly-Si.<sup>31,33)</sup> Moreover, manganese nitride compounds behave like metals rather than semiconductors.<sup>31)</sup> Thus, the depletion layer is not formed in the gate electrode when the manganese nitride is used as a gate electrode material. Therefore, an antiperovskite manganese nitride compound is a promising material for gate electrodes to enhance electron mobility in MOSFETs.

First, we measured the X-ray diffraction (XRD) characteristics of the manganese nitride thin film deposited by radiofrequency magnetron sputtering to validate the negative thermal expansion. Figure 2(a) shows the XRD spectrum of the manganese nitride thin film deposited on the Si wafer. The thickness of the manganese nitride thin film was 200 nm.



LETTER







Fig. 2. (Color online) (a) XRD spectra of the manganese nitride thin film measured at 30  $^{\circ}$ C and 70  $^{\circ}$ C, and (b) Change ratio of lattice spacing obtained from XRD spectra.

The power, the pressure, and the gas of the sputtering were 50 W, 0.5 Pa, and Ar, respectively. Using the dopant for the antiperovskite manganese, the CTE value and the temperature region can be controlled, which shows a negative CTE. Here, we used Sn and Zn as the dopant materials. The compositional ratio between Sn and Zn was 1:2. The XRD spectrum of the manganese nitride thin film was measured at temperatures of 30 °C, 50 °C, and 70 °C. The measurements were performed under high temperatures and then under low temperatures. We confirmed the peak position and intensity ratio of the fabricated sample to be similar to that of the antiperovskite manganese nitride compounds.<sup>12,34,35</sup> Furthermore, we obtained the change ratio of lattice spacing from the XRD peak positions, as shown in Fig. 2(b). We validated that fabricated manganese nitride thin film shrunk with an increase in temperature. Therefore, it is demonstrated that fabricated manganese nitride thin films have a negative CTE around room temperature. Additionally, this manganese nitride thin film can be used as a gate electrode that induces tensile stress around room temperature. We fabricated the MOSFETs using this manganese nitride thin film as the gate electrode material.

Figure 3(a) illustrates the process flow and the photograph of the fabricated nMOSFET with the manganese nitride gate. After the isolation process, we performed channel implantation. Subsequently, source/drain implantation was performed with the dummy gates. The dopant for the source/drain was arsenic of  $1 \times 10^{20}$  cm<sup>-3</sup>. Then, the rapid thermal annealing process was performed at the temperature of 1050 °C for 10 s for source/drain activation. We used Al with 0.5% Si and 0.5% Cu for the source/ drain electrode and metal line. After that, we formed the manganese nitride gates. The thickness of the manganese nitride gate and the gate oxide were 200 nm and 10 nm, respectively. The gate oxide was SiO<sub>2</sub>, formed before the metal line process by thermal oxidation. Radio-frequency magnetron sputtering was also used as the deposition method of the manganese nitride



**Fig. 3.** (Color online) (a) Process flow and photograph of the fabricated nMOSFET with the manganese nitride gate electrode, (b) structure used in FEM simulation, (c) simulation results of the strain distributions in the MOSFETs with Al gate electrode, and (d) manganese nitride gate electrode.

gates, which was the same as that of the samples used for XRD analysis. Finally, the samples were annealed at 100 °C under a pressure of 10 Pa with an Ar atmosphere to obtain the tensile strain, as illustrated in Fig. 1. Here, we used a silicon-on-insulator substrate whose layer thickness was 100 nm. MOSFETs with an AI gate were also fabricated using the same process for comparison.

Subsequently, we estimated the strain induced by the manganese nitride gate by finite element method (FEM) simulation. Figure 3(b) shows a cross-section of the structure used in the FEM simulation, which was the same as the structure of fabricated MOSFETs. The current flow was along the xdirection in the figure. The CTE of Si, SiO<sub>2</sub>, and Al were 2.46 ppm, 0.45 ppm, and 23.0 ppm, respectively. The CTE of the manganese nitride was the value obtained from the XRD measurements. The Young's modulus of SiO2, Al, and the manganese nitride were 73 GPa, 71 Gpa, and 200 GPa, respectively. In contrast, it is well-known that a single crystalline Si has an anisotropic Young's modulus. In this study, we used an Si wafer having (100) surface and (110) orientation flat. Thus, we used the following stiffness matrix  $(E_{Si})$  as the Young's modulus of Si to consider the effect of the current direction on the crystal orientation of the Si wafer.<sup>19)</sup>

$$E_{\rm Si} = \begin{pmatrix} 195.1 & 35.5 & 64.4 & 0 & 0 & 0 \\ 35.5 & 195.1 & 64.4 & 0 & 0 & 0 \\ 64.4 & 64.4 & 166.2 & 0 & 0 & 0 \\ 0 & 0 & 0 & 79.8 & 0 & 0 \\ 0 & 0 & 0 & 0 & 79.8 & 0 \\ 0 & 0 & 0 & 0 & 0 & 50.9 \end{pmatrix} (\rm GPa).$$

Here, the current direction was perpendicular to the (110) plane. The structure was subjected to the same thermal process succeeding gate formation as illustrated in Fig. 3(a).

Figures 3(c) and 3(d) show the FEM simulation results of the strain distribution in the MOSFETs with Al and the manganese nitride gate at 25 °C. The results illustrate the normal strain in the current direction ( $\varepsilon_{xx}$ ). The Young's modulus of Al was lower than that of Si, and the CTE of SiO<sub>2</sub>, which is the gate oxide, was much lower than that of Al. Thus, little tensile strain was impressed on the Si channel of the MOSFET with Al gate. In contrast, we observed a high tensile strain of approximately 0.06% in the Si channel of the MOSFET with the manganese nitride gate having a negative CTE. These FEM simulation results indicated that tensile strain was induced in the Si channel by the negative CTE gate.

We also measured the current–voltage and mobility characteristics of the fabricated MOSFETs with a manganese nitride gate to confirm whether the manganese nitride could work as the gate electrode. Figures 4(a) and 4(b) show the drain current–gate voltage ( $I_D-V_G$ ) and current–drain voltage ( $I_D-V_D$ ) characteristics of the fabricated nMOSFETs. The gate length and width of the measured nMOSFET were 10  $\mu$ m. The  $I_D-V_G$  characteristics were measured under drain voltages of 0.05 and 2.0 V. The  $I_D-V_D$  characteristics were measured under gate voltages of 0.2–2.0 V in increments of 0.2 V. The fabricated nMOSFETs with manganese nitride gates exhibited typical characteristics. These results indicate that the manganese nitride can work as the gate electrode of the MOSFET. In the negative gate voltage region, the drain current under the drain voltage of 2.0 V increased compared with the drain current under the drain voltage of 0.05 V. We consider that the drain current under the negative gate voltage is mainly composed of gate-induced drain leakage in the case of the fabricated devices. Therefore, the drain current under the negative gate voltage increased as the drain voltage increased.

Figure 4(c) illustrates the capacitance–voltage (C-V) characteristics of the fabricated MOSFETs with manganese nitride and Al gates. The measurement frequency was 1 MHz, and we observed a flat-band voltage  $(V_{\rm fb})$  shift. In general,  $V_{\rm fb}$  is expressed as follows:

$$V_{fb} = \phi_{SM} - \frac{Q_0}{C_{0X}},\tag{1}$$

where  $\phi_{\rm SM}$ ,  $Q_{\rm O}$ , and  $C_{\rm OX}$  show the work function difference between the gate electrode and the substrate, the fixed-charge density, and the gate oxide capacitance per area, respectively. Therefore, the  $V_{\rm fb}$  shift, which was approximately 0.5 V, was caused by the work function difference between the manganese nitride compound and Al. Thus, as the work function of Al is 4.25 eV, which is close to the conduction band minimum of Si, the manganese nitride compound is estimated to be the mid-gap work function material. This work function difference affects the threshold voltage ( $V_{\rm TH}$ ) of the MOSFETs. Thus, we should consider the effect of the work function difference in investigating the effect of the manganese nitride gate on the MOSFET characteristics.

To evaluate the effect of the manganese nitride gate without considering some factors, such as  $V_{\text{TH}}$ , we investigated the electron mobility obtained via the split C-V



Fig. 4. (Color online) (a)  $I_D - V_G$ , and (b)  $I_D - V_D$  characteristics of the fabricated nMOSFET with a manganese nitride gate. (c) Comparison between the manganese nitride gate and Al gate through the C-V characteristics and (d) the electron mobility characteristics.

111004-3

© 2022 The Author(s). Published on behalf of The Japan Society of Applied Physics by IOP Publishing Ltd method.<sup>36)</sup> Figure 4(d) shows the electron mobility characteristics of the fabricated MOSFETs having a manganese nitride gate and an Al gate. MOSFETs with manganese nitride and Al gates were both fabricated through the same process, as shown in Fig. 3. We consider that the region higher than the difference between  $V_{\rm G}$  and  $V_{\rm TH}$  ( $V_{\rm G}-V_{\rm TH}$ ) of approximately 0.8 V shows the region dominated by phonon scattering. In the phonon scattering region, the electron mobility of the MOSFET with the manganese nitride gate was 10% higher than that of the MOSFET with the Al gate. The FEM simulation results for the strain, which are illustrated in Fig. 3(d), show that an estimated 0.06% tensile strain was induced into the Si channel because of the manganese nitride gate. The relationship between strain and mobility enhancement rate, which was obtained in this study, is consistent with that in other reports.<sup>37)</sup> Therefore, this increase in electron mobility can be attributed to the introduction of tensile strain by the negative thermal expansion gate. Consequently, the negative CTE material can introduce tensile strain into the channel of MOSFETs.

Finally, we investigated the applicability of the manganese nitride gates to the advanced MOSFETs. FinFET structures are used in advanced integrated circuits. Gate-all-around (GAA) structures with nanosheet channels are currently being considered for the further scaling of MOSFETs. Thus, we should also investigate the effect of the negative CTE materials on these structures in a bid to apply the negative CTE materials to the gate electrode of near-future MOSFETs. We investigated the effect of the manganese nitride gate on the SOI structure, FinFET structure, and GAA structure via FEM simulation. Figure 5 illustrates the structures used in the FEM simulation as well as the simulation results of the strain distribution in the MOSFETs. The current flow was along the x-direction in the figure. The results illustrate the normal strain in the current direction ( $\varepsilon_{xx}$ ). The physical gate length and Si thickness of all structures were 15 nm and 5 nm, respectively, which were values used in the 7 nm technology node.<sup>38,39)</sup> Figure 5(a) depicts the simulated structure and simulation result for the SOI structure. The results indicate the strain in the current direction. Here, we confirmed approximately 0.05% tensile stress in the Si channel, which is lower than that of the result presented in Fig. 3(d). The scaling of the MOSFETs was performed geometrically, whereas that of the physical thickness of the gate oxide was saturant recently. Thus, the gate oxide thickness indicated in Fig. 5 was larger than that of other materials compared with the gate oxide thickness indicated in Fig. 3. Therefore, the tensile strain induced by the manganese nitride was reduced.

Figures 5(b) and 5(c) show the simulated structures and simulation results of the FinFET and GAA structures. We can observe a tensile strain larger than 0.1% in the Si channel. In these structures, the channel region was isolated from the substrate, and the overlap between the channel region and gate electrode increased. Thus, the negative manganese nitride gate can effectively introduce tensile strain into the Si channel.

To enhance electron mobility, we proposed to apply the negative CTE material as the gate electrode. The deposited manganese nitride thin film exhibited a negative thermal expansion. Hence, the fabricated MOSFET with the



**Fig. 5.** (Color online) Structures used in FEM simulation and the crosssection of the simulation results of the strain distribution in (a) SOI FET, (b) FinFET, and (c) nanosheet FET with the manganese nitride gate electrode.

manganese nitride gate, having a negative CTE, indicated an enhancement in electron mobility. The use of negative thermal expansion materials as gate electrodes to introduce strain is a unique and unprecedented approach. Recently, the structure of MOSFETs has been changed to the FinFET structure and GAA structure from the planar structure, which was used in this study. The FEM simulation results indicated that the effect of the negative CTE gate structure increased in these structures. These results indicate that the negative CTE gate structure is promising for the scaling down of MOSFETs with FinFET or GAA structures.

Acknowledgments This work was supported by KAKENHI JP20H02193, JP19K21953 and through the activities of VDEC, the University of Tokyo, in collaboration with Cadence Design Systems. The work was performed in the Micro/Nano-Machining Research and Education Center at Tohoku University.

ORCID iDs Hisashi Kino (1) https://orcid.org/0000-0001-9348-120X

- T.-Y. Liow, K.-M. Tan, H.-C. Chin, R. T. P. Lee, C.-H. Tung, G. S. Samudra, N. Balasubramanian, and Y.-C. Yeo, 2006 Int. Electron Devices Meeting (IEDM) (IEEE, 2006), p. 473.
- K. W. Ang, C. H. Tung, N. Balasubramanian, G. S. Samudra, and Y. C. Yeo, IEEE Electron Device Lett. 28, 609 (2007).

© 2022 The Author(s). Published on behalf of The Japan Society of Applied Physics by IOP Publishing Ltd

111004-4

- C. Chen, K. Sumita, K. Toprasertpong, M. Takenaka, and S. Takagi, IEEE Trans. Electron Devices 69, 25 (2022).
- S. Ito et al., 2000 Int. Electron Devices Meeting (IEDM) (IEEE, 2000), p. 247, 10.1109/IEDM.2000.904303.
- 5) F. Ootsuka, S. Wakahara, K. Ichinose, A. Honzawa, S. Wada, H. Sato, T. Ando, H. Ohta, K. Watanabe, and T. Onai, 2000 Int. Electron Devices Meeting (IEDM) (IEEE, 2000), 2000, p. 575.
- 6) A. Shimizu, K. Hachimine, N. Ohki, H. Ohta, M. Koguchi, Y. Nonaka, H. Sato, and F. Ootsuka, 2001 Int. Electron Devices Meeting (IEDM) (IEEE, 2001), p. 19.4.1.
- 7) T. Ghani et al., 2003 Int. Electron Devices Meeting 2003 (IEEE, 2003), p. 11.6.1.
- 8) T. A. Mary, J. S. O. Evans, T. Vogt, and A. W. Sleight, Science 272, 90 (1996).
- 9) Y. W. Long, N. Hayashi, T. Saito, M. Azuma, S. Muranaka, and Y. Shimakawa, Nature 458, 60 (2009).
- 10) K. Takenaka and S. Technol, Sci. Technol. Adv. Mater. 13, 013001 (2012).
- 11) M. Azuma et al., Nat. Commun. 2, 347 (2011).
- 12) K. Takenaka, M. Ichigo, T. Hamada, A. Ozawa, T. Shibayama, T. Inagaki, and K. Asano, Sci. Technol. Adv. Mater. 15, 015009 (2014).
- 13) M. Kobayashi and M. Mochizuki, Phys. Rev. Mater. 3, 024407 (2019).
- 14) K. Takenaka and H. Takagi, Appl. Phys. Lett. 87, 261902 (2005).
- 15) F. Yu, L. Ren, M. Meng, Y. Wang, M. Yang, S. Wu, and S. Li, J. Appl. Phys. 115, 133911 (2014).
- 16) K. Takenaka, K. Asano, M. Misawa, and H. Takagi, Appl. Phys. Lett. 92, 011927 (2008).
- 17) H. Kino, J. C. Bea, M. Murugesan, K. W. Lee, T. Fukushima, M. Koyanagi, and T. Tanaka, Jpn. J. Appl. Phys. 52, 04CB11 (2013).
- 18) Y. Zhu, J. Zhang, H. Y. Li, C. S. Tan, and G. Xia, IEEE Trans. Device Mater. Reliab. 15, 142 (2015).
- 19) H. Kino, H. Hashiguchi, S. Tanikawa, Y. Sugawara, S. Ikegaya, T. Fukushima, M. Koyanagi, and T. Tanaka, Jpn. J. Appl. Phys. 55, 04EC03 (2016).
- 20) Y.-T. Oh, I.-P. Roh, H. Kino, T. Tanaka, and Y.-H. Song, IEEE Trans. Electron Devices 65, 4313 (2018).
- 21) Y.-T. Oh, J.-M. Sim, N. Van Toan, H. Kino, T. Ono, T. Tanaka, and Y.-H. Song, IEEE Trans. Electron Devices 66, 1741 (2019).
- 22) H. Kino, T. Fukushima, and T. Tanaka, 2017 IEEE 67th Electronic Components and Technology Conf. (ECTC) (IEEE, 2017), p. 1523.

- 23) M. S. Sutton and J. Talghader, 12th Int. Conf. on Solid-State Sensors, Actuators and Microsystems. Digest of Technical Papers, 2003 (IEEE) Vol 2, p. 1148, (Cat. No. 03TH8664).
- 24) T. Takao, K. Yamamoto, Y. Yamada, Y. Nakajima, K. Nakamura, M. Arikawa, S. Fukui, A. Nishimura, and A. Yamanaka, IEEE Trans. Appl. Supercond. 18, 1378 (2008).
- 25) K.-M. Tan, T.-Y. Liow, R. T. P. Lee, C.-H. Tung, G. S. Samudra, W.-J. Yoo, and Y.-C. Yeo, IEEE Electron Device Lett. 27, 769 (2006).
- 26) M.-H. Liao, C. H. Chen, L. C. Chang, C. Yang, and S. C. Kao, IEEE Trans. Electron Devices 62, 1360 (2015).
- 27) C. Y. Kang, R. Choi, M. M. Hussain, J. Wang, Y. J. Suh, H. C. Floresca, M. J. Kim, J. Kim, B. H. Lee, and R. Jammy, Appl. Phys. Lett. 91, 033511 (2007).
- 28) H. Kino, T. Fukushima, and T. Tanaka, Appl. Phys. Express 14, 091003 (2021).
- 29) T. Oe, N. Kaneko, and K. Takenaka, IEEJ Trans. Fundam. Mater. 136, 448 (2016).
- 30) H. Kino, T. Fukushima, and T. Tanaka, 2021 IEEE Int. Interconnect
- Technology Conf. (IITC) (IEEE, 2021), 10.1109/IITC51362.2021.9537336.
  31) T. Oe, C. Urano, N. Kaneko, M. Hadano, and K. Takenaka, Appl. Phys. Lett. 103, 173518 (2013).
- 32) Y. Nakamura, K. Takenaka, A. Kishimoto, and H. Takagi, J. Am. Ceram. Soc. 92, 2999 (2009).
- 33) L. Ding, C. Wang, L. Chu, J. Yan, Y. Na, Q. Huang, and X. Chen, Appl. Phys. Lett. 99, 251905 (2011).
- 34) Z. Sun and X. Song, J. Mater. Sci. Technol. 30, 903 (2014).
- 35) X. Guo, P. Tong, J. Lin, C. Yang, K. Zhang, S. Lin, W. Song, and Y. Sun, Front. Chem. 6, 1 (2018).
- 36) C. G. Sodini, T. W. Ekstedt, and J. L. Moll, Solid. State. Electron. 25, 833 (1982).
- 37) S. E. Thompson, S. Suthram, Y. Sun, G. Sun, S. Parthasarathy, M. Chu, and T. Nishida, 2006 Int. Electron Devices Meeting (IEDM) (IEEE, 2006), p. 681.
- 38) S.-Y. Wu et al., 2016 Int. Electron Devices Meeting (IEDM) (IEEE, 2016), p. 2.6.1.
- 39) P. Oldiges, R. A. Vega, H. K. Utomo, N. A. Lanzillo, T. Wassick, J. Li, J. Wang, and G. G. Shahidi, IEEE Access 8, 154329 (2020).