Nonlinear Optical Properties of CdTe Microcrystallites in CaF_2 Thin Film

To cite this article: Meng-Yan Shen *et al* 1995 *Jpn. J. Appl. Phys.* **34** 134

View the [article online](#) for updates and enhancements.

You may also like

- [Effect of purity and proportion of microcrystalline graphite ore on the electrical, mechanical and tribological performance of copper-carbon composites](#)
Shengzhi Duan, Xiaowen Wu, Xin Min et al.
- [Structure and optical properties of CdTe microcrystallites in \$\text{CaF}_2\$](#)
Meng-Yan Shen, M Saito, T Goto et al.
- [Characterization of Microcrystalline from Pineapple Leaf \(*Ananas comosus* L. Merr\)](#)
S Yuliasmi, Nerdy and A Husnita

Nonlinear Optical Properties of CdTe Microcrystallites in CaF₂ Thin Film

Meng-Yan SHEN, Satoshi YANO and Takenari GOTO

Department of Physics, Faculty of Science, Tohoku University, Sendai 980, Japan

Futami SATO and Michiyoshi TANAKA

Research Institute for Scientific Measurements, Tohoku University, Sendai 980, Japan

The nonlinear optical properties of CdTe microcrystallites embedded in CaF₂ by pulsed laser beam and electron beam coevaporation method are investigated with pump-probe technique. Only bleaching effect around wavelength region corresponding to the larger size microcrystallites can be obtained. The bleaching spectra are simulated with a state filling model. The upper energy states of the quantum confinement microcrystallites are perhaps also important to the nonlinear optical properties of microcrystallites.

KEYWORDS: Microcrystallite, CdTe, Nonlinear optical property.

1. Introduction

Because of the application background, the investigation about the nonlinear optical properties of microcrystallites are increasingly important. To realize strong and fast response nonlinear optical properties of semiconductor microcrystallites, many methods have been used to prepare the samples. In our previous work ¹⁾, we embedded CdTe microcrystallites into a CaF₂ thin film by pulsed laser beam and electron beam coevaporation in a high vacuum chamber. Nanometer scale CdTe particles embedded in the CaF₂ thin film were observed in transmission electron micrographs. The blue shifts of the absorption bands and in particular the corresponding photoluminescence bands are easily obtained in the CdTe-microcrystallite-doped CaF₂ thin film. The broadened optical phonon Raman structure and low wave number acoustic phonon structure were also obtained. These results are considered to be a size effect of the CdTe microcrystallites. The nonlinear optical property of the mesoscopic semiconductor system is a basic property for the possible application. In the present work, using pump-probe technique, we investigate the nonlinear optical processes of the CdTe microcrystallites prepared by the pulsed laser beam and electron beam coevaporation method.

Fig. 1. Absorption spectrum and photoluminescence excited by 4579 Å of the CdTe microcrystallites, E_g is the bulk CdTe band gap.

Fig. 2 Electron transmission micrograph of a sample prepared by the same growth condition as that for the sample in Fig. 1.

2. Experimental

Our sample, CdTe microcrystallites in CaF₂, are prepared by the pulsed laser beam and electron beam coevaporation method, the details are given in our previous work ¹⁾. The Optical absorption and photoluminescence spectra of the sample used in this work are shown in Fig. 1. The transmission electron micrograph of a sample prepared by the same growth condition as that for the sample in Fig. 1 are shown in Fig. 2. In the absorption spectrum, there are two broad shoulders, of which one is at about 6500 Å and the other is at about 7400 Å. They may correspond to two kinds of CdTe microcrystallites, i.e., that of small size and of large size. In the transmission electron micrograph of Fig. 2, we see that there are roughly two kinds of size of CdTe microcrystallites in the sample, one is about 50 Å and the other is about 200 Å in diameter, which may result from the process of laser evaporation.

Using a laser beam with the wavelength of 6100 Å, the pulse width of 700 fs, the repetition rate of 1 KHz, and average power of 300 mW/cm², the changes of the absorption spectra at different delays after pump laser pulse are shown in Fig. 3. Only bleaching effect around 7400 Å corresponding to the larger size microcrystallites can be obtained. In the optical density change spectra, there are some fine structures.

Fig. 3 The optical density change spectra at different delays after the pump laser pulse.

3. Results and Discussion

The previous theoretical and experimental researches²⁾ show that effective mass approximation with infinitely deep well model is a simple but effective method when the size of the microcrystallites is larger than 50 Å in diameter. Within effective mass approximation on assumption of infinitely deep spherical potential well and negligible Coulomb interaction between the carriers, energies of different optical allowable transitions can be expressed by

$$E_{nl} = E_g + \frac{2\hbar^2 K_{nl}^2}{mD^2} \quad (1)$$

Where $l = s, p, d, \dots, n=1, 2, 3, \dots$, K_{nl} is the n -th root of the l -th spherical Bessel function, E_g the band gap of bulk crystal, m the reduced mass of electron and hole, and D the diameter of the microcrystallites. With equation (1) and the two broad shoulder wavelength, the estimated CdTe microcrystallite sizes are 60 and 240 Å respectively, which are similar to the observed size scale by transmission electron micrograph.

Perhaps there are two simple models to understand the fine structures in the optical density change spectra, one is that the fine structures may result from size difference of CdTe microcrystallites, the other one is that the fine structures may result from different energy levels of an average size distribution of microcrystallites. In Fig. 3, the life time of the shorter wavelength fine structures are much shorter (within 5 ps) than the longest wavelength fine structure (above tens ps), which are similar to the experimental results of CdSe in reference 3). If the fine structures result from size difference of CdTe microcrystallites, the lifetimes should be similar. And the theoretical research of Kayanuma⁴⁾ shows that the oscillator strength of some upper electron energy state can be much larger than the ground state. Thus the latter model may be more reasonable than the former one. With equation (1) and $D = 240$ Å, the calculated energy levels are demonstrated on the top of Fig. 3. Following the example

Fig. 4 The simulated optical density change spectra with state filling model.

of Dneprovskii, *et al.*³⁾, we simulate the optical density change spectra.

Assume the decrease of the optical density is proportional to the occupation of the state by electrons and holes (state filling model), and assume the size distributes Gaussian with an average size of 240 Å in diameter and a half width of 50 Å, which may near to the actual case for the larger size CdTe microcrystallites. We can simulate the optical density change spectra.

The energy of the electron-hole system of (i,j) state in a microcrystallite can be expressed by

$$E_{ij} = E_e(i) + E_h(j) + E_g \quad (2)$$

$E_e(i)$ and $E_h(j)$ are the i -th electron and j -th hole state kinetic energies respectively. Assuming quasi-equilibrium Fermi distribution, we can get N_{ij} the number of occupation of the (i,j) state of the electron-hole system,

$$N_{ij} = 1 / [\exp[(E_{ij} - \mu) / kT_e] + 1], \quad (3)$$

here T_e is the effective temperature of the quasi-equilibrium electron-hole system, μ the fermi energy. The total number of electron-hole in the microcrystallite N_{eh} ,

$$N_{eh} = \sum_{ij} N_{ij} \quad (4)$$

Only considering the optical allowable transition, we can obtain the absorption change:

$$\Delta\alpha \sim - \sum_i N_{ii} \quad (5)$$

The Simulated spectra are shown in Fig. 5, which are very similar to the experimental results. There are only two

fitting parameters: the effective temperature of electron-hole system T_e and the excited electron-hole pair number per microcrystallite N_{eh} . The shapes of the spectra are very sensitive to T_e , and the intensity of the spectra are very sensitive to N_{eh} .

Using this simple state filling model, we may understand the experimental results. The excited upper state electron can very quickly, within 5 ps, relax to the 1s state, and the electron-hole pairs may recombine through nonradiative process, because the radiative time is in a few hundred ps scale⁵⁾. The induced changes of absorption corresponding to upper energy state $\Delta\alpha/\alpha$ is obvious. Here it can reach 20%. The oscillator strength of some upper electron energy states can be much larger than 1s state⁴⁾. To quicken the nonlinear optical response, the upper energy states of microcrystallite with an appropriate size are perhaps more favorable than 1s state.

In Fig. 3, the optical density change in the spectrum at 35 ps delay after the pump laser pulse are all positive. The positive optical density change may mainly result from the temperature effect. In the above analysis we know that a lot of excited electrons and holes may recombine through nonradiative process. It means that the temperature effect is important.

The reason that we could not observe the bleaching effect around wavelength region corresponding to the smaller size microcrystallites is perhaps that the normalized oscillator strength of microcrystallites decreases as the size of microcrystallites decreases. Since it may make the bleaching effect of smaller size microcrystallites weaker compared to the possible positive optical density change due to temperature effect. To prove this point and understand the details of the process further, using a "better" size

distribution microcrystallites sample, we should do much more research about the contribution of the upper energy states to the nonlinear optical processes of microcrystallites.

4. Summary

The nonlinear optical process of CdTe microcrystallites embedded in CaF_2 are investigated with pump-probe techniques. Only bleaching effect around wavelength region corresponding to the larger size microcrystallites can be obtained. The optical density change spectra are simulated by state filling model. The upper energy states are perhaps very important to the nonlinear optical properties of microcrystallites.

Acknowledgments

This work was supported in part by the Grant-in-Aid for Scientific Research from the Ministry of Education, Science and Culture of Japan. We would like to thank Mr. Makoto Saito in Tohoku University for technical help.

References

- 1) M.-Y. Shen, M. Saito, T. Goto, F. Sato and M. Tanaka, *J. Phys. Condens. Matter* (1994) to be published.
- 2) For example: M.V. Rama Krishna and R.A. Friesner, *Phys. Rev. Lett.* **67** (1991) 629.
- 3) V.S. Dneprovskii, V.I. Klimov, D.K. Okorokov, Yu.V. Vandyshev, *Solid State Comm.* **81** (1992) 227.
- 4) Y. Kayanuma, *Phys. Rev. B* **38** (1988) 9797.
- 5) For example: J. R. Kuklinski and S. Mukamel, *Chem. Phys. Lett.* **189** (1992) 119.