PAPER

Crystal growth and spectral properties of Tb:Lu $_2O_{3^-}^{*}$

To cite this article: Jiaojiao Shi et al 2018 Chinese Phys. B 27 097801

View the article online for updates and enhancements.



You may also like

- Electronic structure and photoluminescence property of a novel white emission phosphor Na₃MgZr(PO₄)₆:Dy³⁺ for warm white light emitting diodes Ge Zhu, , Zhuo-Wei Li et al.
- <u>Measurement of CO, HCN, and NO</u> productions in atmospheric reaction induced by femtosecond laser filament Xiao-Dong Huang, , Meng Zhang et al.
- <u>Phase-Gradient Metasurfaces Based on</u> <u>Local Fabry–Pérot Resonances</u> Yanyan Cao, , Bocheng Yu et al.

Crystal growth and spectral properties of Tb:Lu₂O₃*

Jiaojiao Shi(施佼佼)^{1,2}, Bin Liu(刘斌)^{1,2}, Qingguo Wang(王庆国)^{1,2}, Huili Tang(唐慧丽)^{1,2,4}, Feng Wu(吴锋)^{1,2}, Dongzhen Li(李东振)³, Hengyu Zhao(赵衡煜)^{1,2}, Zhanshan Wang(王占山)^{1,2}, Wen Deng(邓文)⁵, Zian Xu(徐子安)⁶, Jiayue Xu(徐家跃)⁶, Xiaodong Xu(徐晓东)^{3,†}, and Jun Xu(徐军)^{1,2,7,‡}

¹ School of Physics Science and Engineering, Institute for Advanced Study, Tongji University, Shanghai 200092, China ² MOE Key Laboratory of Advanced Micro-Structure Materials, Shanghai 201899, China

³ Jiangsu Key Laboratory of Advanced Laser Materials and Devices, School of Physics and Electronic Engineering,

Jiangsu Normal University, Xuzhou 221116, China

⁴ State Key Laboratory of Crystal Materials, Shandong University, Jinan 250100, China

⁵ School of Physical Science and Technology, Guangxi University, Nanning 530004, China

⁶Institute of Crystal Growth, School of Materials Science and Engineering, Shanghai Institute of Technology, Shanghai 201418, China

⁷ Shanghai Engineering Research Center for Sapphire Crystals, Shanghai 201899, China

(Received 15 May 2018; revised manuscript received 25 June 2018; published online 28 August 2018)

The crystal growth, x-ray diffraction pattern, absorption spectrum, emission spectrum, and fluorescence lifetime of a Tb:Lu₂O₃ single crystal were studied. Excited at 483 nm, the peak absorption cross-section was calculated to be 3.5×10^{-22} cm², and the full width at half maximum was found to be 2.85 nm. The Judd–Ofelt (J–O) intensity parameters Ω_2 , Ω_4 , and Ω_6 were computed to be 3.79×10^{-20} cm², 1.30×10^{-20} cm², and 1.08×10^{-20} cm², with a spectroscopic quality factor Ω_4/Ω_6 being 1.20. The emission cross-sections of green emission around 543 nm and yellow emission around 584 nm were calculated to be 9.43×10^{-22} cm² and 1.32×10^{-22} cm², respectively. The fluorescence lifetime τ_{exp} of ⁵D₄ was fitted to be 1.13 ms. The data suggest that the Tb:Lu₂O₃ crystal could be a potential candidate for green and yellow laser operation.

Keywords: fluorescence spectra, laser materials, excited states

PACS: 78.55.-m, 42.70.Hj, 78.47.da

DOI: 10.1088/1674-1056/27/9/097801

1. Introduction

Visible lasers are very attractive for their widespread applications, such as optical storage devices, display technology, medicine, materials processing, and more.^[1,2] Recently, visible lasers have aroused much attention due to the invention of the InGaN laser diode,^[3] because the emission wavelength of InGaN laser diode matches well with the absorption wavelength of most rare-earth ions, which is favorable for laser operation.

 Pr^{3+} is a famous rare earth ion in the visible laser operation. Efficient laser operations in deep red, red, orange, green, and blue regions have been demonstrated for Pr^{3+} -doped laser materials.^[4] Unfortunately, for Pr^{3+} , there is no yellow emission transition. The electronic configuration of trivalent terbium ions is [Xe]4f⁸, with a large energy gap (~ 15000 cm⁻¹) between the metastable ⁵D₄ excited state and the lower ⁷F_J (J = 6, 5, ..., 0) multiplets,^[5], which determines the presence of multiple visible emissions in red, yellow, green, and blue spectral ranges, high luminescence quantum efficiency, and a long lifetime of the emission state (ranging from a few hundred microseconds to a few milliseconds).^[6] Particularly, the yellow emission corresponding to the ${}^{5}D_{4} \rightarrow {}^{7}F_{4}$ transition makes Tb³⁺ ions a good candidate for yellow laser operation, which is not included by Pr³⁺ ions. Various materials doped with Tb³⁺ ions have been researched for fluorescence imaging and green phosphors.^[7–9] In 1973, the stimulated emission at 544.5 nm was first demonstrated in Tb:LiYF₄ crystals.^[10] Recently, pumped by the InGaN laser diode, highefficiency room temperature continuous wave lasers emitting green (${}^{5}D_{4} \rightarrow {}^{7}F_{5}$) and yellow (${}^{5}D_{4} \rightarrow {}^{7}F_{4}$) light from Tb³⁺doped fluoride crystals have also been achieved, with the maximum slope efficiencies being 58% around 545 nm in the green region and 20% around 585 nm in the yellow region.^[6,11]

The laser performance of rare-earth ions doped fluoride crystals strongly depends on the temperature. Thus it is necessary to find a new single crystal host, which not only owns the low phonon energy similar with fluoride crystals, but also has better thermal and mechanical properties than fluoride crystals. The sesquioxide Lu_2O_3 belonging to the bixbyite structure with the cubic space group $Ia3^{[12]}$ meets these requirements well. They possess higher thermal con-

[†]Corresponding author. E-mail: xdxu79@jsnu.edu.cn

[‡]Corresponding author. E-mail: xujun@mail.shcnc.ac.cn

© 2018 Chinese Physical Society and IOP Publishing Ltd

^{*}Project supported by the National Natural Science Foundation of China (Grant No. 61621001), the National Key Research and Development Program of China (Grant Nos. 2016YFB1102202 and 2016YFB0701002), and the Fundamental Research Funds for the Central Universities, China. We acknowledge the help of MOE Key Laboratory of Advanced Micro-Structured Materials and School of Physical Science and Technology, Guangxi University.

ductivity (~ 12.5 W/m·K) than that of fluoride materials (e.g., CaF₂ ~ 7.0 W/m·K).^[13,14] Compared with pure lutecia, the thermal conductivity of 3 at.% Yb³⁺-doped lutecia only decreases slightly to 11.0 W/m·K.^[15] In addition, the phonon energy of Lu₂O₃ (~ 430 cm⁻¹) is lower than that of other oxides,^[15] which means that the rare earth ions doped into Lu₂O₃ own lower non-radiative transition rates between the metastable electron levels, resulting in higher radiation probability and quantum efficiency. Up to now, the optical characteristics of Tm³⁺, Er³⁺, and Yb³⁺ doped Lu₂O₃ crystals^[16,17] have been reported. However, very few researches were focused on the Lu₂O₃ crystals doped with Tb³⁺ ions.

In this work, we study the x-ray diffraction (XRD) pattern, absorption spectrum, Judd–Ofelt (J–O) theory, emission spectrum, and fluorescence lifetime of a Tb:Lu₂O₃ crystal grown by floating zone (Fz) method in detail.

2. Experiments

2.1. Crystal growth

The Lu₂O₃ doped with trivalent terbium ions was grown by the Fz method. The Lu_2O_3 (4N purity) and Tb_4O_7 (4N purity) powders were used as raw materials and weighed precisely according to the equation $(Tb_xLu_{1-x})_2O_3$ (x = 0.01). After mixed evenly in an agate mortar, the raw powders were pressed into two rods and then sintered in the air at 1780 °C for 24 h. The rotation rate and growth rate were selected to be 8-10 rpm and 1-2 mm/h, respectively. High-purity argon gas was aerated into the floating zone furnace as a protective atmosphere. The grown Tb:Lu₂O₃ was slowly cooled to room temperature. There was an internal stress in the crystal due to the large temperature gradient in the growth process of the Fz method. Therefore, the grown Tb:Lu₂O₃ crystal was annealed in air at 1700 °C for 24 h to eliminate the internal stress. Then the obtained Tb:Lu₂O₃ crystal was cut into 2.5 mm×4 mm×1 mm and polished for spectral measurements.

2.2. Spectral measurements

The following measurements were performed at room temperature. The sample of Tb:Lu₂O₃ was ground into powders for XRD measurement using an Ultima IV diffractometer from Japan. As shown in Fig. 1, the diffraction peaks of the Tb:Lu₂O₃ crystal are in very good accordance with the JCPDS card of pure Lu₂O₃ crystal. The lattice parameter of the Tb:Lu₂O₃ crystal was calculated to be 1.0424 nm, which is close to that of pure Lu₂O₃ (1.0391 nm), indicating that the doping of the Tb³⁺ ions into Lu₂O₃ did not affect the phase and crystal structure obviously. The concentration of terbium in Tb:Lu₂O₃ reached 1 at.% (i.e., 2.85×10^{20} cm⁻³), which was measured by an ICP-AES (Ultima2, Jobin–Yvon). The absorption spectrum of $Tb:Lu_2O_3$ from 300 nm to 2400 nm with the resolution of 1 nm was measured by a spectrometer (Lambda900). The emission spectrum together with the decay curve of $Tb:Lu_2O_3$ was obtained by a fluorospectrophotometer (FSP920).



Fig. 1. Powder XRD pattern of Tb:Lu₂O₃ crystal.

3. Results and discussion

3.1. Absorption spectrum

The absorption spectra of the Tb:Lu₂O₃ crystal in the ranges of 320–495 nm and 1600–2400 nm are presented in Fig. 2. The absorption peaks centered around 328 nm, 331 nm, 339 nm, 342 nm, 344 nm, 349 nm, 353 nm, 355 nm, and 483 nm, corresponding to the transitions from ${}^{7}F_{6}$ to ${}^{5}H_{6}$,



Fig. 2. Room temperature absorption spectrum of Tb:Lu₂O₃ crystal: (a) 320–495 nm, (b) 1600–2400 nm.

⁵H₇+⁵D₀, ⁵L₉, ⁵G₄, ⁵G₅+⁵D₂, ⁵L₁₀, ⁵G₆, ⁵D₃, and ⁵D₄, respectively, are assigned and marked in Fig. 2(a). Figure 2(b) shows four absorption bands at 1752 nm, 1843 nm, 1906 nm, and 2075 nm, corresponding to the transitions from ⁷F₆ to ⁷F₀, ⁷F₁, ⁷F₂, and ⁷F₃, respectively. Some absorption bands overlap with each other due to the interaction of the crystal field. The absorption band around 483 nm corresponding to the ⁷F₆ \rightarrow ⁵D₄ transition fits well with the emission wavelength of the InGaN laser diode.^[18] At the peak wavelength of 483 nm, its absorption cross-section σ_{abs} and FWHM are 3.5×10^{-22} cm² and 2.85 nm, respectively. For the Tb:Lu₂O₃ crystal, its σ_{abs} is larger than that of Tb:LiLuF₄ crystal (2.0×10^{-22} cm² at 488.8 nm for π -polarization)^[11] and the FWHM is larger than that of Tb:KYbW (only 1.0 nm for *E* ||N_m).^[19]

3.2. Judd-Ofelt analysis

The Judd–Ofelt (J–O) theory is a useful tool to calculate the 4f^N radiative transition intensities of lanthanide ions in various host materials. The detailed calculation process is the same with the literature.^[19–21] The refractive index formula of Lu₂O₃ and the transition matrix elements of Tb³⁺ ions required for the calculation are taken from Refs. [5], [19], and [22]. In our J–O theory analysis, six bands corresponding to the ⁷F₆ \rightarrow ⁵L₁₀, ⁵G₆+⁵D₃, ⁵D₄, ⁷F₀+⁷F₁, ⁷F₂, and ⁷F₃ transitions are chosen to confirm the J–O intensity parameters. The parameters of the average wavelength $\overline{\lambda}$, the refractive index n, the calculated line strengths S_{cal} , and the experimental line strengths S_{exp} are shown in Table 1. The small value of rms ΔS (0.011 × 10⁻²⁰ cm²) indicates that the fitting results between $S_{\exp}(J, J')$ and $S_{cal}(J, J')$ could be considered as reasonable. The three J-O intensity parameters of Tb:Lu₂O₃ and Tb^{3+} -doped other host materials are presented in Table 2. The parameter Ω_2 depends on the asymmetry and covalence of the lanthanide ions coordination field. The high value of Ω_2 means the increase of the covalent bonding and a higher asymmetry of the lanthanide ion site in host materials.^[23] As shown in Table 2, Ω_2 of Tb³⁺-doped Lu₂O₃ is 3.79, which is larger than that of NaPO₃-BaF₂-(GdF₃/TbF₃) and KYb(WO₄)₂, but smaller than that of CdF₂, TbAl₃(BO₃)₄, LiYF₄, and GAGSe, indicating that the covalent bonding and asymmetry of Tb^{3+} in Lu₂O₃ are higher than those of NaPO₃-BaF₂-(GdF₃/TbF₃) and $KYb(WO_4)_2$, but lower than those of CdF_2 , $TbAl_3(BO_3)_4$, LiYF₄, and GAGSe. Furthermore, Ω_2 is relatively sensitive because of the admixing of the configuration, while Ω_4 and Ω_6 are less sensitive to the environment of the crystal field.^[23] As a spectroscopic quality factor, Ω_4/Ω_6 is generally used to predict the stimulated emission in laser hosts.^[21,24] For Tb:Lu₂O₃, Ω_4/Ω_6 is calculated to be 1.20, which is larger than that of most Tb^{3+} -doped host materials listed in Table 2. This suggests that Tb:Lu₂O₃ is a very promising medium for the visible laser operation.

Table 1. The average wavelength $(\overline{\lambda})$, refractive index (*n*), experimental line strength $S_{\exp}(J, J')$, and calculated line strength $S_{cal}(J, J')$ of Tb:Lu₂O₃ crystal.

| Transition (from ${}^{7}F_{6}$) | $\bar{\lambda}/nm$ | n | $S_{\rm exp}/10^{-20}~{\rm cm}^2$ | $S_{\rm cal}/10^{-20}~{\rm cm}^2$ |
|---|--------------------|-------|-----------------------------------|-----------------------------------|
| ⁵ L ₁₀ | 349 | 2.010 | 0.065 | 0.064 |
| ${}^{5}G_{6} + {}^{5}D_{3}$ | 353 | 2.007 | 0.027 | 0.027 |
| $^{5}D_{4}$ | 483 | 1.953 | 0.008 | 0.006 |
| ${}^{7}F_{0}+{}^{7}F_{1}$ | 1764 | 1.899 | 0.573 | 0.562 |
| ${}^{7}F_{2}$ | 1908 | 1.897 | 0.555 | 0.570 |
| ⁷ F ₃ | 2137 | 1.895 | 0.752 | 0.748 |
| rms $\Delta S/10^{-20}$ cm ² | 0.011 | | | |

Table 2. Comparison of the J–O intensity parameters and the values of Ω_4/Ω_6 for Tb:Lu₂O₃ crystal and other Tb³⁺-doped materials.

| Hosts | $\Omega_2/10^{-20}~\mathrm{cm}^2$ | $\Omega_4/10^{-20}~\mathrm{cm}^2$ | $\Omega_6/10^{-20}~\mathrm{cm}^2$ | $\chi=\Omega_4/\Omega_6$ | Ref. |
|--|-----------------------------------|-----------------------------------|-----------------------------------|--------------------------|-----------|
| KYb(WO ₄) ₂ | 1.91 | 2.41 | 4.91 | 0.49 | [19] |
| CdF ₂ | 7.90 | 2.99 | 3.09 | 0.96 | [21] |
| $TbAl_3(BO_3)_4$ | 8.15 | 0.29 | 2.44 | 0.12 | [26] |
| LiYF ₄ | 28.30 | 1.65 | 2.15 | 0.77 | [28] |
| GAGSe | 7.50 | 4.40 | 2.40 | 1.83 | [29] |
| NaPO ₃ -BaF ₂ -(GdF ₃ /TbF ₃) | 2.76 | 3.21 | 3.36 | 0.95 | [30] |
| Lu_2O_3 | 3.79 | 1.30 | 1.08 | 1.20 | this work |

For the Lu₂O₃ crystal, the radiative lifetime (τ_{rad}), fluorescence branching ratio (β), and spontaneous radiation transition probability (A) of ⁵D₄ multiplet of Tb³⁺ ions are calculated and shown in Table 3. Here, we mainly pay attention to the ⁵D₄ \rightarrow ⁷F₅ transition emitting green light and the ${}^{5}D_{4} \rightarrow {}^{7}F_{4}$ transition emitting yellow light. The fluorescence branching ratio of the ${}^{5}D_{4} \rightarrow {}^{7}F_{5}$ transition is 65.89%, which is the largest one among the listed transitions in Table 3, indicating the high possibility of a green emission around 543 nm. For the ${}^{5}D_{4} \rightarrow {}^{7}F_{4}$ transition at 584 nm, the fluorescence branching ratio is 4.50%. In addition, the radiative lifetime τ_{rad} is 3.02 ms, larger than that of Tb:KYb(WO₄)₂ (2.08 ms)^[19] and Tb:CdF₂ (2.77 ms),^[21] suggesting the higher energy storage capability of the Tb:Lu₂O₃ crystal.

Table 3. The spontaneous radiation transition probability (*A*), fluorescence branching ratio (β), and radiative lifetime (τ_{rad}) of Tb:Lu₂O₃ crystal.

| Transition (from ⁵ D ₄) | A/s^{-1} | eta/% |
|--|-------------------------|-------|
| ⁷ F ₆ | 53.71 | 16.22 |
| ${}^{7}F_{5}$ | 218.20 | 65.89 |
| ${}^{7}F_{4}$ | 14.89 | 4.50 |
| ⁷ F ₃ | 23.10 | 6.98 |
| ⁷ F ₂ | 10.35 | 3.13 |
| ⁷ F ₁ | 6.65 | 2.01 |
| ${}^{7}F_{0}$ | 4.24 | 1.28 |
| Radiative lifetime/ms | $\tau_{\rm rad} = 3.02$ | |

3.3. Fluorescence spectrum

Excited by 483 nm, the room-temperature fluorescence spectrum of the Tb^{3+} -doped Lu_2O_3 crystal is shown in Fig. 3, in which three observed emissions corresponding to the ${}^5D_4 \rightarrow {}^7F_5$, 7F_4 , and 7F_3 transitions are assigned and marked. The intensities of the three emission bands are in good agreement with the results of J-O analysis presented in Table 3. It can be seen that the ${}^{5}D_{4} \rightarrow {}^{7}F_{5}$ transition at 543 nm corresponding to green emission owns the largest emission cross-section $(9.43 \times 10^{-22} \text{ cm}^2)$ and the obtained FWHM is 4.15 nm. The emission cross-section is higher than that of Tb:KY₃F₁₀ $(8.0 \times 10^{-22} \text{ cm}^2 \text{ at } 545 \text{ nm})^{[6]}$ and Tb:LaF₃ $(7.5 \times 10^{-22} \text{ cm}^2 \text{ at } 543 \text{ nm})$.^[6] Furthermore, the emission cross-section of the yellow emission band at 584 nm corresponding to the ${}^{5}D_{4} \rightarrow {}^{7}F_{4}$ transition is 1.32×10^{-22} cm². The value is higher than that of Tb:PZABP $(0.7 \times 10^{-22} \text{ cm}^2 \text{ at}$ 582 nm),^[25] Tb:LBTAF $(0.58 \times 10^{-22} \text{ cm}^2 \text{ at } 585 \text{ nm})$,^[23] and Tb:TPP $(1.0 \times 10^{-22} \text{ cm}^2 \text{ at } 587 \text{ nm})$.^[26] The above data indicate that the Tb:Lu₂O₃ crystal is a promising candidate for a visible laser operation.



Fig. 3. Fluorescence spectrum of Tb:Lu₂O₃ crystal excited at 483 nm.

Excited at 483 nm, the fluorescence decay curve of ${}^{5}D_{4}$ level measured at room temperature is shown in Fig. 4. Obviously, it is single-exponential. The fluorescence lifetime τ_{exp} of ${}^{5}D_{4}$ level in the Tb:Lu₂O₃ crystal is fitted to be 1.13 ms. With the obtained radiative lifetime τ_{rad} (3.02 ms), the fluorescence quantum efficiency η (τ_{exp}/τ_{rad}) of the Tb:Lu₂O₃ crystal is calculated to be 37.4%, which is comparable to that of Tb:KY₃F₁₀^[27] (38%) and higher than that of Tb:KYb(WO₄)₂^[19] (19%). Furthermore, with the concentration of Tb³⁺ ions decreasing from 2.0 mol% to 0.1 mol%, the quantum efficiency was reported to change from 46% to 93% in Tb:LBTAF.^[23] Hence, the quantum efficiency of the Tb:Lu₂O₃ crystal could also be optimized by changing the doped concentration of the Tb³⁺ ions.



Fig. 4. (color online) Fluorescence decay curve of $^5\mathrm{D}_4$ level of Tb:Lu_2O_3 crystal.

4. Conclusion

Tb³⁺-doped Lu₂O₃ was successfully grown through the Fz method. The J–O theory was adopted to analyze the 4f^N radiative transitions of Tb³⁺ ions doped in Lu₂O₃. Around 483 nm, the absorption cross-section was obtained to be 3.5×10^{-22} cm² with an FWHM of 2.85 nm. As shown in the fluorescence spectrum, the ⁵D₄ \rightarrow ⁷F₅ transition around 543 nm, corresponding to the green emission, has the largest emission cross-section of 9.43×10^{-22} cm² with the FWHM of 4.15 nm and the emission cross-section of the ⁵D₄ \rightarrow ⁷F₄ transition around 584 nm, corresponding to the yellow emission, is 1.32×10^{-22} cm². With the fluorescence lifetime τ_{exp} of ⁵D₄ level fitted to be 1.13 ms and the radiative lifetime τ_{rad} of 3.02 ms, the fluorescence quantum efficiency was calculated to be 37.4%. These results reveal that the Tb:Lu₂O₃ crystal would be promising for green and yellow laser operations.

References

- [1] Gao J, Zhang L, Sun H X, Dai X J and Wu X D 2014 *Opt. Commun.* 319 110
- [2] Fang Q N, Lu D Z, Yu H H, Zhang H J and Wang J Y 2016 Opt. Lett. 41 1002
- [3] Nakamura S, Mukai T and Senoh M 1994 Appl. Phys. Lett. 64 1687

- [4] Zhang Y X, Wang S X, Alberto D L, Yu G L, Yu H H, Zhang H J, Mauro T, Xu X G and Wang J Y 2015 *Chin. Phys. Lett.* **32** 054210
- [5] Carnall W T, Fields P R and Rajnak K 1968 J. Chem. Phys. 49 4447
- [6] Metz P W, Marzahl D T, Majid A, Kränkel C and Huber G 2016 Laser Photon. Rev. 10 335
- [7] Zhang S, Hu Y, Chen L, Ju G, Wang Z and Lin J 2015 Opt. Mater. 47 203
- [8] Ji Z G, Zhao S C, Xiang Y, Song Y L and Ye Z Z 2004 Chin. Phys. 13 561
- [9] Liao J, Qiu B and Lai H 2009 J. Lumin. 129 668
- [10] Jenssen H P, Castleberry D, Gabbe D and Linz A 1973 IEEE J. Quant. Elect. 9 665
- [11] Kränkel C, Marzahl D T, Moglia F, Huber G and Metz P W 2016 Laser Photon. Rev. 10 548
- [12] Pauling L and Shappell M D 1930 Z. Kristallogr. 75 128
- [13] Peters V, Bolz A, Petermann K and Huber G 2002 J. Cryst. Growth 879 237
- [14] Lindan P J D and Gillan M J 1991 J. Phys.: Condens. Matter **3** 3929
- [15] Fukuda T and Chani V I 2007 Shaped Cryst.: Growth By Micro-Pulling-Down Technique (Berlin: Springer) p. 8
- [16] McMillen C, Thompson D, Tritt T and Kolis J 2011 Cryst. Growth . 11 4386
- [17] Fukabori A, Chani V, Kamada K, Moretti F and Yoshikawa A 2011 Cryst. Growth . 11 2404

- [18] Nakamura S, Senoh M, Nagahama S I, Iwasa N, Yamada T, Matsushita T and Sugimoto Y 1996 Jpn. J. Appl. Phys. 35 74
- [19] Loiko P, Mateos X, Dunina E, Kornienko A, Volokitina A, Vilejshikova E and Díaz F 2017 J. Lumin. 190 37
- [20] Zhang L, Peng M, Dong G and Qiu J 2012 Opt. Mater. 34 1202
- [21] Boubekri H, Diaf M, Labbaci K, Guerbous L, Duvaut T and Jouart J P 2013 J. Alloys Compd. 575 339
- [22] Kaminskii A A, Akchurin M S, Becker P, Ueda K, Bohatý L, Shirakawa A, Tokurakawa M, Takaichi K, Yagi H, Dong J and Yanagitani T 2008 Laser Phys. Lett. 5 300
- [23] Jamalaiah B C, Kumar J S, Babu A M, Sasikala T and Moorthy L R 2009 Physica B 404 2020
- [24] Jacobs R and Weber M 1976 IEEE J. Quant. Elect. 12 102
- [25] Kesavulu C R, Silva A C A, Dousti M R, Dantas N O, Camargo A S S and Catunda T 2015 J. Lumin. 165 77
- [26] Colak S and Zwicker W K 1983 J. Appl. Phys. 54 2156
- [27] Zhang J, Hao Z, Zhang X, Luo Y, Ren X, Wang X J and Zhang J 2009 J. Appl. Phys. 106 034915
- [28] Kaminskii A A 1996 Cryst. Lasers: Phys. Processes Operating Schemes (New York: CRC Press) p. 12
- [29] Shaw L B, Cole B, Thielen P A, Sanghera J S and Aggarwal I D 2001 IEEE J. Quant. Elect. 37 1127
- [30] Duhamel-Henry N, Adam J L, Jacquier B and Linarés C 1996 Opt. Mater. 5 197