### PAPER • OPEN ACCESS

# Effect of sintering on the mechanical properties of hydroxyapatite from fish bone (*Pangasius Hypophthalmus*)

To cite this article: Poedji Loekitowati Hariani et al 2019 IOP Conf. Ser.: Mater. Sci. Eng. 509 012109

View the article online for updates and enhancements.

## You may also like

- <u>The effects of hydroxyapatite</u> nanoparticles embedded in a MMPsensitive photoclickable PEG hydrogel on encapsulated MC3T3-E1 pre-osteoblasts Maria Carles-Carner, Leila S Saleh and Stephanie J Bryant
- <u>Synthesis of iron-substituted</u> <u>hydroxyapatite nanomaterials by co-</u> <u>precipitation method for defluoridation</u> Dagne Bayih Adamu, Enyew Zereffa, Teshome Abdo Segne et al.
- Fabrication and characterization of nHA/titanium dental implant Sina Sazesh, Aazam Ghassemi, Reza Ebrahimi et al.





DISCOVER how sustainability intersects with electrochemistry & solid state science research



This content was downloaded from IP address 3.134.90.44 on 07/05/2024 at 20:22

# Effect of sintering on the mechanical properties of hydroxyapatite from fish bone (Pangasius Hypophthalmus)

#### Poedji Loekitowati Hariani<sup>1,\*</sup>, Muhammad Said<sup>1</sup>, Salni<sup>2</sup>

<sup>1</sup>Department of Chemistry, Faculty of Mathematic and Natural Sciences, Sriwijaya University, Indonesia

<sup>2</sup> Department of Biology, Faculty of Mathematic and Natural Sciences, Sriwijaya University, Indonesia

Email: <sup>a,\*</sup> puji lukitowati@mipa.unsri.ac.id; <sup>b</sup> saidusman2011@gmail.com; <sup>c</sup> salnibasir@vahoo.com

Abstract. Hydroxyapatite was synthesized from materials containing calcium. The aim of this research is to determine the effect of sintering i.e. temperature and duration on mechanical properties of hydroxyapatite from paten fish (Pangasius hypophthalmus) bone. The calcium content of fish bone was analyzed by using atomic absorption spectroscopy. Hydroxyapatite synthesis was conducted by hydrothermal method followed by a sintering process at various temperatures 800, 900, 1000, 1100 and 1200°C for 2 hours. The optimum temperature for sintering hydroxyapatite was used for further synthesis by varying duration i.e. 1, 2, 3, 4 and 5 hours. The result shows that increasing temperature and duration of sintering enhanced Vickers Hardness and Modulus Young of hydroxyapatite product before it decreases subsequently. The optimum sintering condition was obtained at 1100°C and 2 hours with mechanical properties represent by Vickers Hardness 20.6±0.62 VHN and Modulus Young 3.23±0.11 GPa. The hydroxyapatite obtained has an average crystallite size of 45.68 nm and crystallinity of 87.31%. SEM-EDS analysis indicates the hydroxyapatite was porous and has an irregular shape with O, Ca and P content 33.12; 21.35 and 45.53%, respectively.

**Keywords:** hydroxyapatite, fish bone, sintering, mechanical properties

#### 1. Introduction

Hydroxyapatite is an apatite mineral compound having general formula  $Ca_{10}(PO_4)_6(OH)_2$ . The mineral shows the hexagonal structure and contains a stoichiometrically Ca/P element ratio 1.667 [1]. Hydroxyapatite is a biomaterial that has the potential to be used in biomedical applications such as tissue engineering, teeth and maxillofacial [2-4]. Hydroxyapatite can also be used in the water treatment process for pollutants removals such as Pb [5], nitrobenzene [6], and dye [7].

Hydroxyapatite has a composition like bone and teeth [1]. The mineral shows biocompatibility and able to form bonds with living tissue, it also can integrate with a bone to form new tissue. It displays antimicrobial property as well as osteoconductivity and osteoinductivity [3]. In addition to the properties mention above, hydroxyapatite can be made in form of powder with a porous structure and good mechanical strength hence it suitable for medical application [8]. Biomaterial contained calcium such as star fish [3], egg shell [9], bovine bone [10] and phosphogypsum waste [5] can be used as raw material for hydroxyapatite.

One of the fish types that are cultivated and consumed by the people in Indonesia is paten fish (Pangasius Hypophthalmus). Paten fish production in Indonesia continues to increase annually due to

Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

13th Joint Conference on Chemistry (13th JCC)

IOP Conf. Series: Materials Science and Engineering 509 (2019) 012109 doi:10.1088/1757-899X/509/1/012109

increased demand for both domestic and export consumption. The increased number of paten fish consumed also increases the solid waste produced i.e. fish bones. Fish bone composes approximately 10-15% of the fish body [11]. Calcium content in fish bone is a potential resource for hydroxyapatite synthesis due to its cheapness and availability [12]. Synthesis of hydroxyapatite using fish bones also provides benefit for the environment because it solves the solid waste problem from paten fish consumption [13].

Several methods had been developed for hydroxyapatite synthesis such as sol-gel method [8], hydrothermal [10], wet-precipitation [4] and microwave processing [14]. The difference in synthesis method can result in different degree of crystallinity, particle size, morphology, homogeneity, and stoichiometry of resulting product. The hydrothermal method shows a high success rate among other methods not to mention its simplicity. Proper condition of sintering process plays important role in producing high quality of hydroxyapatite. Temperature selection and duration time of sintering impacts on the crystallinity and mechanical property i.e. Vickers Hardness and Modulus Young [15].

The aim of the research is to synthesis hydroxyapatite from raw materials of paten fish (*Pangasius Hypophthalmus*) bone by hydrothermal method. Optimum temperature and sintering duration will be evaluated. CaCO<sub>3</sub> from fish bone was converted to CaO through calcination process at 900°C. CaO compound was further converted into hydroxyapatite through a chemical reaction with  $(NH_4)_2HPO_4$  in alkaline condition.

#### 2. Material and Methods

#### 2.1. Materials

A sample of fish bone was obtained from Palembang, South Sumatera Indonesia. Chemicals used in this research were distilled water,  $HNO_3$  (65%),  $NH_4OH$  ( $NH_3$  in  $H_2O$  28-30%) both were purchased from Sigma-Aldrich (65%) and ( $NH_4$ )<sub>2</sub>HPO<sub>4</sub> purchased from Merck.

#### 2.2. Determination of calcium in fish bone

The fish bone powder (0.142 g) poured into the flask, added by 10 mL HNO<sub>3</sub> 36% and deionized water 50 mL. The mixture was heated by using an electric mantle at 180°C for 2 hours. The resulting filtrate was transferred into a volumetric flask of 50 mL and then diluted using deionized water. The Ca contents were determined by using Atomic Absorption Spectroscopy Shimadzu AA 7000.

#### 2.3. Synthesis of Hydroxyapatite

Fish bones were cleaned from dirt, washed with distilled water, then boiled for 3 hours. The bones were dried in an oven at  $110^{\circ}$ C for 2 hours. About 250 g of fish bone powder was heated at 900°C for 2 hours to convert CaCO<sub>3</sub> to CaO and then it was crushed into powder using ball milling to obtain nano size.

The mixture of 12 g CaO and 100 mL HNO<sub>3</sub> 2 M stirred at 70°C for an hour. The precipitate was filtered and washed using distilled water until pH neutralized. The precipitate was dried in an oven at 110°C for 2 hours. This dried powder of 6.0 g was added into 250 mL (NH<sub>4</sub>)<sub>2</sub>HPO<sub>4</sub> 0.9 M, mixed by using shaker at 120 rpm and NH<sub>4</sub>OH 1 M was added dropwise to obtain pH±10. Mixing was continued for 24 hours, then the mixture was washed with distilled water to remove NH<sub>4</sub><sup>+</sup> and NO<sub>3</sub><sup>-</sup>. The materials were dried in an oven at 110°C for 3 hours.

The powder was then solidified using the hydraulic machine at 20 MPa on cylinder specimen with 38 mm diameter and 40 mm length. The sintering process was conducted at 800, 900, 1000, 1100 and 1200°C for 2 hours, and then by using optimum sintering temperature, the calcination was carried out for various duration time (1, 2, 3, 4 and 5 hours).

#### 2.4. Characterization of Hydroxyapatite

Hardness test was conducted using the Vickers method with 50 g load for 10 seconds and 5 different points of measurement were chosen. The test repeats for 3 times to estimate the deviation standard. Modulus Young is measured using the same instrument. Hydroxyapatite powder was characterized to

**IOP** Publishing

determine the crystallinity using X-ray diffractometer (XRD Miniflex 600) the 2 $\theta$  at a range of 0-90° using CuK $\alpha$ =1.5418 Å, voltage 45 kV, and 100 mA. XRD data were used to calculate crystallite size and crystallinity using Scherrer equation. The morphology and elemental composition were evaluated by using SEM-EDS JEOL JSM 6510 LA.

#### 3. Results and Discussion

This study report that paten fish (*Pangasius Hypophthalmus*) bone contained calcium 18.30%. This amount of calcium has the potential as raw materials resources for hydroxyapatite synthesis. The synthesis was conducted via a hydrothermal method. Calcination of fish bone to convert CaCO<sub>3</sub> into CaO was carried out through chemical reaction as follows:

$$CaCO_3 \rightarrow CaO + CO_2$$
 (1)

$$CaO + 2HNO_3 + 3H_2O \rightarrow Ca(NO_3)_2 + 4H_2O$$
<sup>(2)</sup>

$$10Ca(NO_3)_2 + 6(NH_4)_2HPO_4 + 2NH_4OH \rightarrow Ca_{10}(PO_4)_6(OH)_2 + 14NH_4NO_3 + 6HNO_3$$
(3)

The XRD pattern of hydroxyapatite synthesized at different temperatures 800, 900, 1000, 1100 and 1200°C depicted in Fig. 1. The sintering temperature at 800°C shows broad peaks represents an amorphous structure. The broad pattern indicates the existence of protein and collagen [13]. As the temperature got higher, sharp and narrow peaks resulted. Even though, at 1200°C the peak intensity is decreased. At a temperature <1250°C,  $\alpha$ -TCP was formed which is converted into  $\beta$ -TCP and tetra calcium phosphate at a higher temperature [8].  $\beta$ -TCP can reduce the mechanical property of hydroxyapatite [15]. The sintering temperature at 1250°C can not attain pure hydroxyapatite but it will contain potassium calcium phosphate with crystalline size quite large i.e. 1224 nm [16].



**Figure 1.** XRD pattern of hydroxyapatite sintered at (a)  $800^{\circ}$ C (b)  $900^{\circ}$ C (c)  $1000^{\circ}$ C (d)  $1100^{\circ}$ C and (e)  $1200^{\circ}$ C.

Based on JCPDS No. 09.0432, characteristic peak of hydroxyapatite at  $2\theta$ =25.8 (002); 31.7 (211); 32.1 (112); 32.9 (300); 46.7 (222) and 49.4° (213). The peaks shown is for synthetic hydroxyapatite in different intensity. The average crystalline size and crystallinity shown in table 1. Crystallite size is proportional to the crystallinity. The similar result of hydroxyapatite synthesis using calcium nitrate and potassium dihydrogen phosphate precursors [17]. In this study, we report that the sintering process at 800°C produced lowest crystallite size and crystallinity whereas sintering process at 1100°C obtained highest crystallite size and crystallinity. The other research described increased of crystallite size

accompanied by a decrease of the amorphous phase [18]. The hydroxyapatite of our synthesis indicates a similarity between hydroxyapatite from human bone i.e. 20-80 nm [19].

Sintering temperature (°C)	Average crystallite size (nm)	Average crystallinity (%)
800	24.16	66.78
900	31.26	73.56
1000	38.89	80.20
1100	45.68	87.31
1200	42.46	85.19

**Table 1.** The average crystallite size and crystallinity of hydroxyapatite.

Process duration affected the optimum condition for sinter completion. Fig. 2 shows various duration time of sintering at 1100°C. Optimum time obtained is 2 hours while 1 hour duration still displayed low peaks and longer duration (3 and 4 hours) indicates a decrease in intensity at  $2\theta=31.7^{\circ}$ . The long heating process during sintering caused decomposition of hydroxyapatite product henceforth decreased its intensity.



**Figure 2.** XRD pattern of hydroxyapatite sintered for (a) 1 (b) 2 (c) 3 (d) 4 and (e) 5 hours.

Table 2 displays crystallite size and crystallinity of hydroxyapatite which was synthesized at various duration time and 1100°C. While 3 hours duration shows slight different with 2 hours, sintering duration for 4 and 5 hours resulted in lower crystallite size and crystallinity. Longer heating duration on sintering triggered contraction and expansion which caused damaged materials.

Time (hour)	Average crystallite size (nm)	Average crystallinity (%)
1	42.16	85.78
2	45.68	87.31
3	44.76	86.69
4	36.89	78.89
5	34.67	74.90

**Table 2.** The average crystallite size and crystallinity of hydroxyapatite at various sintering duration.

The temperature used in sintering affect the mechanical property of hydroxyapatite. This material's drawback inhibits its utilization in bone implants due to fragility. One way to overcome this situation is by controlling the sintering process i.e. temperature [20]. Mechanical property can be measured by hardness value and Modulus Young. Material hardness defined as material hardness against deformation on the local area while Modulus Young indicates stiffness measure of materials. The high temperature of the sintering process induced microstructure alteration of hydroxyapatite as well as pore size. Increase hardness of crystal can be encouraged by positioning atoms in crystal lattice which is highly ordered. Increased sintering temperature enhanced crystal size and crystallinity but decreased porosity and surface area [16]. The porosity deceased will affect hardness by increase it. Fig. 3 and 4 shows the effect of sintering temperature on hardness and Modulus Young.



Figure 3. Vickers Hardness of hydroxyapatite sintered at various temperatures.



Figure 4. Modulus Young of hydroxyapatite sintered at a various temperature.

Hardness decrease was observed at 1200°C as well as Modulus Young even though just a bit. The hydroxyapatite synthesis by using wet precipitation method and wet mechanochemical result in a similar trend which is increased sintering temperature up to certain degree will cause increased hardness and then decreased at a higher temperature [21]. The hardness is not only affected by solid density but also grain size [20]. The largest hardness value obtains at 1100°C. For to the same temperature (1100°C) on his hydroxyapatite synthesis by using precursors of calcium hydroxide and orthophosphoric acids [22]. The increase of sintering temperature also increasing Modulus Young. The Modulus Young for 1100 and 1200°C sintering temperature shows a slight discrepancy i.e. 3.23 and 3.26 GPa.

The effect of sintering duration to Vickers Hardness and Modulus Young is shown on Fig. 5 and 6. The Fig. depicted the rise of Vickers Hardness and Modulus Young at 1 and 2 hours duration which is decreased afterward. Optimum values obtained after 2 hours duration are 20.6±0.62 VHN and 3.23±0.11 GPa for Vickers Hardness and Modulus Young, respectively.



**Figure 5.** Vickers Hardness of hydroxyapatite sintered at the various duration of time.



**Figure 6.** Modulus Young of hydroxyapatite sintered at the various duration of time.

The morphological of hydroxyapatite synthesized at 1100°C and 2 hours sintering temperature and duration is shown in Fig. 7. The studied the effect of sintering on the transformation of hydroxyapatite micro structure, finds out that change of pore began above 1260°C, pore shape became roundish, obtrusive and solid [23]. The temperature creates a condition which plays an important role in the morphologic formation, temperature control undoubtedly vital to the size and shape of crystal formed [24]. In this report, we obtained that hydroxyapatite has an oval shape, agglomerated and display porous structure. This result is alike what has been reported the other author which was hydroxyapatite synthesis from calcium nitrate and diammonium hydrogen phosphate using the same method [25]. Table 3 shows an elemental analysis result by the EDS method. Based on the data displayed, hydroxyapatite is purified

comprised of Ca, P and O and shows the molar ratio of Ca/P 1.654 approach standard ratio of synthetic hydroxyapatite 1.667.



**Figure 7.** Hydroxyapatite morphology sintered at 1100°C for 2 hours.

**Table 3.** Elemental composition of hydroxyapatite sintered at 1100°C for 2 hours.

Elements	Mass (%)
0	33.12
Р	21.35
Ca	45.53

#### 4. Conclusions

This work shows that temperature and duration of sintering affect hydroxyapatite product prepared from paten fish (*Pangasius Hypophthalmus*) bone using the hydrothermal method. Using various temperature (800-1200°C) and sintering duration (1-5 hours) hydroxyapatite were obtained having best Vickers Hardness and Modulus Young value i.e.  $20.6\pm0.62$  VHN and Modulus Young  $3.23\pm0.11$  GPa at  $1100^{\circ}$ C after 2 hours sintering process. XRD pattern supported this result by sharp and narrow peaks with high intensity. The average crystallite size obtained of 45.68 nm and 87.31% of crystallinity. Elemental analysis shows no impurity in the product with Ca/P ratio 1.654 approaches the standard ratio of pure hydroxyapatite 1.667.

#### Acknowledgments

We are very grateful to the Ministry of Research, Technology and Higher Education of the Republic Indonesia for financial support through Hibah Penelitian Dasar Unggulan Perguruan Tinggi (Grant No. 093/SP2H/LT/DRPM/IV/2018).

#### References

- [1] Best S, Porter A, Thian E and Huang J 2008 Bioceramics: past, present and for the future *J. Eur. Ceram. Soc.* **28** 7 1319-27
- [2] Nikpour M, Rabiee S and Jahanshahi M 2012 Synthesis and characterization of hydroxyapatite/chitosan nanocomposite materials for medical engineering applications *Compos. B. Eng.* 43 4 1881-6
- [3] Rodríguez-Lugo V, Salinas-Rodríguez E, Vázquez R, Alemán K and Rivera A 2017

Hydroxyapatite synthesis from a starfish and  $\beta$ -tricalcium phosphate using a hydrothermal method *RSC Adv.* 7 13 7631-9

- [4] Santos M H, Oliveira M d, Souza L P d F, Mansur H S and Vasconcelos W L 2004 Synthesis control and characterization of hydroxyapatite prepared by wet precipitation process *Mater*. *Res.* 7 4 625-30
- [5] Mousa S, Ammar N and Ibrahim H 2016 Removal of lead ions using hydroxyapatite nanomaterial prepared from phosphogypsum waste *J. Saudi Chem. Soc.* **20** 3 357-65
- [6] Wei W, Sun R, Jin Z, Cui J and Wei Z 2014 Hydroxyapatite–gelatin nanocomposite as a novel adsorbent for nitrobenzene removal from aqueous solution *Appl. Surf. Sci.* **292** 1020-9
- [7] Allam K, El Bouari A, Belhorma B and Bih L 2016 Removal of methylene blue from water using hydroxyapatite submitted to microwave irradiation *J. Water Resource Prot.* **8** 03 358
- [8] Sopyan I, Singh R and Hamdi M 2008 Synthesis of nano sized hydroxyapatite powder using solgel technique and its conversion to dense and porous bodies *Indian J. Chem. A* **47A** 1626-31
- [9] Ibrahim W and Mohamad Kasim A 2011 Evaluation of Compressive Strength of Eggshell Hydroxyapatite *Adv. Mater. Res.* **264** 571-5
- [10] Barakat N A, Khil M S, Omran A, Sheikh F A and Kim H Y 2009 Extraction of pure natural hydroxyapatite from the bovine bones bio waste by three different methods *J. Mater. Process. Technol.* 209 7 3408-15
- [11] Malde M, Graff I, Siljander-Rasi H, Venäläinen E, Julshamn K, Pedersen J and Valaja J 2010 Fish bones-a highly available calcium source for growing pigs J. Anim. Physiol. Anim. Nutr. 94 5 e66-e76
- [12] Boutinguiza M, Pou J, Comesaña R, Lusquiños F, De Carlos A and León B 2012 Biological hydroxyapatite obtained from fish bones *Mater. Sci. Eng. C* **32** 3 478-86
- [13] Pal A, Paul S, Choudhury A R, Balla V K, Das M and Sinha A 2017 Synthesis of hydroxyapatite from Lates calcarifer fish bone for biomedical applications *Mater. Lett.* 203 89-92
- [14] Xiao W, Gao H, Qu M, Liu X, Zhang J, Li H, Yang X, Li B and Liao X 2018 Rapid microwave synthesis of hydroxyapatite phosphate microspheres with hierarchical porous structure *Ceram*. *Int.* 44 6 6144-51
- [15] Monmaturapoj N and Yatongchai C 2010 Effect of sintering on microstructure and properties of hydroxyapatite produced by different synthesizing methods J. Metals Mater. Miner. 20 2 53-61
- [16] Poinern G E J, Brundavanam R K, Le X and Fawcett D 2012 The mechanical properties of a porous ceramic derived from a 30 nm sized particle based powder of hydroxyapatite for potential hard tissue engineering applications Am. J. Biomed. Eng. 2 6 278-86
- [17] Padmanabhan S K, Balakrishnan A, Chu M-C, Lee Y J, Kim T N and Cho S-J 2009 Sol-gel synthesis and characterization of hydroxyapatite nanorods *Particulogy* 7 6 466-70
- [18] Saeri M, Afshar A, Ghorbani M, Ehsani N and Sorrell C 2003 The wet precipitation process of hydroxyapatite *Mater. Lett.* 57 24-25 4064-9
- [19] Cunniffe G M, O'Brien F J, Partap S, Levingstone T J, Stanton K T and Dickson G R 2010 The synthesis and characterization of nanophase hydroxyapatite using a novel dispersant-aided precipitation method *J. Biomed. Mater. Res. A* 95 4 1142-9
- [20] Ramesh S, Tan C, Peralta C and Teng W 2007 The effect of manganese oxide on the sinterability of hydroxyapatite *Sci. Technol. Adv. Mater.* **8** 4 257-63
- [21] Ramesh S, Aw K, Tolouei R, Amiriyan M, Tan C, Hamdi M, Purbolaksono J, Hassan M and Teng W 2013 Sintering properties of hydroxyapatite powders prepared using different methods *Ceram. Int.* 39 1 111-9
- [22] Tolouei R, Ramesh S, Tan C, Amiriyan M and Teng W 2011 Sintering effects on the densification of nanocrystalline hydroxyapatite *Int. J. Automot. Mech. Eng. (IJAME)* **3** 249-55
- [23] Prokopiev O and Sevostianov I 2006 Dependence of the mechanical properties of sintered hydroxyapatite on the sintering temperature *Mater. Sci. Eng. A* **431** 1-2 218-27
- [24] Wang P, Li C, Gong H, Jiang X, Wang H and Li K 2010 Effects of synthesis conditions on the

morphology of hydroxyapatite nanoparticles produced by wet chemical process *Powder Technology* **203** 2 315-21

[25] Raj S V, Rajkumar M, Sundaram N M and Kandaswamy A 2018 Synthesis and characterization of hydroxyapatite/alumina ceramic nanocomposites for biomedical applications *Bull. Mater. Sci.* 41 4 93