### **OPEN ACCESS**

# Review—Intracellular Sensors Based on Carbonaceous Nanomaterials: A Review

To cite this article: Chunmei Li et al 2020 J. Electrochem. Soc. 167 037540

View the article online for updates and enhancements.

# You may also like

- <u>Advances in nanowire bioelectronics</u> Wei Zhou, Xiaochuan Dai and Charles M Lieber
- Intracellular FRET-based probes: a review Clare E Rowland, Carl W Brown, Igor L Medintz et al.
- <u>Getting around the cell: physical transport</u> in the intracellular world Saurabh S Mogre, Aidan I Brown and Elena F Koslover

# PAT-Tester-x-8 Potentiostat: Modular Solution for Electrochemical Testing!

- Flexible Setup with up to 8 Independent Test Channels! Each with a fully equipped Potentiostat, Galvanostat and EIS!
- Perfect Choice for Small-Scale and Special Purpose Testing!
   Suited for all 3-electrode, optical, dilatometry or force test cells from EL-CELL.
- Complete Solution with Extensive Software!
   Plan, conduct and analyze experiments with EL-Software.
- Small Footprint, Easy to Setup and Operate!
   Usable inside a glove box. Full multi-user, multi-device control via LAN.



# Contact us:

- **L** +49 40 79012-734
- ➡ sales@el-cell.com
- www.el-cell.com





electrochemical test





# **Review—Intracellular Sensors Based on Carbonaceous** Nanomaterials: A Review

#### Chunmei Li, Yihan Wang, Hui Jiang,<sup>z</sup> and Xuemei Wang<sup>z</sup>

State Key Laboratory of Bioelectronics, National Demonstration Center for Experimental Biomedical Engineering Education, School of Biological Science and Medical Engineering, Southeast University, Nanjing 210096, People's Republic of China

In recent years, carbon nanomaterials and their derivatives/composites have attracted much attention for their role in new developments in the field of biosensors due to their unique electronic, optical, thermal and mechanical properties in biosensors, which inspires us to compile this review. To focus on the relationship between cell biology and some diseases (e.g., cancer or diabetes), this review describes the applications of various types of carbon nanomaterials in intracellular sensors. We also introduce four kinds of intracellular sensors based on carbon nanomaterials, including intracellular pH sensors, intracellular thermal sensors, intracellular biomolecule sensors. Then, we briefly summarize the applications of carbon nanomaterials based intracellular sensors for diagnosis or treatment of various diseases. Finally, a future perspective and the challenges of intracellular sensors based on carbon nanomaterials are briefly rendered.

© 2020 The Author(s). Published on behalf of The Electrochemical Society by IOP Publishing Limited. This is an open access article distributed under the terms of the Creative Commons Attribution 4.0 License (CC BY, http://creativecommons.org/licenses/ by/4.0/), which permits unrestricted reuse of the work in any medium, provided the original work is properly cited. [DOI: 10.1149/ 1945-7111/ab67a3]

Manuscript submitted September 16, 2019; revised manuscript received December 11, 2019. Published January 20, 2020. This paper is part of the JES Focus Issue on Sensor Reviews.

Carbon nanomaterials refer to carbon materials having at least one dimension of less than 100 nm and are composed of sp<sup>2</sup> and sp<sup>3</sup>-bonded carbon atoms or heterogeneous components (non-carbon atoms),<sup>1</sup> which generally include carbon dots (also known as carbon quantum dots, CDs), fullerene, carbon nanotube, graphene, graphene oxide and graphitic carbon nitride (g-C<sub>3</sub>N<sub>4</sub>).<sup>2–5</sup> Due to excellent physical, chemical, mechanical and electrical properties, carbon nanomaterials have attracted intensive interest and have been widely used to fabricate sensors, such as gas or vapor sensors,<sup>6–12</sup> electrochemical sensors, <sup>13–30</sup> biological sensors,<sup>31–37</sup> strain sensors,<sup>38–44</sup> optical chemical sensors.<sup>45,46</sup> In particular, the fascinating biocompatibility and chemical inertness of carbon nanomaterials and their composites make them attractive candidates for perception intracellular microenvironment (e.g., pH value and temperature), <sup>13,47–49</sup> sensing molecules or ions inside cells.<sup>50–53</sup>

Cell biology aims to study the structures and functions of millions of biomolecules in single cells, and to discover the relationship between abnormal cell metabolism and some diseases such as cancer or diabetes.54,55 Intracellular microenvironment (e.g., pH value and temperatures) and the spatiotemporal distribution of molecules or ions in cells play important roles in cell metabolism.56 Abnormal microenvironment parameters and inappropriate concentrations of molecules or ions are intuitional indicators for these intractable diseases.<sup>57</sup> Thus, recent advances in the development of cell biology and sensing systems have been achieved, which allow for the precise and rapid detection of intracellular species and the complex microenvironment in live cell for biomedical applications.<sup>49,58–62</sup> However, using common sensing system, the determination of some given analytes or specific microenvironments in cells is easily interfered by the complicated cellular matrices and unavoidable background signals. Here carbon nanomaterials-based sensors may offer great opportunities to monitor intracellular microenvironment and analyzed disease-related species in complicated live cells due to their excellent properties.

In this review, we will summarize the most recent advance on the applications of intracellular sensors fabricated by carbon nanomaterials and their composites (Scheme 1) was summarized. Firstly, we will briefly introduce various kinds of carbon nanomaterials, including CDs or graphene quantum dots, carbon nanotubes, graphene or graphene oxide,  $g-C_3N_4$  and fullerene, and their possibility as intracellular sensors. Then, we will discuss the application of intracellular sensors and summarize four kinds of

intracellular sensors based on carbon nanomaterials, i.e., intracellular pH sensors, intracellular thermal sensors, intracellular metal ions sensors, and intracellular biomolecule sensors. We also briefly summarize the applications of carbon nanomaterials based intracellular sensors for diagnosis or treatment of various diseases. Lastly, the future perspectives and challenges of intracellular sensors based on carbon nanomaterials are briefly rendered.

#### Carbon Nanomaterials and Their Possibility as Intracellular Sensors

Carbon nanomaterials and its derivatives have unique electronic, optical, thermal, and mechanical properties and have attracted considerable attention in the field of biosensors or intracellular sensor in recent years. In this section, we will summarize and discuss the properties of various kinds of carbon nanomaterials and the possibility of application in intracellular sensor for each of carbon nanomaterials.

CDs or graphene quantum dots are zero-dimensional carbon nanomaterials.<sup>63,64</sup> Considerable attention has been paid to fluorescent CDs or graphene quantum dots owing to their small sizes ( $\sim$ 5 nm), low toxicity, good biocompatibility, stable photoluminescence and chemical inertness, which are advantageous over other fluorescence probes used for intracellular sensors.<sup>20,65</sup> In the application of intracellular sensor, CDs generally enter living cells by incubating living cells with CDs at 37 °C and then intracellular microenvironment (e.g., pH value and temperatures) or intracellular molecules or ions are analyzed by CDs through confocal fluorescence microscopic technique or electrochemistry methods.

Carbon nanotubes, including single-walled carbon nanotubes and multi-walled carbon nanotubes, are one kind of carbon nanomaterials with relatively large surface area, unique chemical property (including mechanical, electrical, thermal and catalytic properties). Especially, the excellent catalytic effect between multi-walled carbon nanotubes and metal/metal oxide or sulfides have attracted intensive interest.<sup>66–72</sup> The single-walled carbon nanotubes have a strong photoluminescence and have been used to analyze intracellular microenvironment or intracellular molecules or ions by entering the living cell in the intracellular sensing system. Multi-walled carbon nanotubes with excellent electronic properties and functional surface structures, are not only used to prepare electrode to detect substances secreted by living cells in extracellular sensing system,<sup>73,74</sup> but also modified with designed biomolecules or dyes via functional groups (such as, carboxyl groups) to achieve sensing functions in intracellular sensing system.<sup>74,75</sup>



Scheme 1. A summary of carbon nanomaterials used as intracellular sensors.

Graphene is another kind of carbon nanomaterial, which is composed of sp<sup>2</sup>-hybridized carbon atom and exhibits no fluorescence due to a zero optical bandgap.<sup>76–79</sup> Graphene oxide is obtained by introducing functional groups to graphene, and shows fluorescence. Graphene or graphene oxide has shown great potentials for biosensing applications due to its good water solubility, large surface area, unique surface properties, low cytotoxicity and high cellular uptake efficiency.<sup>80–82</sup> Graphene is usually used to detect substances secreted by living cells or cell lysates in extracellular sensing system through electrochemical methods.<sup>83,84</sup> In sensing system, graphene oxide has been used to sense intracellular microenvironment<sup>85</sup> and determine the molecules or ions inside/outside cells.<sup>86,87</sup>

g-C<sub>3</sub>N<sub>4</sub>, including bulk g-C<sub>3</sub>N<sub>4</sub>, g-C<sub>3</sub>N<sub>4</sub> nanosheets, and g-C<sub>3</sub>N<sub>4</sub> quantum dots, possesses superior optical properties, thermostability, chemical stability, biocompatibility and low toxicity. <sup>88–92</sup> Based on its excellent properties, g-C<sub>3</sub>N<sub>4</sub> has been used to detect pH, metal ions, biomolecules in living cells. In sensing system, g-C<sub>3</sub>N<sub>4</sub> has been used to sense intracellular microenvironment and determine the intracellular molecules or ions by entering living cells or outside the living cells.

Fullerene is also one of kind carbon nanomaterials. Recent studies<sup>93,94</sup> have proved that fullerene was toxicity to bacteria due to direct oxidation of the cell, therefore the application of fullerene in intracellular sensor was still be explored.

#### Intracellular Sensor Based on Carbon Nanomaterials

Carbon nanomaterials have been widely studied for intracellular sensor. In this section, we will summarize and discuss the application of carbon nanomaterials in pH sensing, thermal sensing, metal sensing and biomolecule sensing in living cells, respectively.

**Intracellular pH sensors.**—Intracellular pH is an important parameter of intracellular microenvironment. It is directly related to protein conformational transformation and enzyme catalytic efficiency.<sup>95,96</sup> In order to maintain normal physiological functions, the pH of intracellular organelles (e.g., cytoplasm, mitochondria and lysosomes) are located in a very narrow range.<sup>97</sup> Abnormal intracellular pH causes cytopathic and even apoptosis, and is one of the important indicators of many diseases including cancer.<sup>98–101</sup> Due to the importance of pH in the cell, there are a variety of intracellular pH sensors fabricated by carbon nanomaterials described in this section.

Chen et al.<sup>102</sup> have reported an intracellular pH sensor, which has been prepared by multi-walled carbon nanotubes decorated with gold/silver core–shell nanoparticles (Au@Ag NPs) labeled with 4mercaptobenzoic acid (4MBA) and fluorescein isothiocyanate (FITC), for detecting pH variation through exploit the surface enhanced Raman scattering (SERS) spectra features of 4MBA molecules during intracellular process such as endocytosis (Fig. 1a). Shao et al.<sup>85</sup> have developed an intracellular pH sensor based on graphene oxide-DNA nanosystem fabricated by coupling a hybrid comprising dye-labeled i-motif forming oligonucleotide (IFO)and its cDNA with one mismatch to graphene oxide to sensitively detect pH variations in live cells (Fig. 1b). Shi et al.<sup>103</sup> have proposed an intracellular pH sensor based on nitrogen-rich functional groups carbon nanoparticles(N-CNs) for pH fluorescence imaging of live T24 cells (Fig. 1c). Furthermore, Zhang et al.<sup>104</sup> even have prepared a lysosome pH sensor with CDs (Fig. 1d).

Intracellular thermal sensors .- Intracellular temperature is another important parameter of intracellular microenvironment. First, intracellular temperature affects and regulates chemical and biological reactions in cytoplasm and in organelles, such as endoplasmic reticulum, mitochondria and nucleus.<sup>105–107</sup> For example, the intracellular temperature affects and regulates the synthesis of DNA in nucleus, and also regulates the formation of adenosine triphosphate (ATP) in mitochondria. Second, temperature variation in cells can be an indicator for some disease. For example, the temperature in cancer cells is higher than normal cells owing to excessive metabolic activities or reactive oxygen species (ROS) scavenging in cancer cells, therefore temperature increase in cell can be an evidence for cancer diagnosis.<sup>108</sup> Consequently, there is a need for seeking methods based on new materials that enable reliable and accurate monitoring intracellular temperature. Carbon nanomaterials have attracted increasing interest in monitoring intracellular temperature because of their fascinating biocompatibility and chemical inertness. 49,109,110

Kumawat et al.<sup>58</sup> have synthesized a graphene quantum dots using ethanolic extracts of *mangifera indica* (mango) leaves with excitation-independent near-infrared (NIR)fluorescence emission. The graphene quantum dots have intracellular temperature sensing properties and have been used to analyze intracellular temperature (25 °C–45 °C) of live L929 cells (Fig. 2a).

Shi et al.<sup>111</sup> have used green fluorescence N, S co-doped CDs as a stable bio-imaging probe for sensing of intracellular temperature. Specifically, Hela cells are stained by the N, S co-doped CDs and the green fluorescence of Hela cells in the temperature of 35 °C is weaker than in the temperature of 25 °C (Fig. 2b).

We et al.<sup>112</sup> have prepared a ratiometric intracellular temperature sensor by a fluorescence probe (a CDs-RhB probe) fabricated by conjugating Rhodamine B (RhB) with CDs via a covalent bond. The CDs-RhB probe has two noticeable peaks, 482 and 586 nm, which could be assigned to the emission from CDs and RhB. Therefore, the intracellular temperature of cell is quantified by calculating the ratio between these two peaks ( $I_{586}/I_{482}$ ) (Fig. 2c). Macairan et al.<sup>113</sup> also have proposed a ratiometric intracellular

Macairan et al.<sup>113</sup> also have proposed a ratiometric intracellular temperature sensor by a temperature-dependent fluorescence CDs synthesized via a microwave method. The CDs have a blue band and a red fluorescence band when excited at 405 nm. With increasing temperature, red-to-blue fluorescence ratio are increased. The ratiometric change in fluorescence has been also observed in cells incubated at different temperatures, based on which the ratiometric intracellular temperature sensor has been prepared (Fig. 2d).

Kavitha et al.<sup>114</sup> have prepared a thermometer for sensing intracellular temperatures by a fluorescent thermo-responsive polymer consisting of poly(N-vinylcaprolactam) (PVCL) coupled with CDs (PVCL-CDs). Figure 2e shows the grey-scale intensity of the fluorescence microscopy images of NIH 3T3 cells incubated in PVCL-CDs solution for 24 h obviously decreases as temperature increases. Therefore, the biocompatible PVCL-CDs could be used as an intracellular thermometer.

*Intracellular metal ions sensors.*—Metal ions are required for all cells by serving as essential structural cofactor, redox centers and oxygen porter of chemical and biological reactions in intracellular or



**Figure 1.** (a) The synthesis and functionalization procedure of multifunctional nanocarrier based on multi-walled carbon nanotubes (MWCNT) (up); The bright field image of HeLa cells incubated with multi-walled carbon nanotubes for (A) 2 h, (C) 6 h, (E) 24 h. The SERS mapping image of the ratio of the SERS intensity at 1390 cm<sup>-1</sup> and 1183 cm<sup>-1</sup>, (B) 2 h, (D) 6 h, (F) 24 h (down).<sup>102</sup> Reproduced with permission Copyright 2015, Elsevier B.V. (b) Illustration of physical adsorption between IFO and pristine graphene oxide (Left) or herring sperm DNA-treated graphene oxide (Right) under acidic conditions; Fluorescence images (scale bar = 25  $\mu$ m) of MCF-7, MDA-MB-231, and A549 cells probed by the graphene oxide-cDNA/IFO nanosystem with herring sperm DNA passivation at pH 5.0 and 7.3.<sup>85</sup> Reproduced with permission Copyright 2017, American Chemical Society. (c) Schematic illustrations for the synthesis process of N-CNs and pH-responsive.<sup>103</sup> Reproduced with permission Copyright 2016, Elsevier B.V. (d) Schematic representation of CDs preparation and lysosomal pH monitoring.<sup>104</sup> Reproduced with permission Copyright 2018, The Royal Society of Chemistry.

subcellular regions.<sup>115–117</sup> Therefore, there is great interest in accurate monitoring of the distribution of intracellular metal ions to study the cell biology of metals.<sup>118–121</sup> As nanomaterials, carbon nanomaterials have been widely studied for determination metal ions and possessed promising potential in metal ion sensor. Much research effort has been devoted to develop intracellular metal ions sensors for understanding physiological or pathological functions of metal ions in living cells. In recent years, carbon nanomaterials were used to probe various types of metal ions, such as Fe<sup>3+</sup>, Ag<sup>+</sup>, Cu<sup>2+</sup>, Al<sup>3+</sup>, Zn<sup>2+</sup>, Pb<sup>2+</sup>, Hg<sup>2+</sup> and Cr<sup>3+,122–126</sup> Cao et al.<sup>127</sup> have successfully prepared an intracellular Ag<sup>+</sup>

Cao et al.<sup>127</sup> have successfully prepared an intracellular Ag<sup>+</sup> sensor based on acetaldehyde-modified  $g-C_3N_4$  ultrathin nanosheets (ACNNSs). The ACNNSs are low cytotoxicity and good biocompatibility. HeLa cells after incubating with ACNNSs for 6 h show bright blue fluorescence, whereas negligible fluorescence in Hela cells with ACNNSs is observed followed by incubating with Ag<sup>+</sup> for 2 h. The above results proved that ACNNSs can react with intracellular Ag<sup>+</sup>, therefore intracellular Ag<sup>+</sup> sensor has been established (Fig. 3a).

Zou et al.<sup>128</sup> have proposed an intracellular Cu<sup>2+</sup> ratiometric nanosensor based on a satellite hybrid nanoprobe composed by CdTe/CdS quantum dots capped around the silica microsphere and blue-emitting CDs. Intracellular Cu<sup>2+</sup> could quench the CdTe/CdS quantum dots emission (at 650 nm) effectively but have no ability for reduction of the CDs emission (at 425 nm). The variation of intracellular Cu<sup>2+</sup> concentration is in accordance with linearly with decrease of the F<sub>650</sub>/F<sub>425</sub> ratio, and satellite hybrid nanoprobe is utilized to the ratiometric fluorescence sensing for Cu<sup>2+</sup> in HeLa cells (Fig. 3b).

cells (Fig. 3b). Shi et al.<sup>129</sup> have developed an intracellular Fe<sup>3+</sup> nanosensor based on multi heteroatoms (nitrogen and phosphorus) co-doped carbon nanodots (N, P-CDs). The N, P-CDs could enter into intracellular region with high cell viability. Consequently, the usefulness of N, P-CDs in sensing intracellular Fe<sup>3+</sup> are demonstrated by confocal fluorescence images. Experimental results prove that the fluorescence brightness of cells became weaker as  $Fe^{3+}$  into cells treated with N, P-CDs. All observations indicate that the proposed N, P-CDs could be used to effectively semiquantitative sensing  $Fe^{3+}$  in live cells (Fig. 3c).

Xiong et al.<sup>130</sup> have developed an intracellular  $Pb^{2+}$  sensor via electrochemiluminescence method using N doped CDs (N-CDs) in situ electro-polymerized onto a glassy carbon electrode (GCE) as luminophores, and Pd-Au hexoctahedrons (Pd@Au HOHs) as enhancers (Fig. 3d). Yan et al.<sup>131</sup> have described an intracellular Hg<sup>2+</sup> sensor using photoluminescent CDs (Fig. 3e).

Intracellular biomolecule sensors.—Intracellular biomolecules, including biomacromolecules (e.g., proteins, nucleic acids and polysaccharides) and small biomolecules (e.g., cysteines, cholesterols, glutathione and ascorbic acids), are crucial for cell metabolic processes. Intracellular bioenzyme, as one kind of proteins or ribonucleic acids (RNA), ensures biological reactions and chemical reactions in living cells perform efficiently and specifically.<sup>132</sup> Intracellular nucleic acids, including deoxyribonucleic acids (DNA) or RNA, exist in all cells and create, encode, store, transmit and express information inside/outside the cells.133 Some small biomolecules, such as cysteines, play considerable roles in peptide and protein synthesis, and some small biomolecules, such as ascorbic acid, are basic vitamins for biological systems and participate in amino acid metabolism, collagen formation and ion absorption.<sup>134,135</sup> Despite the necessity and importance of biomolecules for intracellular life processes, rapid and accurate determination of intracellular biomolecules is essential. Up to now, several approaches based on carbon nanomaterials have been explored for determination of intracellular biomolecules, such as based on carbon nanospheres, CDs, g-C<sub>3</sub>N<sub>4</sub>, graphene, graphene oxide.<sup>136,13</sup>

Wang et al.<sup>138</sup> have constructed an intracellular telomerase sensor based a single patchy gold/carbon nanosphere (PG/CNS). The surface of the PG/CNS is decorated with hybridized-DNA (HS-



**Figure 2.** (a) Schematic representation of graphene quantum dots (mGQDs) preparation and live intracellular temperature sensing using graphene quantum dots in L929 cells.<sup>58</sup> Reproduced with permission Copyright 2017, American Chemical Society. (b) (a)–(c) Confocal microscopy images of HeLa cells (at 25 °C); (d)–(f) Confocal microscopy images of N, S co-doped CDs-stained cells with corresponding fluorescence field at 25, 35 and 25 °C, respectively. (Emission was collected at 415–550 nm and excited at 405 nm.)<sup>111</sup> Reproduced with permission Copyright 2017, The Royal Society of Chemistry. (c) Fluorescent microscopic images of HeLa cells stained with CDs-RhB at 5 (a) and 37 °C (b) respectively; From left to right: the red, blue channel fluorescence images and the red/blue ratio image respectively.<sup>112</sup> Reproduced with permission Copyright 2017, The Royal Society of Chemistry. (d) Fluorescence microscopy images of CD-treated HeLa cells incubated at the different temperatures; The scale bars: 10  $\mu$ m; The red-to-blue fluorescence ratios are 1.8 at 32 °C, 2.0 at 37 °C and 2.3 at 42 °C; The control shows untreated HeLa cells at 42 °C with no fluorescence signal as expected.<sup>113</sup> Reproduced with permission Copyright 2017, The Royal Society of Chemistry (e) Fluorescence microscopy images of the NIH 3T3 cells incubated awith the PVCL-CDs during (a) heating and (b) cooling at (i) 25, (ii) 30, (iii) 35, (iv) 40, and (v) 45 °C; (c) Grey-scale intensity of the images of the circled area during heating as a function of temperature.<sup>114</sup> Reproduced with permission Copyright 2015, Elsevier B.V.

DNA/Primer-DNA/Flare-DNA) via Au-S bond and H1/H2-DNA (a pair of cross complementary DNA hairpins) via electrostatic interaction. In the presence of telomerase, the primer-DNA (telomerase primer) is released from the surface PG/CNS, and which initiates cross hybridization chain reaction (HCR) with H1-DNA and H2-DNA resulting in amplifying the fluorescence signal (Fig. 4a). Li et al.<sup>139</sup> have developed an intracellular protein kinase A sensor based on  $g-C_3N_4$  and titanium dioxide (TiO<sub>2</sub>) complex via a novel photoelectrochemical (PEC) assay. The protein kinase A (PKA) can catalyze phosphorylation reaction in solution to obtain phosphorylated peptide (P-peptide). The P-peptide is immobilized on electrode surface which was modified with g-C<sub>3</sub>N<sub>4</sub> and TiO<sub>2</sub> in advance for providing PEC signal and conjugating phosphate groups of P-peptide, respectively. Subsequently, PAMAM dendrimers are captured on the P-peptide to immobilize Alkaline Phosphatase (ALP) which can catalyze L-ascorbic acid 2phosphate trisodium salt (AAP) to produce electron donor of ascorbic acid (AA), resulting in an increased photocurrent (Fig. 4b).

There also exists some intracellular small biomolecule sensor. Liu et al.<sup>140</sup> have reported an intracellular adenosine triphosphate (ATP) sensor based on fluorescent aptamer probes covalently linked to graphene oxide (Fig. 4c). Zhang et al.<sup>83</sup> have established an intracellular glutathione sensor based on magnetic nanoporous graphene nanocomposites synthesized by graphene oxide and ferric chloride. In cells, the oxidation of glutathione and thiamine are competitive, and a novel and simple intracellular glutathione sensor are established on the basis of the inhibition effect of glutathione on the oxidation of thiamine (Fig. 4d). Liu et al.<sup>141</sup> have prepared an intracellular microRNA-21 based on lysozyme-modified gold nanoclusters modified with the ss-DNA probe (a 22-mer) for microRNA-21and carbon nanotubes. There exists a fluorescence resonance energy transfer between gold nanoclusters and carbon nanotubes. However, after addition of microRNA-21, the fluorescence resonance energy transfer between gold nanoclusters and carbon nanotubes is blocked because of combination of ss-DNA and microRNA-21 (Fig. 4e). Liu et al.<sup>142</sup> have prepared an intracellular H<sub>2</sub>O2 sensor based on porous graphene network (Fig. 4f).

Intracellular gaseous signaling molecules including carbon monoxide (CO), hydrogen sulfide (H<sub>2</sub>S) and nitric oxide (NO) generate in biological reactions in living cells with complex interrelationships and are of great significance in many biological processes.<sup>143–145</sup> Unusual concentrations of CO, H<sub>2</sub>S and NO are associated with some diseases, such as asthma, sickle cell anemia, diabetes,<sup>143</sup> a variety of neurodegenerative pathologies,<sup>144</sup> Huntington's, Parkinson's and Alzheimer's13 diseases.<sup>146</sup> From these perspectives, it is worthy to develop sensitive, specific and fast techniques for these intracellular gaseous signaling molecules detection. Recent studies have focused on intracellular gaseous signaling molecules sensor based on carbon nanomaterials.

Li et al.<sup>147</sup> have developed an intracellular  $H_2S$  sensor based on (2,4-dinitrophenoxy) tyrosine functionalized graphene quantum dots via fluorescent techniques to detect  $H_2S$  in MCF-7 cells. Ulissi et al.<sup>148</sup> have constructed an intracellular NO sensor based on



**Figure 3.** (a) General scheme for the preparation of ACNNSs from graphitic carbon nitride (BCN) and their application in sensing Ag<sup>+</sup> (up); Fluorescence images of cells: (a) control cells treated with no ACNNSs or Ag<sup>+</sup> and (b) control cells treated with 100  $\mu$ l ACNNSs for 6 h only; (c) contrast and (d) fluorescence images of cells treated with both 100  $\mu$ l ACNNSs and 2.0 ml Ag<sup>+</sup> (20  $\mu$ M) for 2 h (down).<sup>127</sup> Reproduced with permission Copyright 2018, American Chemical Society. (b) scheme of carbon-dot and quantum-dot-coated dual-emission core-satellite silica nanoparticles for ratiometric intracellular Cu<sup>2+</sup> sensing.<sup>128</sup> Reproduced with permission Copyright 2016, American Chemical Society. (c) Synthesis of N, P-CDs and Fe<sup>3+</sup> detection in human herum and living cells.<sup>129</sup> Reproduced with permission Copyright 2016, American Chemical Society. (d) The fabrication and reaction mechanism of the proposed electrochemiluminescence (ECL) biosensor for the detection of intracellular lead ions.<sup>130</sup> Reproduced with permission Copyright 2016, The Royal Society of Chemistry. (e) Schematic illustration for the synthesis of CDs and their applications in the determination and intracellular imaging Hg(II).<sup>131</sup> Reproduced with permission Copyright 2016, Springer-Verlag Wien.



**Figure 4.** (a) Schematic diagram of the preparation process of PG/CNS-based sensor. (B) Schematic illustration of PG/CNS-based mimic-HCR sensor for in situ detection of intracellular telomerase.<sup>138</sup> Reproduced with permission Copyright 2019, Elsevier B.V. (b) Schematic representation of the fabricated PEC biosensor for assay of PKA activity based on PKA-Catalyzed phosphorylation reaction in solution and signal amplification of TiO<sub>2</sub>/g-C<sub>3</sub>N<sub>4</sub>, PAMAM-COOH, and ALP.<sup>139</sup> Reproduced with permission Copyright 2017, American Chemical Society. (c) Schematic diagram of intracellular detection of ATP using an aptamer beacon covalently linked to graphene oxide resisting nonspecific probe displacement.<sup>140</sup> Reproduced with permission Copyright 2014, American Chemical Society. (d) Schematic diagram of discriminative detection of glutathione in cell lysates based on oxidase-like activity of magnetic nanoporous graphene.<sup>83</sup> Reproduced with permission Copyright 2019, American Chemical Society. (e) Schematic presentation of the FRET fluorescent assay for microRNA-21 analysis.<sup>141</sup> Reproduced with permission Copyright 2019, Springer-Verlag GmbH Austria, part of Springer Nature. (f) Schematic of horseradish peroxidase/ porous graphene (HRP/PGN) modified glassy carbon electrode (GCE) used for detecting H<sub>2</sub>O<sub>2</sub> release from cells stimulated with ascorbic acid (AA).<sup>142</sup> Reproduced with permission Copyright 2016, Elsevier B.V.

near-infrared fluorescent intracellular single-walled carbon nanotubes to determine NO in A375 melanoma cells.

#### Carbon Nanomaterials Based Intracellular Sensors for Diagnosis or Treatment of Diseases

The early diagnosis of diseases, especially various types of cancers, plays a critical role in clinical treatment. As already discussed above, abnormal intracellular microenvironmental parameters and inappropriate concentrations of molecules or ions are intuitional indicators for various types of diseases. Therefore, intracellular sensors have become essential tools in achieving diagnosis and treatment of diseases. Until now, diseases diagnosed and/or treated by carbon nanomaterials based intracellular sensor include cancers (e.g., cervical cancer, live cancer, breast cancer, bladder cancer),<sup>127,129,149,150</sup> disease caused by pathogenic bacteria,<sup>151</sup> and neurological disease.<sup>152,153</sup> For examples, Shu et al.<sup>149</sup> have prepared intracellular metal ions sensors based on CDs to diagnose breast cancer. Mohapatra et al.<sup>150</sup> have established intracellular ions sensors based on  $Fe_3O_4@SiO_2@carbon quantum dot to diagnose colon cancer. Shi et al.<sup>129</sup> have established$ intracellular metal ions based on nitrogen and phosphorus codoped CDs to diagnosed bladder cancer. Cao et al.<sup>127</sup> have successfully prepared intracellular thermal sensor based on  $g-C_3N_4$  to diagnosed cervical cancer. These works may pave a new possible way to rapid screening and accurate treatment of these intractable diseases.

#### **Conclusions and Outlooks**

In summary, this paper provides a brief overview of recent researches on the applications of carbon nanomaterials, including CDs or graphene quantum dots, carbon nanotubes, graphene or graphene oxide,  $g-C_3N_4$  and fullerene, in pH sensing, thermal sensing, metal ion sensing and biomolecule sensing in living cells. Though many achievements have been obtained for intracellular sensors based on carbon nanomaterials, there are still significant challenges that need to be solved.

- CDs are the main materials in the application of fabricating intracellular sensors. Therefore, other carbon nanomaterials (such as, carbon nanotubes, graphene or graphene oxide, g-C3N4 and fullerene) should be further exploited in intracellular sensors urgently.
- (2) During the use of intracellular sensor, confocal fluorescence microscopic technique and electrochemistry methods are more commonly used. Thus, other advanced techniques (such as, Raman spectroscopy method) should be tried.
- (3) Some given analytes or microenvironments in intracellular organelles (e.g., cytoplasm, mitochondria and lysosomes) are also important in measurement of the cells status. Therefore, we must focus on the detection of analytes or parameters of microenvironments in cell organelles in future.

#### Acknowledgments

This work was supported by National Key Research and Development Program of China (2017YFA0205300), the National Natural Science Foundation of China (21675023 and 91753106).

#### References

- B. Bayatsarmadi, Y. Zheng, A. Vasileff, and S. Z. Qiao, "Recent advances in atomic metal doping of carbon-based nanomaterials for energy conversion." *Small*, 13, 1700191 (2017).
- J. F. Ni and Y. Li, "Carbon nanomaterials in different dimensions for electrochemical energy storage." *Adv. Energy Mater.*, 6, 1600278 (2016).
   K. Bhattacharya, S. P. Mukherjee, A. Gallud, S. C. Burkert, S. Bistarelli,
- K. Bhattacharya, S. P. Mukherjee, A. Gallud, S. C. Burkert, S. Bistarelli, S. Bellucci, M. Bottini, A. Star, and B. Fadeel, "Biological interactions of carbon-based nanomaterials: from coronation to degradation." *Nanomed.-Nanotechnol. Biol. Med.*, **12**, 333 (2016).

- J. N. Tiwari, V. Vij, K. C. Kemp, and K. S. Kim, "Engineered carbonnanomaterial-based electrochemical sensors for biomolecules." ACS Nano, 10, 46 (2016).
- W. Z. Zhai, N. Srikanth, L. B. Kong, and K. Zhou, "Carbon nanomaterials in tribology." *Carbon*, 119, 150 (2017).
- S. W. Lee, W. Lee, Y. Hong, G. Lee, and D. S. Yoon, "Recent advances in carbon material-based NO<sub>2</sub> gas sensors." *Sens. Actuator B-Chem.*, 255, 1788 (2018).
   G. P. Evans, M. J. Powell, I. D. Johnson, D. P. Howard, D. Bauer, J. A. Darr, and
- G. P. Evans, M. J. Powell, I. D. Johnson, D. P. Howard, D. Bauer, J. A. Darr, and I. P. Parkin, "Room temperature vanadium dioxide-carbon nanotube gas sensors made via continuous hydrothermal flow synthesis." *Sens. Actuator B-Chem.*, 255, 1119 (2018).
- G. P. Evans, D. J. Buckley, A. L. Adedigba, G. Sankar, N. T. Skipper, and I. P. Parkin, "Controlling the cross-sensitivity of carbon nanotube-based gas sensors to water using zeolites." *ACS Appl. Mater. Interfaces*, 8, 28096 (2016).
- P. Bindra and A. Hazra, "Capacitive gas and vapor sensors using nanomaterials." J. Mater. Sci.-Mater. Electron., 29, 6129 (2018).
- J. Casanova-Chafer, E. Navarrete, X. Noirfalise, P. Umek, C. Bittencourt, and E. Llobet, "Gas sensing with iridium oxide nanoparticle decorated carbon nanotubes." *Sensors*, **19**, 113 (2019).
- J. Koo, H. Bae, L. Kang, B. Huang, and H. Lee, "Calcium-decorated carbon nanostructures for the selective capture of carbon dioxide." *Phys. Chem. Chem. Phys.*, 18, 29086 (2016).
- D. J. Babu, M. Bruns, R. Schneider, D. Gerthsen, and J. J. Schneider, "Understanding the influence of N-doping on the CO<sub>2</sub> adsorption characteristics in carbon nanomaterials." *J. Phys. Chem. C*, **121**, 616 (2017).
- Y. B. Yang, X. D. Yang, Y. J. Yang, and Q. Yuan, "Aptamer-functionalized carbon nanomaterials electrochemical sensors for detecting cancer relevant biomolecules." *Carbon*, **129**, 380 (2018).
- J. Li, H. F. Hu, H. Y. Li, and C. B. Yao, "Recent developments in electrochemical sensors based on nanomaterials for determining glucose and its byproduct H<sub>2</sub>O<sub>2</sub>." *J. Mater. Sci.*, 52, 10455 (2017).
- P. Yanez-Sedeno, A. Gonzalez-Cortes, L. Agui, and J. M. Pingarron, "Uncommon carbon nanostructures for the preparation of electrochemical immunosensors." *Electroanalysis*, 28, 1679 (2016).
- Y. N. Zhang, Q. Y. Niu, X. T. Gu, N. Yang, and G. H. Zhao, "Recent progress on carbon nanomaterials for the electrochemical detection and removal of environmental pollutants." *Nanoscale*, 11, 11992 (2019).
- M. A. Beluomini, J. L. da Silva, A. C. de Sa, E. Buffon, T. C. Pereira, and N. R. Stradiotto, "Electrochemical sensors based on molecularly imprinted polymer on nanostructured carbon materials: a review." *J. Electroanal. Chem.*, 840, 343 (2019).
- P. A. Rasheed and N. Sandhyarani, "Carbon nanostructures as immobilization platform for DNA: A review on current progress in electrochemical DNA sensors." *Biosens. Bioelectron.*, 97, 226 (2017).
- M. Thangamuthu, W. E. Gabriel, C. Santschi, and O. J. F. Martin, "Electrochemical sensor for bilirubin detection using screen printed electrodes functionalized with carbon nanotubes and graphene." *Sensors*, 18, 800 (2018).
- S. Campuzano, P. Yanez-Sedeno, and J. M. Pingarron, "Carbon dots and graphene quantum dots in electrochemical biosensing." *Nanomaterials*, 9, 634 (2019).
   M. Govindasamy, V. Mani, S. M. Chen, T. W. Chen, and A. K. Sundramoorthy,
- M. Govindasamy, V. Mani, S. M. Chen, T. W. Chen, and A. K. Sundramoorthy, "Methyl parathion detection in vegetables and fruits using silver@graphene nanoribbons nanocomposite modified screen printed electrode." *Sci. Rep.*, 7, 46471 (2017).
- M. Govindasamy, R. Umamaheswari, S. M. Chen, V. Mani, and C. Su, "Graphene oxide nanoribbons film modified screen-printed carbon electrode for real-time detection of methyl parathion in food samples." *J. Electrochem. Soc.*, 164, B403 (2017).
- 23. M. Govindasamy, S. M. Chen, V. Mani, R. Devasenathipathy, R. Umamaheswari, K. J. Santhanaraj, and A. Sathiyan, "Molybdenum disulfide nanosheets coated multiwalled carbon nanotubes composite for highly sensitive determination of chloramphenicol in food samples milk, honey and powdered milk." *J. Colloid Interface Sci.*, 485, 129 (2017).
- V. Mani, M. Govindasamy, S. M. Chen, R. Karthik, and S. T. Huang, "Determination of dopamine using a glassy carbon electrode modified with a graphene and carbon nanotube hybrid decorated with molybdenum disulfide flowers." *Microchim. Acta*, 183, 2267 (2016).
- M. Govindasamy, V. Mani, S. M. Chen, R. Karthik, K. Manibalan, and R. Umamaheswari, "MoS<sub>2</sub> flowers grown on graphene/carbon nanotubes: a versatile substrate for electrochemical determination of hydrogen peroxide." *Int. J. Electrochem. Sci.*, **11**, 2954 (2016).
- M. Govindasamy, S. Manavalan, S. M. Chen, U. Rajaji, T. W. Chen, F. M. A. Al-Hemaid, M. A. Ali, and M. S. Elshikh, "Determination of neurotransmitter in biological and drug samples using gold nanorods decorated f-MWCNTs modified electrode." *J. Electrochem. Soc.*, 165, B370 (2018).
- 27. M. Govindasamy, B. Subramanian, S. F. Wang, S. Chinnapaiyan, R. J. Ramalingam, and H. A. Al-lohedan, "Ultrasound-assisted synthesis of tungsten trioxide entrapped with graphene nanosheets for developing nanomolar electro-chemical (hormone) sensor and enhanced sensitivity of the catalytic performance." Ultrason. Sonochem., 56, 134 (2019).
- M. Govindasamy, S. F. Wang, R. Jothiramalingam, S. N. Ibrahim, and H. A. Allohedan, "A screen-printed electrode modified with tungsten disulfide nanosheets for nanomolar detection of the arsenic drug roxarsone." *Microchim. Acta*, 186, 420 (2019).
- G. Boopathy, M. Govindasamy, M. Nazari, S. F. Wang, and M. J. Umapathy, "Facile synthesis of tungsten carbide nanosheets for trace level detection of toxic

mercury ions in biological and contaminated sewage water samples: An electrocatalytic approach." J. Electrochem. Soc., 166, E761 (2019).

- U. Rajaji, M. Govindasamy, S. M. Chen, T. W. Chen, X. H. Liu, and S. Chinnapaiyan, "Microwave-assisted synthesis of Bi<sub>2</sub>WO<sub>6</sub> flowers decorated graphene nanoribbon composite for electrocatalytic sensing of hazardous dihydroxybenzene isomers." *Compos. Pt. B-Eng.*, **152**, 220 (2018).
- 31. A. Muthumariappan, M. Govindasamy, S. M. Chen, K. Sakthivel, V. Mani, T. W. Chen, and S. Selvaraj, "Determination of non-steroidal anti-inflammatory drug (NSAID) azathioprine in human blood serum and tablet samples using multi-walled carbon nanotubes (MWCNTs) decorated manganese oxide microcubes composite film modified electrode." *Int. J. Electrochem. Sci.*, **12**, 7446 (2017).
- K. Šakthivel, M. Govindasamy, S. M. Chen, A. Muthumariappan, V. Mani, T. W. Chen, and S. Selvaraj, "MWCNTs/MoS<sub>2</sub> decorated cobalt oxide polyhedrons composite film modified electrode for electrochemical determination of dopamine in rat brain and human blood serum samples." *Int. J. Electrochem. Sci.*, **12**, 7435 (2017).
- 33. M. Govindasamy, S. F. Wang, B. Subramanian, R. J. Ramalingam, H. Al-Lohedan, and A. Sathiyan, "A novel electrochemical sensor for determination of DNA damage biomarker (8-hydroxy-2'-deoxyguanosine) in urine using sono-chemically derived graphene oxide sheets covered zinc oxide flower modified electrode." *Ultrason. Sonochem.*, 58, 104622 (2019).
- 34. B. Sriram, M. Govindasamy, S. F. Wang, R. J. Ramalingam, H. Al-lohedan, and T. Maiyalagan, "Novel sonochemical synthesis of Fe<sub>3</sub>O<sub>4</sub> nanospheres decorated on highly active reduced graphene oxide nanosheets for high sensitive detection of uric acid in biological samples." *Ultrason. Sonochem.*, **58**, 104618 (2019).
- M. Govindasamy, S. F. Wang, W. C. Pan, B. Subramanian, R. J. Ramalingam, and H. Al-lohedan, "Facile sonochemical synthesis of perovskite-type SrTiO<sub>3</sub> nanocubes with reduced graphene oxide nanocatalyst for an enhanced electrochemical detection of α-amino acid (tryptophan)." Ultrason. Sonochem., 56, 193 (2019).
- 36. V. Mani, M. Govindasamy, S. M. Chen, T. W. Chen, A. S. Kumar, and S. T. Huang, "Core-shell heterostructured multiwalled carbon nanotubes@reduced graphene oxide nanoribbons/chitosan, a robust nanobiocomposite for enzymatic biosensing of hydrogen peroxide and nitrite." *Sci. Rep.*, 7, 11910 (2017).
- M. Govindasamy, S. F. Wang, S. Kumaravel, R. J. Ramalingam, and H. A. Allohedan, "Facile synthesis of copper sulfide decorated reduced graphene oxide nanocomposite for high sensitive detection of toxic antibiotic in milk." *Ultrason. Sonochem.*, 52, 382 (2019).
- Z. Wang and Z. J. Pan, "Flexible strain sensors fabricated using carbon-based nanomaterials: a review." *Curr. Opin. Solid State Mat. Sci.*, 22, 213 (2018).
- J. Z. Liu, Z. H. Liu, M. Li, Y. Zhao, G. C. Shan, M. J. Hu, and D. Z. Zheng, "Polydimethylsiloxane nanocomposite filled with 3D carbon nanosheet frameworks for tensile and compressive strain sensors." *Compos. Pt. B-Eng.*, 168, 175 (2019).
- T. Lee, W. Lee, S. W. Kim, J. J. Kim, and B. S. Kim, "Flexible textile strain wireless sensor functionalized with hybrid carbon nanomaterials supported ZnO nanowires with controlled aspect ratio." *Adv. Funct. Mater.*, 26, 6206 (2016).
- S. H. Min, G. Y. Lee, and S. H. Ahn, "Direct printing of highly sensitive, stretchable, and durable strain sensor based on silver nanoparticles/multi-walled carbon nanotubes composites." *Compos. Pt. B-Eng.*, 161, 395 (2019).
- Z. Pei, Y. Liu, Q. Zhang, D. Zhao, J. Wang, Z. Y. Yuan, W. D. Zhang, and S. B. Sang, "Highly sensitive, stretchable strain sensor based on Ag@COOH-functionalized CNTs for stroke and pronunciation recognition." *Adv. Electron. Mater.*, 5, 1900227 (2019).
- S. Jang, J. Kim, D. W. Kim, J. W. Kim, S. Chun, H. J. Lee, G. R. Yi, and C. Pang, "Carbon-based, ultraelastic, hierarchically coated fiber strain sensors with crackcontrollable beads." ACS Appl. Mater. Interfaces, 11, 15079 (2019).
- 44. K. Sun, H. Ko, H. H. Park, M. Seong, S. H. Lee, H. Yi, H. W. Park, T. I. Kim, C. Pang, and H. E. Jeong, "Hybrid architectures of heterogeneous carbon nanotube composite microstructures enable multiaxial strain perception with high sensitivity and ultrabroad sensing range." *Small*, **15**, 1900161 (2019).
- B. B. Chen, Z. X. Liu, H. Y. Zou, and C. Z. Huang, "Highly selective detection of 2,4,6-trinitrophenol by using newly developed terbium-doped blue carbon dots." *Analyst*, 9, 2676 (2016).
- T. Das, B. K. Saikia, H. P. Dekaboruah, M. Bordoloi, D. Neog, J. J. Bora, J. Lahkar, B. Narzary, S. Roy, and D. Ramaiah, "Blue-fluorescent and biocompatible carbon dots derived from abundant low-quality coals." *J. Photochem. Photobiol. B-Biol.*, **195**, 1 (2019).
- J. F. Shangguan, D. G. He, X. X. He, K. M. Wang, F. Z. Xu, J. Q. Liu, J. L. Tang, X. Yang, and J. Huang, "Label-free carbon-dots-based ratiometric fluorescence pH nanoprobes for intracellular pH sensing." *Anal. Chem.*, 88, 7837 (2016).
- A. Safavi, R. Ahmadi, Z. Mohammadpour, and J. Zhou, "Fluorescent pH nanosensor based on carbon nanodots for monitoring minor intracellular pH changes." *RSC Adv.*, 6, 104657 (2016).
- S. Kalytchuk, K. Polakova, Y. Wang, J. P. Froning, K. Cepe, A. L. Rogach, and R. Zboril, "Carbon dot nanothermometry: intracellular photoluminescence lifetime thermal sensing." *ACS Nano*, **11**, 1432 (2017).
- H. Y. Liu, L. Y. Weng, and C. Yang, "A review on nanomaterial-based electrochemical sensors for H<sub>2</sub>O<sub>2</sub>, H<sub>2</sub>S and NO inside cells or released by cells." *Microchim. Acta*, 184, 1267 (2017).
- V. Sharma, A. K. Saini, and S. M. Mobin, "Multicolour fluorescent carbon nanoparticle probes for live cell imaging and dual palladium and mercury sensors." *J. Mat. Chem. B*, 4, 2466 (2016).
- W. Li, R. Liu, Y. L. Wang, Y. L. Zhao, and X. Y. Gao, "Temporal techniques: dynamic tracking of nanomaterials in live cells." *Small*, 9, 1585 (2013).
- H. Y. Liu, L. N. Zhang, M. Yan, and J. H. Yu, "Carbon nanostructures in biology and medicine." J. Mat. Chem. B, 5, 6437 (2017).

- A. L. Barabasi and Z. N. Oltvai, "Network biology: understanding the cell's functional organization." *Nat. Rev. Genet.*, 5, 101 (2004).
- M. Brownlee, "Biochemistry and molecular cell biology of diabetic complications." *Nature*, 414, 813 (2001).
- J. R. Casey, S. Grinstein, and J. Orlowski, "Sensors and regulators of intracellular pH." *Nat. Rev. Mol. Cell Biol.*, **11**, 50 (2010).
- Z. S. Ge and S. Y. Liu, "Functional block copolymer assemblies responsive to tumor and intracellular microenvironments for site-specific drug delivery and enhanced imaging performance." *Chem. Soc. Rev.*, 42, 7289 (2013).
- M. K. Kumawat, M. Thakur, R. B. Gurung, and R. Srivastava, "Graphene quantum dots from mangifera indica: application in near infrared bioimaging and intracellular nanothermometry." ACS Sustain. Chem. Eng., 5, 1382 (2017).
- L. G. Xu, S. Zhao, W. Ma, X. L. Wu, S. Li, H. Kuang, L. B. Wang, and C. L. Xu, "Multigaps embedded nanoassemblies enhance in situ raman spectroscopy for intracellular telomerase activity sensing." *Adv. Funct. Mater.*, 26, 1602 (2016).
- Z. J. Chen, K. Y. Zhang, X. Tong, Y. H. Liu, C. Y. Hu, S. J. Liu, Q. Yu, Q. Zhao, and W. Huang, "Phosphorescent polymeric thermometers for in vitro and in vivo temperature sensing with minimized background interference." *Adv. Funct. Mater.*, 26, 4386 (2016).
- D. Lee, K. M. K. Swamy, J. Hong, S. Lee, and J. Yoon, "A rhodamine-based fluorescent probe for the detection of lysosomal pH changes in living cells." *Sens. Actuator B-Chem.*, 266, 416 (2018).
- ACHIAIOP De Chem, 200, 410 (2013).
  P. W. Gong, L. Sun, F. Wang, X. C. Liu, Z. Q. Yan, M. Z. Wang, L. Zhang, Z. Z. Tian, Z. Liu, and J. M. You, "Highly fluorescent N-doped carbon dots with two-photon emission for ultrasensitive detection of tumor marker and visual monitor anticancer drug loading and delivery." *Chem. Eng. J.*, 356, 994 (2019).
- Y. X. Wang, M. Myers, and J. A. Staser, "Electrochemical UV sensor using carbon quantum dot/graphene semiconductor." *J. Electrochem. Soc.*, 165, H3001 (2018).
- M. L. Yola and N. Atar, "A highly efficient nanomaterial with molecular imprinting polymer: carbon nitride nanotubes decorated with graphene quantum dots for sensitive electrochemical determination of chlorpyrifos." *J. Electrochem. Soc.*, 164, B223 (2017).
- J. J. Du, N. Xu, J. L. Fan, W. Sun, and X. J. Peng, "Carbon dots: applications in bioimaging and theranostics." *Small*, 15, 1805087 (2019).
- 66. D. M. Morales, M. A. Kazakova, S. Dieckhofer, A. G. Selyutin, G. V. Golubtsov, W. Schuhmann, and J. Masa, "Trimetallic Mn–Fe–Ni oxide nanoparticles supported on multi-walled carbon nanotubes as high-performance bifunctional ORR/OER electrocatalyst in alkaline media." *Adv. Funct. Mater.*, 1905992 (2019).
- X. H. He, D. M. Li, Z. Y. Bai, F. F. Chang, J. L. Qiao, and L. Yang, "Multi-wall carbon nanotube-supported palladium-cobalt oxide nanoparticle as efficient catalyst for oxygen reduction reaction." *Ionics*, 25, 5929 (2019).
- X. W. Li, J. D. Wei, Y. Z. Chai, and S. Zhang, "Carbon nanotubes/tin oxide nanocomposite-supported Pt catalysts for methanol electro-oxidation." *J. Colloid Interface Sci.*, 450, 74 (2015).
- 69. A. Sharma, S. Gudala, S. R. Ambati, S. Penta, S. P. Mahapatra, R. R. Vedula, S. Pola, and B. Acharya, "Synthesis of heterocyclic compounds catalyzed by metal/metal oxide-multiwall carbon nanotube nanocomposites." *J. Chin. Chem. Soc.*, 64, 589 (2017).
- X. Y. Lu, H. M. Chan, C. L. Sun, C. M. Tseng, and C. Zhao, "Interconnected core-shell carbon nanotube-graphene nanoribbon scaffolds for anchoring cobalt oxides as bifunctional electrocatalysts for oxygen evolution and reduction." *J. Mater. Chem. A*, **3**, 13371 (2015).
- M. Zheng, J. H. Huo, Y. G. Tu, J. H. Wu, L. H. Hu, and S. Y. Dai, "Flowerlike molybdenum sulfide/multi-walled carbon nanotube hybrid as Pt-free counter electrode used in dye-sensitized solar cells." *Electrochim. Acta*, **173**, 252 (2015).
- E. Aslan, I. Akin, and I. H. Patir, "Highly active cobalt sulfide/carbon nanotube catalyst for hydrogen evolution at soft interfaces." *Chem.-Eur. J.*, 22, 5342 (2016).
- R. Y. A. Hassan and U. Wollenberger, "Direct determination of bacterial cell viability using carbon nanotubes modified screen-printed electrodes." *Electroanalysis*, 31, 1112 (2019).
- J. Bai, C. H. Sun, and X. E. Jiang, "Carbon dots-decorated multiwalled carbon nanotubes nanocomposites as a high-performance electrochemical sensor for detection of H<sub>2</sub>O<sub>2</sub> in living cells," *Anal. Bioanal. Chem.*, **408**, 4705 (2016).
- L. Camilli and M. Passacantando, "Advances on sensors based on carbon nanotubes." *Chemosensors*, 6, 62 (2018).
- H. Kalil, S. Maher, T. Bose, and M. Bayachou, "Manganese oxide/heminfunctionalized graphene as a platform for peroxynitrite sensing." *J. Electrochem. Soc.*, 165, G3133 (2018).
- X. Yang, X. H. Niu, Z. L. Mo, J. Wang, C. Shuai, Z. Pan, Z. Y. Liu, N. J. Liu, and R. B. Guo, "3D nitrogen and sulfur Co -doped graphene/integrated polysaccharides for electrochemical recognition tryptophan enantiomers." *J. Electrochem. Soc.*, 166, B1053 (2019).
- B. Cardenas-Benitez, I. Djordjevic, S. Hosseini, M. J. Madou, and S. O. Martinez-Chapa, "Review-covalent functionalization of carbon nanomaterials for biosensor applications: an update." *J. Electrochem. Soc.*, 165, B103 (2018).
- A. Khalifa, H. El-Desoky, and M. Abdel-Galeil, "Graphene-based sensor for voltammetric quantification of dapoxetine hydrochloride: a drug for premature ejaculation in formulation and human plasma." *J. Electrochem. Soc.*, 165, H128 (2018).
- P. Bollella, G. Fusco, C. Tortolini, G. Sanzo, G. Favero, L. Gorton, and R. Antiochia, "Beyond graphene: Electrochemical sensors and biosensors for biomarkers detection." *Biosens. Bioelectron.*, 89, 152 (2017).
- P. Zheng and N. Q. Wu, "Fluorescence and sensing applications of graphene oxide and graphene quantum dots: a review." *Chem.-Asian J.*, 12, 2343 (2017).

- H. Beitollahi, M. Safaei, and S. Tajik, "Application of graphene and graphene oxide for modification of electrochemical sensors and biosensors: a review." *Int. J. Nano Dimens*, **10**, 125 (2019).
- H. J. Zhang, J. Chen, Y. L. Yang, L. Wang, Z. Li, and H. D. Qiu, "Discriminative detection of glutathione in cell lysates based on oxidase-like activity of magnetic nanoporous graphene." *Anal. Chem.*, **91**, 5004 (2019).
- 84. H. C. Chang, X. M. Wang, K. K. Shiu, Y. L. Zhu, J. L. Wang, Q. W. Li, B. A. Chen, and H. Jiang, "Layer-by-layer assembly of graphene, Au and poly (toluidine blue O) films sensor for evaluation of oxidative stress of tumor cells elicited by hydrogen peroxide." *Biosens. Bioelectron.*, **41**, 789 (2013).
- C. Shao, J. Liang, S. H. He, T. Q. Luan, J. T. Yu, H. R. Zhao, J. Y. Xu, and L. L. Tian, "pH-responsive graphene oxide-DNA nanosystem for live cell imaging and detection." *Anal. Chem.*, 87, 5445 (2017).
- B. Muthuraj, S. Mukherjee, S. R. Chowdhury, C. R. Patra, and P. K. Iyer, "An efficient strategy to assemble water soluble histidine-perylene diimide and graphene oxide for the detection of PPi in physiological conditions and in vitro "Biosens. Bioelectron., 89, 636 (2017).
- N. Zou, X. Y. Wei, Z. M. Zong, X. Li, Z. X. Wang, and X. L. Wang, "A novel enzymatic biosensor for detection of intracellular hydrogen peroxide based on 1aminopyrene and reduced graphene oxides." *J. Chem. Sci.*, **131**, 28 (2019).
- Y. Q. Dong, Q. Wang, H. S. Wu, Y. M. Chen, C. H. Lu, Y. W. Chi, and H. H. Yang, "Graphitic carbon nitride materials: Sensing, imaging and therapy." *Small*, 12, 5376 (2016).
- M. H. Xiang, J. W. Liu, N. Li, H. Tang, R. Q. Yu, and J. H. Jiang, "A fluorescent graphitic carbon nitride nanosheet biosensor for highly sensitive, label-free detection of alkaline phosphatase." *Nanoscale*, 8, 4727 (2016).
- R. M. Mazhabi, L. Q. Ge, H. Jiang, and X. M. Wang, "A facile photoelectrochemical sensor for high sensitive ROS and AA detection based on graphitic carbon nitride nanosheets." *Biosens. Bioelectron.*, **107**, 54 (2018).
- P. Balasubramanian, T. S. T. Balamurugan, S. M. Chen, T. W. Chen, M. A. Ali, F. M. A. Al-Hemaid, and M. S. Elshikh, "An amperometric sensor for low level detection of antidepressant drug carbamazepine based on graphene oxide-g-C<sub>3</sub>N<sub>4</sub> composite film modified electrode." *J. Electrochem. Soc.*, **165**, B160 (2018).
- T. R. Kiran, N. Atar, and M. L. Yola, "A methyl parathion recognition method based on carbon nitride incorporated hexagonal boron nitride nanosheets composite including molecularly imprinted polymer." *J. Electrochem. Soc.*, 166, H495 (2019).
- P. A. Indeglia, A. T. Georgieva, V. B. Krishna, C. J. Martyniuk, and J. C. J. Bonzongo, "Toxicity of functionalized fullerene and fullerene synthesis chemicals." *Chemosphere*, **207**, 1 (2018).
- Q. Chen, Z. Ma, G. Liu, H. Wei, and X. Xie, "Antibacterial activity of cationic cyclen-functionalized fullerene derivatives: membrane stress." *Dig. J. Nanomater. Biostruct.*, **11**, 753 (2016).
- J. Srivastava, D. L. Barber, and M. P. Jacobson, "Intracellular pH sensors: design principles and functional significance." *Physiology*, 22, 30 (2007).
- S. Takahashi et al., "Development of a series of practical fluorescent chemical tools to measure pH values in living samples." J. Am. Chem. Soc., 140, 5925 (2018).
- E. Faggi, J. Serra-Vinardell, M. D. Pandey, J. Casas, G. Fabrias, S. V. Luis, and I. Alfonso, "Pseudopeptidic fluorescent on-off pH sensor based on pyrene excimer emission: imaging of acidic cellular organelles." *Sens. Actuator B-Chem.*, 2234, 633 (2016).
- M. Kanamala, W. R. Wilson, M. M. Yang, B. D. Palmer, and Z. M. Wu, "Mechanisms and biomaterials in pH-responsive tumour targeted drug delivery: a review." *Biomaterials*, 85, 152 (2016).
- H. Yang, Q. Wang, S. Huang, A. Xiao, F. Y. Li, L. Gan, and X. L. Yang, "Smart pH/redox dual-responsive nanogels for on-demand intracellular anticancer drug release." ACS Appl. Mater. Interfaces, 8, 7729 (2016).
- S. Granja, D. Tavares-Valente, O. Queiros, and F. Baltazar, "Value of pH regulators in the diagnosis, prognosis and treatment of cancer." *Semin. Cancer Biol.*, 43, 17 (2017).
- 101. T. F. Sergeeva, M. V. Shirmanova, O. A. Zlobovskaya, A. I. Gavrina, V. V. Dudenkova, M. M. Lukina, K. A. Lukyanov, and E. V. Zagaynova, "Relationship between intracellular pH, metabolic co-factors and caspase-3 activation in cancer cells during apoptosis." *Biochim. Biophys. Acta-Mol. Cell Res.*, **1864**, 604 (2017).
- 102. P. Chen, Z. Y. Wang, S. F. Zong, D. Zhu, H. Chen, Y. Z. Zhang, L. Wu, and Y. P. Cui, "pH-sensitive nanocarrier based on gold/silver core-shell nanoparticles decorated multi-walled carbon manotubes for tracing drug release in living cells." *Biosens. Bioelectron.*, **75**, 446 (2016).
- 103. B. F. Shi, Y. B. Su, L. L. Zhang, R. J. Liu, M. J. Huang, and S. L. Zhao, "Nitrogenrich functional groups carbon nanoparticles based fluorescent pH sensor with broad-range responding for environmental and live cells applications." *Biosens. Bioelectron.*, 82, 233 (2016).
- 104. Q. Q. Zhang, T. Yang, R. S. Li, H. Y. Zou, Y. F. Li, J. Guo, X. D. Liu, and C. Z. Huang, "A functional preservation strategy for the production of highly photoluminescent emerald carbon dots for lysosome targeting and lysosomal pH imaging." *Nanoscale*, **10**, 14705 (2018).
- J. Qiao, X. Y. Mu, and L. Qi, "Construction of fluorescent polymeric nanothermometers for intracellular temperature imaging: a review." *Biosens. Bioelectron.*, 85, 403 (2016).
- Z. Y. Ding, C. F. Wang, G. Feng, and X. J. Zhang, "Thermo-responsive fluorescent polymers with diverse LCSTs for ratiometric temperature sensing through FRET." *Polymers*, **10**, 283 (2018).
   K. Okabe, N. Inada, C. Gota, Y. Harada, T. Funatsu, and S. Uchiyama,
- 10/. K. Okabe, N. Inada, C. Gota, Y. Harada, T. Funatsu, and S. Uchiyama, "Intracellular temperature mapping with a fluorescent polymeric thermometer and fluorescence lifetime imaging microscopy." *Nat. Commun.*, **3**, 705 (2012).

- 108. C. Tapeinos et al., "Cell membrane—coated magnetic nanocubes with a homotypic targeting ability increase intracellular temperature due to ROS scavenging and act as a versatile theranostic system for glioblastoma multiforme." Adv. Healthc. Mater, 8, 1900612 (2019).
- S. W. Hong, D. Y. Kim, J. U. Lee, and W. H. Jo, "Synthesis of polymeric temperature sensor based on photophysical property of fullerene and thermal sensitivity of poly (n-isopropylacrylamide)." *Macromolecules*, 42, 2756 (2009).
- S. A. Binslem, M. R. Ahmad, and Z. Awang, "Intracellular thermal sensor for single cell analysis-short review." *Jurnal Teknologi*, **73**, 71 (2015).
- 111. W. L. Shi, F. Guo, M. M. Han, S. L. Yuan, W. S. Guan, H. Li, H. Huang, Y. Liu, and Z. H. Kang, "N, S co-doped carbon dots as a stable bio-imaging probe for detection of intracellular temperature and tetracycline." *J. Mat. Chem. B*, **5**, 3293 (2017).
- 112. L. Wei, Y. H. Ma, X. Y. Shi, Y. X. Wang, X. Su, C. Y. Yu, S. L. Xiang, L. H. Xiao, and B. Chen, "Living cell intracellular temperature imaging with biocompatible dye-conjugated carbon dots." *J. Mat. Chem. B*, **5**, 3383 (2017).
- J. R. Macairan, D. B. Jaunky, A. Piekny, and R. Naccache, "Intracellular ratiometric temperature sensing using fluorescent carbon dots." *Nanoscale Adv.*, 1, 105 (2019).
- 114. T. Kavitha, J. O. Kim, S. Jang, D. P. Kim, I. K. Kang, and S. Y. Park, "Multifaceted thermoresponsive poly(N-vinylcaprolactam) coupled with carbon dots for biomedical applications." *Mater. Sci. Eng. C-Mater. Biol. Appl.*, **61**, 492 (2016).
- 115. G. T. Sfrazzetto, C. Satriano, G. A. Tomaselli, and E. Rizzarelli, "Synthetic fluorescent probes to map metallostasis and intracellular fate of zinc and copper." *Coord. Chem. Rev.*, **311**, 125 (2016).
- D. W. Domaille, E. L. Que, and C. J. Chang, "Synthetic fluorescent sensors for studying the cell biology of metals." *Nat. Chem. Biol.*, 4, 507 (2008).
- L. A. Finney and T. V. O'Halloran, "Transition metal speciation in the cell: insights from the chemistry of metal ion receptors." *Science*, 300, 931 (2003).
- 118. L. N. Neupane, E. T. Oh, H. J. Park, and K. H. Lee, "Selective and sensitive detection of heavy metal ions in 100% aqueous solution and cells with a fluorescence chemosensor based on peptide using aggregation-induced emission." *Anal. Chem.*, 88, 3333 (2016).
- J. J. Zhang, F. F. Cheng, J. J. Li, J. Zhu, and Y. Lu, "Fluorescent nanoprobes for sensing and imaging of metal ions: recent advances and future perspectives." *Nano Today*, **11**, 309 (2016).
- 120. W. J. Wang, N. S. R. Satyavolu, Z. K. Wu, J. R. Zhang, J. J. Zhu, and Y. Lu, "Near-infrared photothermally activated DNAzyme-gold nanoshells for imaging metal ions in living cells." *Angew. Chem.-Int. Edit.*, **56**, 6798 (2017).
- 121. W. J. Zhou, W. B. Liang, D. X. Li, R. Yuan, and Y. Xiang, "Dual-color encoded DNAzyme nanostructures for multiplexed detection of intracellular metal ions in living cells." *Biosens. Bioelectron.*, 85, 573 (2017).
- 122. G. C. Zuo, A. Xie, J. J. Li, T. Su, X. H. Pan, and W. Dong, "Large emission redshift of carbon dots by fluorine doping and their applications for red cell imaging and sensitive intracellular Ag<sup>+</sup> detection." *J. Phys. Chem. C*, **121**, 26558 (2017).
- 123. Y. H. Liu, W. X. Duan, W. Song, J. J. Liu, C. L. Ren, J. Wu, D. Liu, and H. L. Chen, "Red emission B, N, S-co-doped carbon dots for colorimetric and fluorescent dual mode detection of Fe<sup>3+</sup> ions in complex biological fluids and living cells." ACS Appl. Mater. Interfaces, 9, 12663 (2017).
- 124. D. P. Kong, F. Y. Yan, Y. M. Luo, Q. H. Ye, S. Y. S. Zhou, and L. Chen, "Amphiphilic carbon dots for sensitive detection, intracellular imaging of Al<sup>3+</sup>." *Anal. Chim. Acta*, 953, 63 (2017).
- 125. H. Kaur, P. Raj, H. Sharma, M. Verma, N. Singh, and N. Kaur, "Highly selective and sensitive fluorescence sensing of nanomolar Zn<sup>2+</sup> ions in aqueous medium using Calix[4]arene passivated carbon quantum dots based on fluorescence enhancement: Real-time monitoring and intracellular investigation." *Anal. Chim. Acta*, 1009, 1 (2018).
- 126. V. K. Singh, V. Singh, P. K. Yadav, S. Chandra, D. Bano, V. Kumar, B. Koch, M. Talat, and S. H. Hasan, "Bright-blue-emission nitrogen and phosphorus-doped carbon quantum dots as a promising nanoprobe for detection of Cr(VI) and ascorbic acid in pure aqueous solution and in living cells." *New J. Chem.*, **42**, 12990 (2018).
- 127. S. H. Cao, H. Chen, F. Jiang, Z. X. Hu, and X. Wang, "Construction of acetaldehyde-modified g-C<sub>3</sub>N<sub>4</sub> ultrathin nanosheets via ethylene glycol-assisted liquid exfoliation for selective fluorescence sensing of Ag<sup>+</sup>." ACS Appl. Mater. Interfaces, **10**, 44624 (2018).
- 128. C. C. Zou, M. F. Foda, X. C. Tan, K. Shao, L. Wu, Z. C. Lu, H. S. Bahlol, and H. Y. Han, "Carbon-dot and quantum-dot-coated dual-emission core-satellite silica nanoparticles for ratiometric intracellular Cu<sup>2+</sup> imaging." *Anal. Chem.*, 88, 7359 (2016).
- 129. B. F. Shi, Y. B. Su, L. L. Zhang, M. J. Huang, R. J. Liu, and S. L. Zhao, "Nitrogen and phosphorus Co-doped carbon nanodots as a novel fluorescent probe for highly sensitive detection of Fe<sup>3+</sup> in human serum and living cells." *ACS Appl. Mater. Interfaces*, 8, 10717 (2016).
- 130. C. Y. Xiong, W. B. Liang, H. J. Wang, Y. N. Zheng, Y. Zhuo, Y. Q. Chai, and R. Yuan, "In situ electro-polymerization of nitrogen doped carbon dots and their application in an electrochemiluminescence biosensor for the detection of intracellular lead ions," *Chem. Commun.*, **52**, 5589 (2016).
- 131. F. Y. Yan, D. P. Kong, Y. M. Luo, Q. H. Ye, J. J. He, X. F. Guo, and L. Chen, "Carbon dots serve as an effective probe for the quantitative determination and for intracellular imaging of mercury(II)." *Microchim. Acta*, 183, 1611 (2016).
- 132. L. Zhang, Y. Wang, X. B. Zhang, X. Wei, X. Xiong, and S. B. Zhou, "Enzyme and redox dual-triggered intracellular release from actively targeted polymeric micelles." ACS Appl. Mater. Interfaces, 9, 3388 (2017).
- J. Li, A. A. Green, H. Yan, and C. H. Fan, "Engineering nucleic acid structures for programmable molecular circuitry and intracellular biocomputation." *Nat. Chem.*, 9, 1056 (2017).

- 134. Y. X. Lv, C. Y. Jiang, K. Hu, Y. Huang, Y. F. He, X. Y. Shen, and S. L. Zhao, "Insitu growth of cobalt oxyhydroxide on graphitic-phase C<sub>3</sub>N<sub>4</sub> nanosheets for fluorescence turn-on detection and imaging of ascorbic acid in living cells." *Microchim. Acta*, 186, 360 (2019).
- J. Yin et al., "I-Cysteine metabolism and its nutritional implications." *Mol. Nutr. Food Res.*, 60, 1334 (2016).
- 136. X. L. Zhang, C. Zheng, S. S. Guo, J. Li, H. H. Yang, and G. N. Chen, "Turn-on fluorescence sensor for intracellular imaging of glutathione using g-C<sub>3</sub>N<sub>4</sub> nanosheet-MnO<sub>2</sub> sandwich nanocomposite." *Anal. Chem.*, 86, 3426 (2014).
- 137. H. Y. Jiang, F. R. Li, W. Li, X. D. Lu, and K. Ling, "Multiplexed determination of intracellular messenger RNA by using a graphene oxide nanoprobe modified with target-recognizing fluorescent oligonucleotides." *Microchim. Acta*, 185, 552 (2018).
- 138. X. X. Wang, D. D. Yang, M. Liu, D. W. Cao, N. Y. He, and Z. F. Wang, "Highly sensitive fluorescence biosensor for intracellular telomerase detection based on a single patchy gold/carbon nanosphere via the combination of nanoflare and hybridization chain reaction." *Biosens. Bioelectron.*, **137**, 110 (2019).
- 139. X. Li, L. S. Zhu, Y. L. Zhou, H. Yin, and S. Y. Ai, "Enhanced photoelectrochemical method for sensitive detection of protein kinase A activity using TiO<sub>2</sub>/g-C<sub>3</sub>N<sub>4</sub>, PAMAM dendrimer, and alkaline phosphatase." *Anal. Chem.*, 89, 2369 (2017).
- 140. Z. B. Liu, S. S. Chen, B. W. Liu, J. P. Wu, Y. B. Zhou, L. Y. He, J. S. Ding, and J. W. Liu, "Intracellular detection of ATP using an aptamer beacon covalently linked to graphene oxide resisting nonspecific probe displacement." *Anal. Chem.*, 86, 12229 (2014).
- 141. Y. Y. Liu, L. P. Jiang, X. J. Fan, P. P. Liu, S. H. Xu, and X. L. Luo, "Intracellular fluorometric determination of microRNA-21 by using a switch-on nanoprobe composed of carbon nanotubes and gold nanoclusters." *Microchim. Acta*, 186, 477 (2019).
- 142. Y. D. Liu, X. H. Liu, Z. P. Guo, Z. G. Hu, Z. H. Xue, and X. Q. Lu, "Horseradish peroxidase supported on porous graphene as a novel sensing platform for detection of hydrogen peroxide in living cells sensitively." *Biosens. Bioelectron.*, 87, 101 (2017).

- R. Motterlini and L. E. Otterbein, "The therapeutic potential of carbon monoxide." Nat. Rev. Drug Discov., 9, 728 (2010).
- U. Forstermann and W. C. Sessa, "Nitric oxide synthases: regulation and function." *Eur. Heart J.*, 33, 829 (2012).
- L. Li, P. Rose, and P. K. Moore, "Hydrogen sulfide and cell signaling." Annu. Rev. Pharmacol. Toxicol., 51, 169 (2011).
- 146. V. S. Lin, W. Chen, M. Xian, and C. J. Chang, "Chemical probes for molecular imaging and detection of hydrogen sulfide and reactive sulfur species in biological systems." *Chem. Soc. Rev.*, 44, 4596 (2015).
- 147. N. Li, A. Than, J. Chen, F. N. Xi, J. Y. Liu, and P. Chen, "Graphene quantum dots based fluorescence turn-on nanoprobe for highly sensitive and selective imaging of hydrogen sulfide in living cells." *Biomater. Sci.*, 6, 779 (2018).
- 148. Z. W. Ulissi, F. Sen, X. Gong, S. Sen, N. Iverson, A. A. Boghossian, L. C. Godoy, G. N. Wogan, D. Mukhopadhyay, and M. S. Strano, "Spatiotemporal intracellular nitric oxide signaling captured using internalized, near-infrared fluorescent carbon nanotube nanosensors." *Nano Lett.*, **14**, 4887 (2014).
- 149. Y. Shu, N. Zheng, A. Q. Zheng, T. T. Guo, Y. L. Yu, and J. H. Wang, "Intracellular zinc quantification by fluorescence imaging with a FRET system." *Anal. Chem.*, **91**, 4157 (2019).
- S. Mohapatra, S. Sahu, S. Nayak, and S. K. Ghosh, "Design of Fe<sub>3</sub>O<sub>4</sub>@SiO<sub>2</sub>@carbon quantum dot based nanostructure for fluorescence sensing, magnetic separation, and live cell imaging of fluoride ion." *Langmuir*, **31**, 8111 (2015).
- 151. L. M. Zuo, Q. Qu, L. Li, X. Ran, J. W. Gui, Q. Wang, X. H. Cui, and C. L. Jiang, "Electrochemical DNA biosensor based on magnetite/multiwalled carbon nanotubes/chitosan nanocomposite for bacillus cereus detection of potential marker for gold prospecting." *Electroanalysis*, **30**, 910 (2018).
- 152. H. J. Zhang, J. Chen, Y. L. Yang, L. Wang, Z. Li, and H. D. Qiu, "Discriminative detection of glutathione in cell lysates based on oxidase-like activity of magnetic nanoporous graphene." *Anal. Chem.*, **91**, 5004 (2018).
- 153. H. J. Oh, J. Kim, H. Park, S. Chung, D. W. Hwang, and D. S. Lee, "Grapheneoxide quenching-based molecular beacon imaging of exosome-mediated transfer of neurogenic miR-193a on microfluidic platform." *Biosens. Bioelectron.*, **126**, 647 (2019).